Synthesis, Characterization, and Reaction of Divinyl-substituted Laddersiloxanes

Yujia Liu, Aimi Endo, Peiyao Zhang, Akira Takizawa, Nobuhiro Takeda,
Armelle Ouali, Masafumi Unno

► To cite this version:

Yujia Liu, Aimi Endo, Peiyao Zhang, Akira Takizawa, Nobuhiro Takeda, et al.. Synthesis, Characterization, and Reaction of Divinyl-substituted Laddersiloxanes. *Silicon*, 2021, 10.1007/s12633-021-01068-6 . hal-03425730

HAL Id: hal-03425730

<https://hal.science/hal-03425730>

Submitted on 11 Nov 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Synthesis, Characterization, and Reaction of Divinyl-substituted Laddersiloxanes

Yujia Liu,^{1,2} Aimi Endo,² Peiyao Zhang,³ Akira Takizawa,² Nobuhiro Takeda,² Armelle Ouali,^{*1,3} Masafumi Unno^{*1,2}

-
- 1 Gunma University Initiative for Advanced Research (GIAR)-International Open Laboratory with Institute Charles Gerhardt Montpellier ICGM, Univ. Montpellier, CNRS, ENSCM, France. Gunma University, Kiryu 376-8515, Japan
2 Department of Chemistry and Chemical Biology, Graduate School of Science and Technology. Gunma University, Kiryu 376-8515, Japan
3 ICGM, Univ. Montpellier, CNRS, ENSCM, 8 rue de l'Ecole Normale, 34296 Montpellier Cedex 05, France

ORCID numbers. Yujia Liu: 0000-0002-3610-6355, Nobuhiro Takeda: 0000-0001-5732-758X, Armelle Ouali: 0000-0001-7436-776X, Masafumi Unno: 0000-0003-2158-1644

e-mail. Armelle Ouali: armelle.ouali@enscm.fr, Masafumi Unno: unno@gunma-u.ac.jp

Abstract

Purpose

Silsesquioxanes with well-defined structures have been of great interest recently because of their superior properties. Among them, laddersiloxanes (ladder-type silsesquioxanes with defined structure) are less explored because step-by-step synthesis is usually necessary. In order to investigate the properties of laddersiloxanes, and apply these compounds as monomer precursors to high function materials, we prepared laddersiloxanes with reactive vinyl groups.

Method

The target compounds were obtained in a two-step reaction from commercially available alkoxysilanes, and total yields were 73-93%. Three product stereoisomers were fully investigated by spectroscopic methods and structures were determined.

Results

As an extension of our previous research on constructing new laddersiloxanes, we will describe here the synthesis, characterization, and functionalization of novel divinyl-substituted laddersiloxanes. Further transformation of all products proceeded smoothly, and extended laddersiloxanes were obtained by hydrosilylation. One isomer was isolated and the structure was determined unequivocally by X-ray analysis.

Conclusion

The laddersiloxanes described here have two reactive vinyl groups at each end of the molecule. Various reactions including hydrosilylation, polymerization, or olefin metathesis are possible, thus these compounds can be potential monomers for highly functionalized materials.

Keywords silsesquioxane • well-defined structure • hydrosilylation • laddersiloxane • crystal structure

1. Introduction

Inorganic-organic hybrid materials find increasing application in various fields. For their construction, polyhedral oligomeric silsesquioxanes (POSSs) are recognized as highly attractive building blocks. Indeed, with an inorganic Si-O-Si nanocore and surrounding reactive organic groups, they permit hybridization at the molecular level [1–5]. Moreover, their multifunctionality, high processability and easy functionalization constitute major assets as well.

Cage silsesquioxanes have therefore been used as key starting blocks to design hybrid materials presenting a great potential in various fields including catalysis, photoactive materials, sensing, liquid crystals, energy-related materials, medicine, self-healing materials, biomass-based nanocomposites or coating materials [6–12]. To date, the cubic SQs have been the most widely used to reach hybrid polymers with various topologies (telechelic, star-shaped, side chain, cross-linked networks and so on) [8]. Generally, the incorporation of SQs in polymer hybrids or polymer composite results in an enhancement of thermal stability, mechanical (strength, hardness) and dielectric properties [1–12].

Recently, the development of difunctionalized double-decker silsesquioxanes (DDSQ), another class of silsesquioxane compounds involving Si-O-Si bonds different from the symmetrical cubic T₈-SQs, opened new opportunities to design hybrid materials [13]. For example, difunctionalized D₂T₈ DDSQ has been successfully incorporated into the backbone

chain of polymers and they conferred excellent transparency and flexibility, good solubility in addition to good thermal, mechanical and dielectric properties [14].

For more extensive investigation of hybrid materials with unexpected properties, the design and synthesis of other topologically structured silsesquioxanes, like ladder-type silsesquioxanes (laddersiloxanes), are strongly required. Laddersiloxanes possessing highly ordered double-chain structures and possibly presenting polymeric forms are of particular interest in several fields such as optics [15,16] or electronics [17,18]. The preparation of tricyclic, pentacyclic [19–22], heptacyclic [23], and nonacyclic [24] SQs was previously reported and these well-defined compounds displayed a high thermal stability [25]. Moreover, the ladder structure was shown to give the highest refractive index and Abbe number among linear, cyclic, or cage silsesquioxanes [26]. Nevertheless, examples of hybrid materials derived from molecular laddersiloxanes are rare [27]. To open new prospects in this field, the discovery of functionalizable versions of well-defined molecular laddersiloxanes appears as a favorable research endeavor. Along these lines, we recently reported the preparation of tricyclic ladder silsesquioxanes with 6-8-6 fused rings bearing four reactive vinyl or allyl substituents on the D-group silicon atoms. The latter could be transformed easily into the corresponding tetrachloro- [28] or tetramercapto- [29] laddersiloxanes through hydrosilylation or thiol-ene reactions, respectively. Some of us also reported the functionalization of phenyl-substituted 8-8-8-laddersiloxanes through Friedel-Crafts acylation to prepare nanoporous materials for water-treatment, which shows the potential of hybrid materials based on laddersiloxanes [27].

In this report, the preparation and characterization of four ladder-shaped silsesquioxanes bearing two peripheral reactive vinyl groups are described. With phenyl or isobutyl substituents present on the core, the molecules were obtained as mixtures of stereoisomers. The successful functionalization of both external vinyl substituents via hydrosilylation was also demonstrated in the case of the most thermally stable laddersiloxane. Lastly, one isomer was isolated after functionalization and was fully characterized. The difunctionalized laddersiloxanes reported here constitute attractive building blocks to prepare hybrid materials.

2. Methods

The targeted difunctionalized laddersiloxanes were prepared from all-*cis*-tetraphenyl-cyclotetrasiloxanetetraol (T₄-Ph-OH, **1a**) and all-*cis*-tetraisobutyl-cyclotetrasiloxanetetraol (T₄-*i*-Bu-OH, **1b**) (Scheme 1). Both of these precursors were obtained in high yields (80 and 74%, respectively) from phenyltrimethoxysilane and isobutyltrimethoxysilane respectively according to previously reported procedures [26,30,31].

Scheme 1 Synthesis of laddersiloxanes **3a** and **3b**

3. Results

A solution of dichloromethylsilane **2a** in anhydrous THF was added dropwise to a mixture of tetrasilanol **1a** or **1b** and distilled triethylamine (used as an HCl scavenger) in anhydrous THF to afford expected laddersiloxanes **3a** and **3b** in 73 and 93% yields, respectively. In both cases, **3a** and **3b** were obtained after a straightforward work-up as mixtures of stereoisomers that were characterized by various analytical techniques including elemental analyses, multinuclear NMR and mass spectroscopy. The structures of three possible *syn*-type isomers are presented in Scheme 2. In isomers (I) and (III), the substituents of the D-group silicon atoms (R¹) are magnetically equivalent. In the same manner, the groups R² borne by T-group silicon atoms also have the same chemical environment and will thus give the same NMR signal. In contrast, in isomer (II), both substituents R¹ present on the peripheral D-group silicon atoms are expected to give rise to two distinct sets of signals. Likewise, two different magnetic environments can be observed for the R² groups of isomer (II) which are thus expected to show two different NMR patterns.

Scheme 2 Possible *syn*-type isomers for prepared laddersiloxanes

The ^1H NMR spectrum of **3a** clearly illustrated the presence of several isomers with methyl groups ($\text{R}^1 = \text{Me}$) showing four distinct singlets at 0.42, 0.43, 0.49, and 0.55 ppm, respectively (Figure 1, a): one would correspond to the methyl groups of isomer (I), another one to isomer (III), the last two peaks corresponding to nonequivalent methyl substituents borne by D-group silicon atoms of isomer II (Scheme 2, R^1). Each of these signals having roughly the same intensity, the isomer ratio (I/II/III) was estimated to be approximatively (1:2:1) in the case of **3a** (Figure 1, a). Accordingly, for **3b**, four resonances were observed for the methyl groups at 0.26, 0.27, 0.28, and 0.32 ppm (Figure 1, b). The determination of the isomer ratio (I/II/III) was hampered by overlapping signals. Along the same lines, the vinyl groups of isomers give rise to a complex pattern in the 6.06–6.25 ppm range for **3a** (Figure 1, a) and between 5.89 and 6.08 ppm for **3b** (Figure 1, b).

By ^{29}Si NMR (Figure 2), the appearance of patterns could be observed for T-group silicon atoms (between –67.85 and –67.77 ppm for **3a** (Figure 2, a) and between –55.66 and –55.51 ppm for **3b** (Figure 1, b). The more shielded resonances at ca. –55 ppm in the case of **3b** (compared to ca. –67 ppm for **3a**) can be rationalized by the positive inductive effect of the more donating isobutyl substituents (compared to the phenyl groups) on the T_4 -unit. D-group silicon atoms resonated as four singlets at –19.23, –19.09, –18.65, and –18.54 ppm for **3a** (Figure 2, a) and –21.03, –20.89, –20.56, and –20.51 ppm for **3b** (Figure 2, b). Elemental analysis and MALDI-TOF mass spectroscopy spectra were in accordance with the molecular structures (see supporting information). Attempts to separate the stereoisomers by crystallization, column chromatography on silica gel or recycle-type reverse-phase HPLC failed at this stage. Nevertheless, the laddersiloxanes may be further used as isomers mixtures for the preparation of hybrid materials

Fig. 1 ^1H NMR spectra (in CDCl_3) of **3a** (a) and **3b** (b) as a mixture of stereoisomers

Fig. 2 ^{29}Si NMR spectra (in CDCl_3) of **3a** (a), **3b** (b), **4a** (c), and **4b** (d) as mixtures of stereoisomers

The thermal stability of laddersiloxanes **3a** and **3b** was studied by thermogravimetric analysis (TGA) (Table 1, entries 1 and 2). **3a** displayed a higher Td_5 (293 °C) than **3b** (203 °C) likely due to the presence of phenyl substituents, which brings more thermal robustness as compared to alkyls [32].

To broaden the range of difunctionalized laddersiloxanes, nucleophilic substitution of the previously described tetrasilanolates generated in situ from **1a** and **1b** in the presence of triethylamine was next explored with dichlorophenylvinylsilane **2b** (Scheme 3).

Corresponding laddersiloxanes **4a** and **4b** were synthesized in 75 and 85% yields, respectively, and were next characterized. As in the case of their related methyl-substituted counterparts **3a** and **3b**, the formation of stereoisomers occurred as evidenced by the sets of signals observed in the NMR spectra. For example, by ^{29}Si NMR spectroscopy, the magnetically nonequivalent D-group silicon atoms have different resonance frequencies and showed four singlets at -33.71 , -33.23 , -33.15 , and -33.09 ppm for **4a** and three at -35.38 , -34.79 and -34.65 ppm for **4b** (two of them being likely overlapped). Equally, T-group silicon atoms produced four peaks at -67.74 , -67.53 , -67.47 , and -67.01 ppm in **4a** and -55.51 , -55.29 , -55.22 , and -54.72 ppm in **4b**. Elemental analysis and MALDI-TOF mass spectroscopy confirmed the structures (see supporting information).

Scheme 3 Synthesis of laddersiloxanes **4a** and **4b**

Entry	1	2	3	4	5
Compound	3a	3b	4a	4b	5'
R ¹	Ph	<i>i</i> -Bu	Ph	<i>i</i> -Bu	Ph
R ²	Me	Me	Ph	Ph	Ph
R ³	vinyl	vinyl	vinyl	vinyl	CH ₂ CH ₂ - SiMe ₂ Ph
Td ₅ (°C)	293	203	343	242	422

Table 1 TG measurement data of **3a**, **3b**, **4a**, **4b**, and **5'** under N₂ atmosphere

The replacement of methyl substituents by phenyls on peripheral silicons increase significantly the thermal stability of **4a** ($T_{d5} = 343\text{ }^{\circ}\text{C}$) compared to **3a** ($T_{d5} = 293\text{ }^{\circ}\text{C}$, Table 1, entries 1 and 3). Along the same lines, the T_{d5} of **4b** ($242\text{ }^{\circ}\text{C}$) was higher than **3b** ($203\text{ }^{\circ}\text{C}$, Table 1, entries 2 and 4). It is worthy to note that laddersiloxanes **3a**, **3b**, **4a**, and **4b** can be easily prepared in gram scale (up to 5 g per reaction) and the syntheses can certainly still be scaled up. As expected, laddersiloxane **4a** bearing phenyl groups both on the T₄-unit and on the peripheral silicon atoms displayed the best thermal stability and appeared as a most promising candidate for further incorporation in hybrid materials.

As a proof of concept, the functionalization of **4a** through hydrosilylation was achieved (Scheme 4). In the presence of dimethylphenylsilane and a very small amount of Karstedt catalyst (0.02 mol% Pt per C=C), **4a** quantitatively yielded laddersiloxane **5** as a mixture of three stereoisomers as expected and shown by the resonance patterns of the ¹H, ¹³C and ²⁹Si NMR spectra (see supporting information).

Scheme 4 Synthesis of laddersiloxane **5**

To our delight, after washing the mixture with cold hexane, one of the stereoisomers of **5** could be isolated from the filtrate as a white solid **5'** in 19% yield. The latter was characterized by multinuclear NMRs, mass spectroscopy and elemental analysis. On the ²⁹Si NMR spectrum of the isolated stereoisomer (Figure 3), the silicon atoms from the T₄-unit (blue Si) resonated as a singlet at -66.63 ppm , while the D-group silicon atoms (red Si) gave rise to a singlet -18.89 ppm . The third singlet at -0.58 ppm was assigned to those of carbosilanes (pink Si). This stereoisomer displaying high symmetry could correspond to isomers (I) or (III) (Scheme 2).

Fig. 3 ^{29}Si NMR spectrum (in CDCl_3) of **5'** (isolated isomer of (I)- or (III), see Scheme 2)

MALDI-TOF confirms the structure with the experimental mass ($1108.84 [\text{M}+\text{Na}]^+$ and $1124.82 [\text{M}+\text{K}]^+$), in good accord with the calculated ones ($1108.76 [\text{M}+\text{Na}]^+$ and $1124.87 [\text{M}+\text{K}]^+$, Figure 4). Elemental analysis also attests to the purity of isolated laddersiloxane (see supporting information). Compound **5'** was further recrystallized from chloroform and hexane by slow evaporation to give single crystals suitable for X-ray analysis (Figure 5, Table 2). As expected, **5'** displayed a *syn*-type structure and was found to correspond to the stereoisomer (I) (Scheme 2). Interestingly, **5'** was shown to be highly thermally stable with a measured Td_5 at $422\text{ }^\circ\text{C}$.

Fig. 4 MALDI-TOF mass spectrum of laddersiloxane **5'**

Fig. 5 X-ray structure of laddersiloxane **5'**. Black: carbon; blue: silicon; red: oxygen

Compounds	5'
empirical formula	C ₅₆ H ₆₀ O ₈ Si ₈
formula weight	1085.76
temperature (K)	130
crystal system	Orthorhombic
space group	P2 ₁ 2 ₁ 2 ₁
<i>a</i> (Å)	10.7393(17)
<i>b</i> (Å)	18.409(3)
<i>c</i> (Å)	29.205(5)
α (deg)	90
β (deg)	90
γ (deg)	90

Table 2 Crystal Data for compound **5'**

4. Conclusions

To conclude, an efficient synthetic route to difunctionalizable laddersiloxanes is described. Four laddersiloxanes bearing various alkyl or phenyl groups and two peripheral vinyl reactive substituents were synthesized in high yields (from 73 to 93%) and in the gram scale (up to 5 g). The mixture of formed stereoisomers was characterized by multinuclear NMRs and mass spectroscopy and the thermal stability was estimated by thermogravimetric analysis. The

most stable laddersiloxane **4a** ($T_d = 343\text{ }^{\circ}\text{C}$) was quantitatively functionalized through a model hydrosilylation with dimethylphenylsilane. One stereoisomer (**5'**) was successfully isolated out of the resulting laddersiloxane (**5**) obtained as a mixture of three stereoisomers and was fully characterized (multinuclear NMRs, MALDI-TOF, elemental analysis). Thanks to the structural determination by X-ray crystallography, the relative positions of the different substituents on the stereoisomer **5'** were determined. In addition, this compound is highly stable (**5'**, $T_d = 422\text{ }^{\circ}\text{C}$). Laddersiloxane **4a** thus represents a promising building block that will be easily incorporated in various hybrid materials thanks to its relatively high thermal stability and high reactivity of its peripheral vinyl groups. The resulting materials could include the assets of highly-ordered ladder-shaped rigid inorganic siloxane rings such as high thermal and mechanical stabilities, high transparency, flexibility and good solubility. Applications of these functionalizable laddersiloxanes are currently underway in our laboratories.

Declarations

Funding statement

Partial financial support was received from the New Energy and Industrial Technology Development Organization (NEDO) under Grant named “Development of Innovative Catalytic Processes for Organosilicon Functional Materials” project (PL: K. Sato).

Conflict of Interest

The authors declare no financial or commercial conflict of interest.

Availability of data and material

All data and material described in this article can be available.

Author contributions

Conceptualization: Armelle Ouali, Masafumi Unno; Methodology: Armelle Ouali, Yujia Liu, Formal analysis and investigation: Yujia Liu, Aimi Endo, Peiyao Zhang, Akira Takizawa, Nobuhiro Takeda; Writing - original draft preparation: Armelle Ouali, Yujia Liu; Writing - review and editing: Armelle Ouali, Masafumi Unno, Funding acquisition: Masafumi Unno, Armelle Ouali

Consent to participate

All authors agreed to participate in this publication.

Consent for Publication

All authors agreed to the publication of this article.

Conflict of Interest

The authors declare no financial or commercial conflict of interest.

References

1. Cordes DB, Lickiss PD, Rataboul F (2010) Recent Developments in the Chemistry of Cubic Polyhedral Oligosilsesquioxanes. *Chem Rev* 110: 2081-2173
2. Laine RM, Roll MF (2011) Polyhedral Phenylsilsesquioxanes. *Macromolecules* 44: 1073-1109
3. Ye Q, Zhou H, Xu J (2016) Cubic Polyhedral Oligomeric Silsesquioxane Based Functional Materials: Synthesis, Assembly, and Applications. *Chem Asian J* 11: 1322-1337
4. Zhou H, Ye Q, Xu J (2017) Polyhedral oligomeric silsesquioxane-based hybrid materials and their applications. *Mater Chem Front* 1:212-230
5. Du Y, Liu H (2020) Cage-like silsesquioxanes-based hybrid materials. *Dalton Trans* 49:5396-5405.
6. Calabrese C, Aprile C, Gruttadauria M, Giacalone F (2020) POSS nanostructures in catalysis. *Catal Sci Technol* 10:7415-7447
7. Dudziec B, Zak P, Marciniak B (2019) Synthetic Routes to Silsesquioxane-Based Systems as Photoactive Materials and Their Precursors. *Polymers* 11:504
8. Chen F, Lin F, Zhang Q, Cai R, Wu Y, Ma X (2019) Polyhedral Oligomeric Silsesquioxane Hybrid Polymers : Well-Defined Architectural Design and Potential Functional Applications. *Macromol Rapid Commun* 40:1900101
9. Wang J, Du W, Zhang Z, Gao W, Li Z (2021) Biomass/polyhedral oligomeric silsesquioxane nanocomposites : Advances in preparation strategies and performances. *J Appl Polym Sci* 138:e49641
10. Mohamed MG, Kuo SW (2019) Functional Polyimide/Polyhedral Oligomeric Silsesquioxane Nanocomposites. *Polymers* 11:26
11. Li Z, Hu J, Yang L, Zhang X, Liu X, Wang Z, Li Y (2020) Integrated POSS-Dendrimer Nanohybrid Materials: Current Status and Future Perspective. *Nanoscale* 12:11395-11415
12. Chi H, Wang M, Xiao Y, Wang F, Joshy KS (2018) Self-Assembly and Applications of Amphiphilic Hybrid POSS Copolymers. *Molecules* 23:2481
13. Dudziec B, Marciniak B (2017) Double-decker Silsesquioxanes: Current Chemistry and Applications. *Curr Org Chem* 21:2794-2813
14. Wang M, Chi H, Joshy KS, Wang F (2019) Progress in the Synthesis of Bifunctionalized Polyhedral Oligomeric Silsesquioxane. *Polymers* 11:2098
15. Kamino BA, Bender TP (2013) The use of siloxanes, silsesquioxanes, and silicones in organic semiconducting materials. *Chem Soc Rev* 42:5119-5130

16. Lee A, Jo YY, Choi S, Baek K, Hwang S (2017) Thermal, Mechanical, and Photophysical Properties of Carbazole-Substituted POSS and Ladder Polysiloxane. *J Nanosci Nanotechnol* 17:5562-5565
17. Kang W, An G, Kim MJ, Lee WH, Lee DY, Kim H, Cho JH (2016) Ladder-Type Silsesquioxane Copolymer Gate Dielectrics for High-Performance Organic Transistors and Inverters. *J Phys Chem C* 120:3501-3508
18. Kim MJ, Heo YM, Cho JH (2017) Ladder-type silsesquioxane copolymer gate dielectrics for gating solution-processed IGZO field-effect transistors. *Org Electron* 43:41-46
19. Unno M, Suto A, Matsumoto H (2002) Pentacyclic Laddersiloxane. *J Am Chem Soc* 124:1574-1575
20. Unno M, Tanaka R, Tanaka S, Takeuchi T, Kyushin S, Matsumoto H (2005) Oligocyclic Ladder Polysiloxanes: Alternative Synthesis by Oxidation. *Organometallics* 24:765-768
21. Unno M, Matsumoto T, Matsumoto H (2007) Synthesis of laddersiloxanes by novel stereocontrolled approach. *J Organomet Chem* 692:307-312
22. Seki H, Abe N, Abe Y, Gunji T (2011) Synthesis and Structure of *syn,anti,syn*-Pentacyclic Ladder Oligomethylsilsesquioxane. *Chem Lett* 40:722-723
23. Chang S, Matsumoto T, Matsumoto H, Unno M (2010) Synthesis and characterization of heptacyclic laddersiloxanes and ladder polysilsesquioxane. *Appl Organometal Chem* 24:241-246
24. Unno M, Matsumoto T, Matsumoto H (2012) Nonacyclic Ladder Silsesquioxanes and Spectral Features of Ladder Polysilsesquioxanes. *Int J Polym Sci* 2012:723892
25. Unno M, Suto A, Matsumoto T (2013) Laddersiloxanes - silsesquioxanes with defined ladder structure. *Russ Chem Rev* 82:289-302
26. Endo H, Takeda N, Takanashi M, Imai T, Unno M (2015) Refractive Indices of Silsesquioxanes with Various Structures. *Silicon* 7:127-132
27. Du Y, Unno M, Liu H (2020) Hybrid Nanoporous Materials Derived from Ladder- and Cage-Type Silsesquioxanes for Water Treatment. *ACS Appl Nano Mater* 3:1535-1541
28. Liu Y, Onodera K, Takeda N, Ouali A, Unno M (2019) Synthesis and Characterization of Functionalizable Silsesquioxanes with ladder-type Structures. *Organometallics* 38:4373-4376
29. Liu Y, Kigure M, Okawa R, Takeda N, Unno M, Ouali A (2021) Synthesis and Characterization of Tetrathiol-substituted Double-Decker or Ladder Silsesquioxane Nano-Cores. *Dalton Trans Accepted Manuscript* DOI: 10.1039/D1DT00042J
30. Ito R, Kakihana Y, Kawakami Y (2009) Cyclic Tetrasiloxanetetraols: Formation, Isolation, and Characterization. *Chem Lett* 38:364-365
31. Endo H, Takeda N, Unno M (2017) Stereoisomerization of Cyclic Silanol. *Chem Asian J* 12:1224-1233
32. Endo H, Takeda N, Unno M (2014) Synthesis and Properties of Phenylsilsesquioxanes with Ladder and Double-Decker Structures. *Organometallics* 33:4148-4151