Biosynthesis of SiO₂ nanoparticles using extract of Nerium oleander leaves for the removal of tetracycline antibiotic

Noureddine El Messaoudi, Mohammed El Khomri, El-Houssaine Ablouh, Amal Bouich, Abdellah Lacherai, Amane Jada, Eder Lima, Farooq Sher

► To cite this version:

Noureddine El Messaoudi, Mohammed El Khomri, El-Houssaine Ablouh, Amal Bouich, Abdellah Lacherai, et al.. Biosynthesis of SiO₂ nanoparticles using extract of Nerium oleander leaves for the removal of tetracycline antibiotic. Chemosphere, 2022, 287, pp.132453. 10.1016/j.chemosphere.2021.132453 . hal-03449937

HAL Id: hal-03449937

<https://hal.science/hal-03449937>

Submitted on 25 Nov 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Biosynthesis of SiO₂ nanoparticles using extract of *Nerium oleander* leaves for the removal of tetracycline antibiotic

El Messaoudi, N¹ ; El Khomri, M¹ ; Ablouh, EH² ; Bouich, A³; Lacherai, A¹; Jada, A⁴; Lima, EC⁵ ; Sher, F⁶

¹ Ibn Zohr Univ, Lab Appl Chem & Environm, Agadir 80000, Morocco

² Mohammed VI Polytech Univ UM6P, Mat Sci Energy & Nanoengn Dept MSN, Benguerir 43150, Morocco

³ Univ Politecn Valencia, Inst Design & Mfg IDF, Dept Appl Phys, Valencia 46000, Spain

⁴ High Alsace Univ, Inst Mat Sci Mulhouse IS2M, F-68100 Mulhouse, France

⁵ Fed Univ Rio Grande do Sul UFRGS, Inst Chem, BR-91501970 Porto Alegre, RS, Brazil

Abstract

The present study aims to improve the adsorption of tetracycline (TC) antibiotic onto dioxide silicon nanoparticles (SiO₂ NPs) biosynthesized from the extract of *Nerium oleander* leaves. The SiO₂ NPs were characterized using SEM-EDX, BET-BJH, FTIR-ATR, TEM, and XRD. TC adsorption on SiO₂ NPs followed the pseudo 2nd order model and the Langmuir isotherm model with Q_m was 552.48 mg g⁻¹. The removal of TC using SiO₂ NPs was 99.56 % at conditions (SiO₂ NPs amount=0.25 g L⁻¹, C_0 =25 mg L⁻¹, and t =40 min) based on design-optimization. Electrostatic interaction governs the adsorption mechanism is attributed. The reusability of SiO₂ NPs was tested, and the performance adsorption was 85.36 % after the five cycles. The synthesized SiO₂ NPs as promising adsorbent has a potential application for antibiotics removal from wastewaters.

Keywords: Tetracycline antibiotic; SiO₂ nanoparticles; *Nerium oleander* leaves adsorption; optimization; wastewater treatment

1 Introduction

One of the major pollutants in wastewater is antibiotics. Various antibiotics such as quinolones, sulfonamides, macrolides, and tetracyclines are broadly used to prevent and treat infectious diseases (Ahamad et al., 2019). Tetracycline (TC) is commonly used for animal husbandry and poultry industries worldwide to promote animal growth and prevent diseases (Aalipour et al., 2014; Song et al., 2020; Van et al., 2020). About 60-80 % of tetracyclines were subject to different natural surroundings original in or metabolized forms due to lower metabolic rates in animals and humans (Epps and Blaney, 2016; Scaria et al., 2021). Due to the high solubility rate, TC is detected in different water bodies and some regions; its concentration exceeds standard environmental limits (Daghrir and Drogui, 2013). Antibiotic residues, frequently found in soil, sediment, and aquatic environments, have adverse side effects as bacterial resistance changes in the microbial ecological functions (Grenni et al., 2018; Sodhi et al., 2021). Antibiotic accumulation may also severely impair human physiological functions and have carcinogenic, teratogenic, or hormonal effects (Liu et al., 2017; Yu et al., 2016), their excess entrance into food chains may cause different disorders in the human body such as gastrointestinal system (Rashidi Nodeh et al., 2020). Therefore, controlling and handling antibiotic contaminants is necessary to have a safe environment.

Several approaches such as membrane filtration, photocatalysis, flocculation, biological treatment, electrochemical, adsorption, and reverse osmosis have been used to remove antibiotics from wastewaters (Rostam and Taghizadeh, 2020; Sharma et al., 2020; Wang et al., 2021). Among these methods, the adsorption process is competitive, high efficiency, low energy demand, and the possibility of reusing adsorbent materials (El Khomri et al., 2020; El Messaoudi et al., 2016a).

Many materials have been used as adsorbents materials, including nanoparticles (MgO, CuO, TiO₂, ZnO, SiO₂, etc.) due to their high-performance adsorption (Das et al., 2017; Ibrahim et al., 2016; Li et al., 2021). Still, the efficacy of SiO₂ is proved to be better due to its unique conductive nature. SiO₂ nanoparticles are used as an excellent adsorbent for the removal of dyes and metals, and a photocatalyst to treat wastewaters (Chen et al., 2012; Hosseini et al., 2018; Sharma et al., 2021). The biosynthesis of nanoparticles from the extract of agricultural solid wastes is regarded as a simple, rapid, cost-effective, and eco-friendly method for creating nanostructured materials such as metals, metal chalcogenides, and bimetal oxide (Das et al., 2018). In this work, we used an extract of *Nerium oleander* leaves for biosynthesized of SiO₂. The *Nerium oleander* leave is agricultural solid waste used for pollutants removal in some studies, but its performance as an adsorbent was limited because of its undeveloped porous structure (Martín et al., 2018; Sebeia et al., 2019; Suba et al., 2018).

The performance of SiO₂ NPs was evaluated in this study by removing tetracycline from the solution aqueous. Besides, characterization techniques were practiced for investigating its structure and properties, such as scanning electron microscope coupled with energy-dispersive X-ray (SEM-EDX), Brunauer-Emmett-Teller and Barrett-Joyner-Halenda (BET-BJH), Fourier transform infrared spectroscopy coupled with attenuated total reflectance (FTIR-ATR), transition electron microscope (TEM), X-ray diffraction (XRD), and point of zero charge (PZC). The present work will substantially impact as it will add unique knowledge on the adsorption potential of SiO₂ NPs synthesized from the extract of *Nerium oleander* leaves. In this current study, the SiO₂ NPs were synthesized from the *Nerium oleander* leaves extract. The impact of different influencing experimental parameters such as pH, SiO₂ NPs dose, reaction time, and TC concentration was investigated. Kinetic and equilibrium models evaluated the adsorption of TC on SiO₂ NPs. The removal of TC optimized using Box–Behnken design (BBD). The adsorption mechanism of TC molecules on

the SiO₂ NPs surface was proposed. The reusability of SiO₂ NPs was evaluated.

2 Experimental

2.1 Materials

Nerium oleander leaves were collected in Tinghir (South-East Morocco). The silicate of sodium (Na₂SiO₃), tetracycline (antibiotic, C₂₂H₂₄N₂O₈, MW=444.435 g mol⁻¹), C₂H₅OH, HCl, and NaOH were purchased from Sigma-Aldrich. The distilled and deionized waters were used through experiments.

2.2 Biosynthesis SiO₂ NPs

10 g *Nerium oleander* leave powder were added in 100 mL of C₂H₅OH and stirred for 3h. After that, the solution was filtered using filter paper then the above mixture was centrifuged for obtained a clear extract of *Nerium oleander* leaves. 2 g Na₂SiO₃ and 50 mL of extract and 5 mL of NaOH (0.5 M) were mixed and stirred for 4h. After precipitation, the mixture was filtered and centrifuged for separated the liquid and the precipitate (SiO₂ NPs). The residue obtained was washed with deionized water. Finally, The SiO₂ nanoparticles were over-dried (80 °C) for 24 h and calcined in the furnace at 500 °C for 3 h.

2.3 Characterization

The physicochemical properties of SiO₂ NPs were examined using different characterization techniques. The morphology and microstructures of SiO₂ NPs were examined by SEM-EDX analysis (JEOL, JSM-IT200) and TEM analysis (Philips CM-30). BET and BJH methods (Belsorp Mini II) were used to determine the surface area, total pore volume, and diameter pore of SiO₂ NPs. The chemical bond characteristics of SiO₂ NPs before and after TC adsorption was acquired by FTIR-ATR analysis (Jasco 4100). The SiO₂ NPs crystal structures were evaluated using XRD analysis recorded on a 6100-Shimadzu. The PZC of adsorbent was determined using the method reported by Fiol and Villaescusa, (2009).

2.4 Batch adsorption experiments

The TC adsorption onto SiO₂ NPs nanoparticles was conducted in batch mode using 12.5 mg of SiO₂ NPs in 50 mL of TC solutions with concentrations varied from 50 to 200 mg L⁻¹ at 23±1°C. The influence of pH solution on adsorption was assessed and varied from 3 to 11 and was adjusted by 0.01M HCl acid or 0.01M NaOH. The adsorbent dose and kinetic reaction were varied from 0.05 to 0.4 g L⁻¹ and from 5 to 120 min, respectively. The separation of the solid-liquid phases was performed by centrifuging. The residual concentration was determined using a UV/Vis spectrophotometer (2300/Techcomp) at 376 nm as $\lambda_{\max}$ of TC. The quantity adsorbed q_e (mg g⁻¹) and the TC removal efficiency (%) were obtained using the following formulas (El Messaoudi et al., 2016b):

$$q_e = \frac{(C_0 - C_e) \times V}{w} \quad (1)$$

$$\% \text{ Removal} = \frac{(C_0 - C_e)}{C_0} \times 100 \quad (2)$$

In Eqs. (1) and (2), C_0 (mg L⁻¹) and C_e (mg L⁻¹) denote the concentrations of TC before and after adsorption, respectively. The w (g) and V (L) represents the weight of SiO₂ NPs and the volume of the reaction solution, respectively.

2.5 Design of experiment runs

BBD used a static method for the design of experimental parameters influencing the adsorption of TC on SiO₂ NPs using design-expert software (version 12.0.3). TC concentration (A), reaction time (B), and SiO₂ NPs dose (C) as factors have significant effects on the TC adsorption on SiO₂ NPs at 23±1°C and pH=5. Design of experiment runs and corresponding responses for TC removal efficiency by SiO₂ NPs are summarized in **Table 1**. A three-factors and levels (-1, 0, and 1) were applied to 21 experiments. The TC removal efficiency R (%) was expressed using the quadratic polynomial model was formalized in Eq.3 (Jawad et al., 2020):

$$R(\%) = \sum_{i=1}^3 \delta_i X_i + \sum_{i=1}^3 \delta_{ii} X_i^2 + \sum_{i<j} \delta_{ij} X_i X_j + \delta_0 \quad (3)$$

In Eq.3, δ_0 denotes constant-coefficient, δ_i is attributed to the direct effect, δ_{ii} corresponds to higher-order effect, and δ_{ij} denote reciprocate effect.

3 Results and discussion

3.1 SiO₂ NPs characterization

The microstructures of synthesized nanoparticles were analyzed using SEM coupled with EDX. The results obtained are shown in **Fig.1**. According to **Fig. 1a**, The SEM image of SiO₂ NPs showed that the particles are agglomerated and have poor dispersion. **Fig.1b** represents the EDX spectrum and elemental analysis of SiO₂ NPs. The synthesis of SiO₂ NPs confirmed by the presence of O (53.82 %) and Si (46.18 %) (Dubey et al., 2015). **Fig 1c** and **d** indicate the uniform distribution of O and Si was illustrated by EDX elemental mapping.

Fig.2 illustrates the N₂ isotherms adsorption-desorption and average diameter distribution for SiO₂ NPs nanospheres. By means, BET and BJH methods, the obtained average surface area, pore diameter, and total pore volume were 583.46 m² g⁻¹, 3.46 nm, and 0.27 cm³ g⁻¹, respectively, confirmed the porosity of SiO₂ NPs.

The FT-IR spectra results are depicted in **Fig.3**. The broad bands at 3452 cm⁻¹ and 1634 cm⁻¹ correspond to OH stretching vibration and absorbed water molecule, respectively (El Messaoudi et al., 2016a; Niksefat et al., 2014). The peaks at 1083 cm⁻¹, 953 cm⁻¹ and 806 cm⁻¹ and 457 cm⁻¹ were ascribed to the Si-O stretching vibration, Si-OH stretching vibration and Si-O-Si symmetric stretching, and Si-O-Si bending, respectively (Rafigh and Heydarinasab, 2017; Yue et al., 2019), which confirms successful synthesis of SiO₂ nanospheres. The spectrum of TC-SiO₂ NPs shows small changes that demonstrate the TC adsorption on the surface of SiO₂ NPs.

Fig.4a shows the nanoparticles of SiO₂ NPs using a TEM image. According to this figure, the synthesized SiO₂ NPs particles were found to be spherical in structure. The XRD characterization results of SiO₂ NPs are provided in **Fig.4b**. A broad peak in the range of 20–30° is corresponded to SiO₂ (Rafigh and Heydarinasab, 2017), indicating the successful synthesis of SiO₂ NPs.

3.2 TC adsorption study

3.2.1 Solution pH

Fig. 5a presents the influence of pH on the TC adsorption at pH values ranging from 3 to 11. In this experiment, 10 mg of SiO₂ NPs were attempted in 50 mL of the solution TC (50 mg L⁻¹) at T=23 ± 1°C for 120 min. As **Fig. 5a** shows, the highest removal of TC was 98.07 % at pH 5. Debnath et al. (2020) and Rashidi Nodeh et al. (2020) obtained even results. This increase of TC removal in the acidic medium can be explained by the charge positive of SiO₂ NPs and the charge negative of TC.

3.2.2 SiO₂ NPs dose

A TC concentration of 50 mg L⁻¹ with a pH 5 at T=23 ± 1 for 120 min, the effect of SiO₂ NPs dose (0.05-0.4 g L⁻¹) on TC adsorption was studied. **Fig.5b** shows the results obtained. The TC removal increased from 54.38 to 98.92 % by increasing the SiO₂ NPs amount from 0.05 to 0.25 g L⁻¹, while the quantity adsorbed decreased from 543.88 to 197.95 mg g⁻¹. Results imply that the number of active adsorption sites for TC adsorption corresponds to the applied dose, prompting higher removal efficiency (Jin et al., 2019). After equilibrium between the adsorbent and antibiotic solution, the removal percentage remains consistent at higher dosages (>0.25 g L⁻¹). The optimum adsorbent dosage was considered 0.25 g L⁻¹ to reach maximum TC removal efficiency, respectively.

3.2.3 Contact time

The influence of the contact time on TC adsorption using SiO₂ NPs displayed in **Fig.5a**. The contact time ranged from 5 to 120 minutes, whereas other parameters were kept constant (SiO₂ NPs=0.25 g L⁻¹, TC concentration=50 mg L⁻¹, pH=5, and T=23±1°C). The TC adsorption was fast at first 40 min. This may be attributed to many sites that are accessible on the surface of the SiO₂ NPs in the initial phase. With decreasing in several active sites, the adsorption rate became consistent (Zhou et al., 2020). Experimental data showed that stability was achieved in 40 min with an adsorption capacity of TC was 195.97 mg g⁻¹.

3.2.4 TC concentration

The influence of TC concentration (25–200 mg L⁻¹) on its retention using SiO₂ NPs was studied with a fixed pH 5 and 0.25 g L⁻¹ of SiO₂ NPs dose for 40 min. As illustrated in **Fig.5d**, by increasing TC concentration, the TC adsorption capacity progressively increased owing to the occupation of all available sites on the surface of nanoparticles by TC molecules. But, a plateau was not achieved in the adsorption capacity, suggesting active sites are still available and no saturation occurred (Ravikumar et al., 2019).

3.2.5 Effect of Ionic Strength

The electrolyte (NaCl) concentration in the aqueous solution affects significantly TC adsorption onto SiO₂ NPs. As reported in **Fig. 6**, at SiO₂ NPs=0.25 g L⁻¹, TC concentration=50 mg L⁻¹, pH=7, and T=23±1°C, the removal efficiency of SiO₂ NPs for TC decreased from 73.15 % (0 M NaCl) to 55.48 % (0.4 M NaCl) by increasing the electrolyte concentrations from 0 to 0.4 M NaCl. By increasing the ionic strength, Cl⁻ competes with negatively charged TC (TCH⁻, TC⁻) species for adsorption sites onto SiO₂ NPs surface site with positively charged at pH 7. This result is in line with another study that reported a decline in TC adsorption onto clay surface sites with negatively charged by increasing

electrolyte concentration in the solution (Parolo et al., 2008). In their study, by increasing Na^+ ion concentration at pH 4 of the solution, the competence for occupying surface sites between Na^+ ion and positively charged TC (TCH^+) increased. The reduction in TC adsorption onto the surface of clay increased in a higher concentration of Na^+ (Parolo et al., 2008).

3.3 Adsorption kinetics

The obtained experimental data were evaluated by using the pseudo 1st order (PFO), pseudo 2nd order (PSO), and intraparticle diffusion (IPD) kinetic models, and their linear forms are given using the following Eqs. (4), (5), and (6) as represented in **Table 2** (Bentahar et al., 2018; El Messaoudi et al., 2017). **Table 2** shows the parameters for linear fitting. As represented in **Table 2**, the PSO model was fitted to data experimental based on R^2 (correlation coefficient). It can be found that R^2 values are very near to 1, and the $q_{e,exp}$ values are also closer to $q_{e,cal}$ values for the PSO. In this model, it is speculated that adsorption pursues a second-order mechanism (Bao et al., 2018; El Messaoudi et al., 2021).

3.4 Adsorption isotherm

The TC adsorption on SiO_2 NPs was the Langmuir, Freundlich, and Temkin isotherm models. The linear forms of these isotherms are expressed on Eqs. (7), (8), and (9) as represented in **Table 3** (Xu et al., 2019). The parameters of linear fitting are listed in **Table 3**. Based on regression coefficients R^2 , the Langmuir isotherm describes the adsorption in the monolayer process (Ani et al., 2020). The Q_m of SiO_2 NPs for TC adsorption was 552.48 mg g^{-1} . **Table 4** show that SiO_2 NPs exhibit high adsorption of TC compared with adsorbents. This result indicates that the SiO_2 NPs is a suitable adsorbent for wastewater treatment.

3.5 Design optimization

Table 5 presents the results of ANOVA analysis of the statistical significance. The p-value (<0.0001) indicates the polynomial equation was significant for the removal of TC on SiO_2 NPs within 95 % (Hu et al., 2021). The high values of R^2 (0.9925), adjusted R^2 (0.9864), and

predicted R^2 (0.9449) indicated the excellent fit of this model to the factors selected. The value of adequate precision of 37.9356 (>4) shows a high level of statistical significance (Oyekanmi et al., 2019). The predicated TC removal using SiO_2 NPs was obtained by the developed model represented below in Eq. (10):

$$R (\%) = 98.57 - 6.84 A + 3.78 B + 0.8861 C + 3.72 AB + 0.6362 AC - 0.0713 BC - 3.57A^2 - 2.36 B^2 - 0.6527 C^2 \quad (10)$$

The residual vs. predicted and 3D response surface plots of TC percentage are illustrated in Fig.7 and Fig.8, respectively. The TC removal was experimentally 99.56 % under optimal conditions (SiO_2 NPs dose = 0.25 g L^{-1} , $C_0 = 25 \text{ mg L}^{-1}$, and $\text{pH} = 5$ at $23 \pm 1^\circ\text{C}$ for 40 min) RSM-BBD modeling.

3.6 Adsorption mechanism

The adsorption mechanism of TC on SiO_2 NPs is schematized in Fig.9 b based on PZC. As Fig.9a shows, PZC of SiO_2 NPs was 8.2. The dominance of charge positive of SiO_2 NPs at $\text{pH} < \text{PZC}$ and negatively charged when $\text{pH} > \text{PZC}$. The high value of PZC indicates the favorable and maximum adsorption in an acidic medium. This result confirmed the effect of pH on adsorption. The charge positive of SiO_2 NPs and the negative charge of TC indicates the governance of electrostatic interactions between TC and SiO_2 NPs.

3.7 Reusability of SiO_2 NPs

To assess the applicability of the adsorbent in the full-scale operation, the reusable capacity of SiO_2 NPs was studied for the removal of TC in optimal conditions (SiO_2 NPs dose = 0.25 g L^{-1} , $t = 40 \text{ min}$, $C_0 = 50 \text{ mg L}^{-1}$, $\text{pH (TC)} = 5$, and $T = 23 \pm 1^\circ\text{C}$). Therefore, the regeneration studies for evaluating the adsorption efficiency of the nanocomposite were conducted within five successive cycles using 0.1 M NaOH . According to Fig.10, less than a 13 % drop in the removal efficiency of TC occurred at the end of the fifth run, signifying the desirable reusability potential of the synthesized nanoparticles within successive runs of operation. In

conclusion, the present adsorbent can be regarded as a promising material for practical application in environmental protection purposes due to its excellent adsorption activities and high stability.

4 Conclusions

The SiO₂ nanoparticles biosynthesized from the extract *Nerium oleander* leaves are effective in removing tetracycline (TC) from an aqueous solution. The result of SEM-EDX, FTIR, TEM, and XRD characterization confirmed the biosynthesis of SiO₂ NPs successfully. Under conditions (SiO₂ NPs dose=0.25 g L⁻¹, *t*=40 min, *C*₀=50 mg L⁻¹, pH (TC)=5, and *T*=23±1°C), the TC removal was 98.62 %. The TC adsorption on SiO₂ NPs followed the PSO and Langmuir models. The *Q_m* was 552.48 mg g⁻¹. The recyclability study demonstrated that the SiO₂ NPs exhibited excellent reusability for TC removal. Optimization is an effective approach for modeling the sorption process of the TC on SiO₂ NPs using BBD–RSM. These results confirm that the SiO₂ NPs nanoparticles are suitable for removing antibiotics from wastewaters.

References

- Aalipour, F., Mirlohi, M., Jalali, M., 2014. Determination of antibiotic consumption index for animal originated foods produced in animal husbandry in Iran, 2010. *J. Environ. Heal. Sci. Eng.* 2014 121 12, 1–7. <https://doi.org/10.1186/2052-336X-12-42>
- Ahamad, T., Ruksana, Chaudhary, A.A., Naushad, M., Alshehri, S.M., 2019. Fabrication of MnFe₂O₄ nanoparticles embedded chitosan-diphenylureaformaldehyde resin for the removal of tetracycline from aqueous solution. *Int. J. Biol. Macromol.* 134, 180–188. <https://doi.org/10.1016/J.IJBIOMAC.2019.04.204>
- Ani, J.U., Akpomie, K.G., Okoro, U.C., Aneke, L.E., Onukwuli, O.D., Ujam, O.T., 2020. Potentials of activated carbon produced from biomass materials for sequestration of dyes, heavy metals, and crude oil components from aqueous environment. *Appl. Water Sci.* 2020 102 10, 1–11. <https://doi.org/10.1007/S13201-020-1149-8>
- Bao, J., Zhu, Y., Yuan, S., Wang, F., Tang, H., Bao, Z., Zhou, H., Chen, Y., 2018. Adsorption of Tetracycline with Reduced Graphene Oxide Decorated with MnFe₂O₄ Nanoparticles. *Nanoscale Res. Lett.* 2018 131 13, 1–8. <https://doi.org/10.1186/S11671-018-2814-9>
- Bentahar, S., Dbik, A., Khomri, M.E., El Messaoudi, N., Lacherai, A., 2018. Removal of a cationic dye from aqueous solution by natural clay. *Groundw. Sustain. Dev.* 6, 255–262. <https://doi.org/10.1016/j.gsd.2018.02.002>
- Chen, K.-H., Pu, Y.-C., Chang, K.-D., Liang, Y.-F., Liu, C.-M., Yeh, J.-W., Shih, H.-C., Hsu, Y.-J., 2012. Ag-Nanoparticle-Decorated SiO₂ Nanospheres Exhibiting Remarkable Plasmon-Mediated Photocatalytic Properties. *J. Phys. Chem. C* 116, 19039–19045. <https://doi.org/10.1021/JP306555J>
- Daghrir, R., Drogui, P., 2013. Tetracycline antibiotics in the environment: a review. *Environ. Chem. Lett.* 2013 113 11, 209–227. <https://doi.org/10.1007/S10311-013-0404-8>

293 Das, R., Vecitis, C.D., Schulze, A., Cao, B., Ismail, A.F., Lu, X., Chen, J., Ramakrishna, S.,
 294 2017. Recent advances in nanomaterials for water protection and monitoring. *Chem. Soc.*
 295 *Rev.* 46, 6946–7020. <https://doi.org/10.1039/C6CS00921B>

296 Das, S., Chakraborty, J., Chatterjee, S., Kumar, H., 2018. Prospects of biosynthesized
 297 nanomaterials for the remediation of organic and inorganic environmental contaminants.
 298 *Environ. Sci. Nano* 5, 2784–2808. <https://doi.org/10.1039/C8EN00799C>

299 Debnath, B., Majumdar, M., Bhowmik, M., Bhowmik, K.L., Debnath, A., Roy, D.N., 2020.
 300 The effective adsorption of tetracycline onto zirconia nanoparticles synthesized by novel
 301 microbial green technology. *J. Environ. Manage.* 261, 110235.
 302 <https://doi.org/10.1016/j.jenvman.2020.110235>

303 Dubey, R.S., Rajesh, Y.B.R.D., More, M.A., 2015. Synthesis and Characterization of SiO₂
 304 Nanoparticles via Sol-gel Method for Industrial Applications. *Mater. Today Proc.* 2,
 305 3575–3579. <https://doi.org/10.1016/J.MATPR.2015.07.098>

306 El Khomri, M., El Messaoudi, N., Dbik, A., Bentahar, S., Lacherai, A., 2020. Efficient
 307 adsorbent derived from *Argania Spinosa* for the adsorption of cationic dye: Kinetics,
 308 mechanism, isotherm and thermodynamic study. *Surfaces and Interfaces* 20, 100601.
 309 <https://doi.org/10.1016/j.surfin.2020.100601>

310 El Messaoudi, N., Dbik, A., El Khomri, M., Sabour, A., Bentahar, S., Lacherai, A., 2017.
 311 Date stones of *Phoenix dactylifera* and jujube shells of *Ziziphus lotus* as potential
 312 biosorbents for anionic dye removal. *Int. J. Phytoremediation* 19, 1047–1052.
 313 <https://doi.org/10.1080/15226514.2017.1319331>

314 El Messaoudi, N., El Khomri, M., Bentahar, S., Dbik, A., Lacherai, A., Bakiz, B., 2016a.
 315 Evaluation of performance of chemically treated date stones: Application for the removal
 316 of cationic dyes from aqueous solutions. *J. Taiwan Inst. Chem. Eng.* 67, 244–253.
 317 <https://doi.org/10.1016/j.jtice.2016.07.024>

318 El Messaoudi, N., El Khomri, M., Dabagh, A., Chegini, Z.G., Dbik, A., Bentahar, S.,

319 Lacherai, A., Iqbal, M., Jada, A., Sher, F., Lima, É.C., 2021. Synthesis of a novel
 320 nanocomposite based on date stones/CuFe₂O₄ nanoparticles for eliminating cationic
 321 and anionic dyes from aqueous solution. *Int. J. Environ. Stud.* 1–19.
 322 <https://doi.org/10.1080/00207233.2021.1929469>
 323 El Messaoudi, N., El Khomri, M., Dbik, A., Bentahar, S., Lacherai, A., Bakiz, B., 2016b.
 324 Biosorption of Congo red in a fixed-bed column from aqueous solution using jujube
 325 shell: Experimental and mathematical modeling. *J. Environ. Chem. Eng.* 4, 3848–3855.
 326 <https://doi.org/10.1016/j.jece.2016.08.027>
 327 Epps, A. Van, Blaney, L., 2016. Antibiotic Residues in Animal Waste: Occurrence and
 328 Degradation in Conventional Agricultural Waste Management Practices. *Curr. Pollut.*
 329 *Reports* 2016 23 2, 135–155. <https://doi.org/10.1007/S40726-016-0037-1>
 330 Fiol, N., Villaescusa, I., 2009. Determination of sorbent point zero charge: Usefulness in
 331 sorption studies. *Environ. Chem. Lett.* 7, 79–84. [https://doi.org/10.1007/s10311-008-](https://doi.org/10.1007/s10311-008-0139-0)
 332 [0139-0](https://doi.org/10.1007/s10311-008-0139-0)
 333 Grenni, P., Ancona, V., Barra Caracciolo, A., 2018. Ecological effects of antibiotics on
 334 natural ecosystems: A review. *Microchem. J.* 136, 25–39.
 335 <https://doi.org/10.1016/J.MICROC.2017.02.006>
 336 Hosseini, S.A., Vossoughi, M., Mahmoodi, N.M., Sadrzadeh, M., 2018. Efficient dye removal
 337 from aqueous solution by high-performance electrospun nanofibrous membranes through
 338 incorporation of SiO₂ nanoparticles. *J. Clean. Prod.* 183, 1197–1206.
 339 <https://doi.org/10.1016/j.jclepro.2018.02.168>
 340 Hu, Y. ying, Pan, C., Zheng, X., Hu, F., Xu, L., Xu, G., Jian, Y., Peng, X., 2021. Prediction
 341 and optimization of adsorption properties for Cs⁺ on NiSiO₄@NiAlFe LDHs hollow
 342 spheres from aqueous solution: Kinetics, isotherms, and BBD model. *J. Hazard. Mater.*
 343 401, 123374. <https://doi.org/10.1016/J.JHAZMAT.2020.123374>
 344 Ibrahim, R.K., Hayyan, M., AlSaadi, M.A., Hayyan, A., Ibrahim, S., 2016. Environmental

application of nanotechnology: air, soil, and water. *Environ. Sci. Pollut. Res.* 2016 2314
 23, 13754–13788. <https://doi.org/10.1007/S11356-016-6457-Z>

Jawad, A.H., Malek, N.N.A., Abdulhameed, A.S., Razuan, R., 2020. Synthesis of Magnetic
 Chitosan-Fly Ash/Fe₃O₄ Composite for Adsorption of Reactive Orange 16 Dye:
 Optimization by Box–Behnken Design. *J. Polym. Environ.* 28, 1068–1082.
<https://doi.org/10.1007/s10924-020-01669-z>

Jin, J., Yang, Z., Xiong, W., Zhou, Y., Xu, R., Zhang, Y., Cao, J., Li, X., Zhou, C., 2019. Cu
 and Co nanoparticles co-doped MIL-101 as a novel adsorbent for efficient removal of
 tetracycline from aqueous solutions. *Sci. Total Environ.* 650, 408–418.
<https://doi.org/10.1016/J.SCITOTENV.2018.08.434>

Li, S., Huang, W., Yang, P., Li, Z., Xia, B., Li, M., Xue, C., Liu, D., 2021. One-pot synthesis
 of N-doped carbon intercalated molybdenum disulfide nanohybrid for enhanced
 adsorption of tetracycline from aqueous solutions. *Sci. Total Environ.* 754, 141925.
<https://doi.org/10.1016/J.SCITOTENV.2020.141925>

Liu, F., Zhang, W., Chen, W., Wang, Jing, Yang, Q., Zhu, W., Wang, Jianlong, 2017. One-pot
 synthesis of NiFe₂O₄ integrated with EDTA-derived carbon dots for enhanced removal
 of tetracycline. *Chem. Eng. J.* 310, 187–196. <https://doi.org/10.1016/J.CEJ.2016.10.116>

Martín, A., Caldelas, C., Weiss, D., Aranjuelo, I., Navarro, E., 2018. Assessment of Metal
 Immission in Urban Environments Using Elemental Concentrations and Zinc Isotope
 Signatures in Leaves of Nerium oleander. *Environ. Sci. Technol.* 52, 2071–2080.
<https://doi.org/10.1021/ACS.EST.7B00617>

Niksefat, N., Jahanshahi, M., Rahimpour, A., 2014. The effect of SiO₂ nanoparticles on
 morphology and performance of thin film composite membranes for forward osmosis
 application. *Desalination* 343, 140–146. <https://doi.org/10.1016/J.DESAL.2014.03.031>

Oyekanmi, A.A., Ahmad, A., Hossain, K., Rafatullah, M., 2019. Statistical optimization for
 adsorption of Rhodamine B dye from aqueous solutions. *J. Mol. Liq.* 281, 48–58.

<https://doi.org/10.1016/J.MOLLIQ.2019.02.057>
 Parolo, M.E., Savini, M.C., Vallés, J.M., Baschini, M.T., Avena, M.J., 2008. Tetracycline
 adsorption on montmorillonite: pH and ionic strength effects. *Appl. Clay Sci.* 40, 179–
 186. <https://doi.org/10.1016/J.CLAY.2007.08.003>
 Rafigh, S.M., Heydarinasab, A., 2017. Mesoporous Chitosan–SiO₂ Nanoparticles: Synthesis,
 Characterization, and CO₂ Adsorption Capacity. *ACS Sustain. Chem. Eng.* 5, 10379–
 10386. <https://doi.org/10.1021/ACSSUSCHEMENG.7B02388>
 Rashidi Nodeh, H., Sereshti, H., Beirakabadi, E., Razmkhah, K., 2020. Synthesis and
 application of lanthanum sulfide nanoparticles for removal of tetracycline from aqueous
 media. *Int. J. Environ. Sci. Technol.* 17, 819–828. <https://doi.org/10.1007/s13762-019-02399-z>
 Ravikumar, K.V.G., Sudakaran, S.V., Ravichandran, K., Pulimi, M., Natarajan, C.,
 Mukherjee, A., 2019. Green synthesis of NiFe nano particles using Punica granatum peel
 extract for tetracycline removal. *J. Clean. Prod.* 210, 767–776.
<https://doi.org/10.1016/j.jclepro.2018.11.108>
 Rostam, A.B., Taghizadeh, M., 2020. Advanced oxidation processes integrated by membrane
 reactors and bioreactors for various wastewater treatments: A critical review. *J. Environ.*
Chem. Eng. 8, 104566. <https://doi.org/10.1016/J.JECE.2020.104566>
 Scaria, J., Anupama, K. V., Nidheesh, P. V., 2021. Tetracyclines in the environment: An
 overview on the occurrence, fate, toxicity, detection, removal methods, and sludge
 management. *Sci. Total Environ.* 771, 145291.
<https://doi.org/10.1016/J.SCITOTENV.2021.145291>
 Sebeia, N., Jabli, M., Ghith, A., 2019. Biological synthesis of copper nanoparticles, using
 Nerium oleander leaves extract: Characterization and study of their interaction with
 organic dyes. *Inorg. Chem. Commun.* 105, 36–46.
<https://doi.org/10.1016/J.INOCHE.2019.04.023>

397 Sharma, G., Bhogal, S., Kumar, A., Naushad, M., Sharma, S., Ahamad, T., Stadler, F.J., 2020.
398 AgO/MgO/FeO@Si₃N₄ nanocomposite with robust adsorption capacity for tetracycline
399 antibiotic removal from aqueous system. *Adv. Powder Technol.* 31, 4310–4318.
400 <https://doi.org/10.1016/J.APT.2020.09.006>

401 Sharma, P., Kherb, J., Prakash, J., Kaushal, R., 2021. A novel and facile green synthesis of
402 SiO₂ nanoparticles for removal of toxic water pollutants. *Appl. Nanosci.* 2021 1–13.
403 <https://doi.org/10.1007/S13204-021-01898-1>

404 Sodhi, K.K., Kumar, M., Balan, B., Dhaulaniya, A.S., Shree, P., Sharma, N., Singh, D.K.,
405 2021. Perspectives on the antibiotic contamination, resistance, metabolomics, and
406 systemic remediation. *SN Appl. Sci.* 2021 32 3, 1–25. [https://doi.org/10.1007/S42452-](https://doi.org/10.1007/S42452-020-04003-3)
407 [020-04003-3](https://doi.org/10.1007/S42452-020-04003-3)

408 Song, Y.X., Chen, S., You, N., Fan, H.T., Sun, L.N., 2020. Nanocomposites of zero-valent
409 Iron@Activated carbon derived from corn stalk for adsorptive removal of tetracycline
410 antibiotics. *Chemosphere* 255, 126917.
411 <https://doi.org/10.1016/J.CHEMOSPHERE.2020.126917>

412 Suba, V., Rathika, G., Kumar, E.R., Saravanabhavan, M., 2018. Influence of Magnetic
413 Nanoparticles on Surface Changes in CoFe₂O₄/Nerium Oleander Leaf Waste
414 Activated Carbon Nanocomposite for Water Treatment. *J. Inorg. Organomet. Polym.*
415 *Mater.* 2018 285 28, 1706–1717. <https://doi.org/10.1007/S10904-018-0831-X>

416 Van, T.T.H., Yidana, Z., Smooker, P.M., Coloe, P.J., 2020. Antibiotic use in food animals
417 worldwide, with a focus on Africa: Pluses and minuses. *J. Glob. Antimicrob. Resist.* 20,
418 170–177. <https://doi.org/10.1016/J.JGAR.2019.07.031>

419 Wang, X., Li, F., Hu, X., Hua, T., 2021. Electrochemical advanced oxidation processes
420 coupled with membrane filtration for degrading antibiotic residues: A review on its
421 potential applications, advances, and challenges. *Sci. Total Environ.* 784, 146912.
422 <https://doi.org/10.1016/J.SCITOTENV.2021.146912>

- Xu, G., Zhu, Y., Wang, X., Wang, S., Cheng, T., Ping, R., Cao, J., Lv, K., 2019. Novel chitosan and Laponite based nanocomposite for fast removal of Cd(II), methylene blue and Congo red from aqueous solution. *e-Polymers* 19, 244–256. <https://doi.org/10.1515/EPOLY-2019-0025>
- Yu, F., Li, Y., Han, S., Ma, J., 2016. Adsorptive removal of antibiotics from aqueous solution using carbon materials. *Chemosphere* 153, 365–385. <https://doi.org/10.1016/J.CHEMOSPHERE.2016.03.083>
- Yue, Y., Peng, Z., Wang, W., Cai, Y., Tan, F., Wang, X., Qiao, X., 2019. Facile preparation of MgO-loaded SiO₂ nanocomposites for tetracycline removal from aqueous solution. *Powder Technol.* 347, 1–9. <https://doi.org/10.1016/J.POWTEC.2019.02.034>
- Zhou, J., Ma, F., Guo, H., 2020. Adsorption behavior of tetracycline from aqueous solution on ferroferric oxide nanoparticles assisted powdered activated carbon. *Chem. Eng. J.* 384, 123290. <https://doi.org/10.1016/J.CEJ.2019.123290>

List of Figures

Fig.1. SEM image (a), elemental analysis (b) and mapping images of SiO₂ NPs: oxygen (c) and silicon (d).

Fig.2. N₂ adsoption/desorption isotherms included pore size distributions curves of TC-SiO₂ NPs.

Fig.3. FTIR spectra of SiO₂ NPs and TC-SiO₂ NPs.

Fig.4. TEM image (a) and XRD pattern (b) of SiO₂ NPs.

Fig.5. Effects of pH (a), SiO₂ NPs dose (b), reaction time (c), and TC concentration (d) on TC adsorption using SiO₂ NPs.

Fig.6. The effect of ionic strength on TC adsorption using SiO₂ NPs.

490

491

Fig.7. Actual versus predicted for TC adsorption on SiO₂ NPs.

Fig.8. Surface response plots of TC removal percentage: initial TC concentration with contact time (a), SiO_2 NPs dose with initial TC concentration (b), SiO_2 NPs dose, and with contact time (c).

Fig.9. PZC of SiO₂ NPs (a) and proposed adsorption mechanism of TC on SiO₂ NPs (b).

Fig.10. Reusability of SiO₂ NPs for the removal of TC.

524

List of Tables

525 **Table 1.** Design of experiment runs and correspondents responses for TC removal efficiency

526

by SiO₂ NPs.

Variables		Codes		
		-1	0	1
A=TC concentration (mg L ⁻¹)		25	50	75
B=Contact time (min)		30	40	50
C=SiO ₂ NPs dose (g L ⁻¹)		0.1	0.25	0.4
Run	A	B	C	R
	(mg L ⁻¹)	(min)	(g L ⁻¹)	(%)
1	25	30	0.1	98.05
2	75	30	0.1	77.11
3	25	50	0.1	98.87
4	75	50	0.1	90.11
5	25	30	0.4	99.23
6	75	30	0.4	78.13
7	25	50	0.4	99.06
8	75	50	0.4	93.55
9	25	40	0.25	99.56
10	75	40	0.25	90.57
11	50	30	0.25	89.45
12	50	50	0.25	98.66
13	50	40	0.1	90.11
14	50	40	0.4	98.65
15	50	40	0.25	98.44
16	50	40	0.25	98.71
17	50	40	0.25	98.24
18	50	40	0.25	98.53
19	50	40	0.25	98.61
20	50	40	0.25	98.72
21	50	40	0.25	98.23

527

528

Table 2. TC adsorption kinetic parameters using SiO₂ NPs.

Model and its equation		Parameter	Value
PFO	$Log(q_e - q_t) = Log(q_e) - \frac{K_{PFO}}{2.303} t$ (4)	$q_{e,exp}$	197.98
		$q_{e,cal}$	51.03
		K_{PFO}	0.0052
		R^2	0.8285
PSO	$\frac{t}{q_t} = \frac{1}{K_{PSO} q_e^2} + \frac{1}{q_e} t$ (5)	$q_{e,cal}$	204.08
		K_{PSO}	0.0019
		R^2	0.9996
		K_{IPD1}	16.0461
IPD	1 st linear portion	C_1	35.28
		R^2	0.9811
		K_{IPD2}	10.1487
	2 nd linear portion	C_2	49.76
		R^2	0.9045
	3 rd linear portion	K_{IPD3}	3.1460
		C_3	62.75
		R^2	0.9733

529

530

531

532

Table 3. TC adsorption isotherm parameters using SiO₂ NPs.

Model and its equation	Parameter	Value
Langmuir	Q_m	552.48
$\frac{C_e}{q_e} = \frac{1}{Q_m K_L} + \frac{C_e}{Q_m}$ (7)	K_L	0.3175
	R^2	0.9931
	Freundlich	K_F
$Lnq_e = LnK_F + \frac{LnC_e}{n}$ (8)	n	3.5997
	R^2	0.9650
	Temkin	K_T
$q_e = B LnK_T + B LnC_e$ (9)	B	75.6710
	R^2	0.9392

533

534

Table 4. Comparison of TC adsorption onto some adsorbents

Adsorbent	Ad	T	<i>t</i>	<i>C</i> ₀	pH	<i>Q</i> _m	Reference
	(mg L ⁻¹)	(°C)	(min)	(mg L ⁻¹)		(mg g ⁻¹)	
ZrO ₂ NPs	0.2	–	15	25–150	6	526.32	(Debnath et al., 2020)
AgO/MgO/FeO@Si ₃ N ₄	–	30	90	30–100	8	172.41	(Sharma et al., 2020)
ACCS	2.5	–	20	100–700	5	38.30	(Song et al., 2020)
ZVI@ACCS	2.5	–	20	100–700	5	78.30	(Song et al., 2020)
NiFe ₂ O ₄ @CDs	10	50	1440	25–100	8	591.72	(Liu et al., 2017)
Pristine MoS ₂	0.4	35	2400	50–500	6	409.84	(Li et al., 2021)
NiFe NPs	0.3	–	90	20–80	7	61.00	(Ravikumar et al., 2019)
La ₂ S ₃ NPs	1	25	90	10–300	5	56.81	(Rashidi Nodeh et al., 2020)
SiO ₂ NPs	0.25	23	40	25–200	5	552.48	Current study

537 **Notation** : Ad=Adsorbent dose, T=Temperature, t=Time, *C*₀= TC concentration

539

Table 5. ANOVA data for design for TC removal using SiO₂ NPs.

Source	Sun	df	Mean Square	F-value	p-value
	Squares				
Model	1221.20	9	135.69	162.55	< 0.0001
A-TC concentration	639.35	1	639.35	765.93	< 0.0001
B -Contact time	195.12	1	195.12	233.75	< 0.0001
C- SiO ₂ NPs dose	10.72	1	10.72	12.85	0.0043
AB	110.78	1	110.78	132.71	< 0.0001
AC	3.24	1	3.24	3.88	0.0746
BC	0.0406	1	0.0406	0.0487	0.8295
A ²	191.81	1	191.81	229.78	< 0.0001
B ²	83.37	1	83.37	99.88	< 0.0001
C ²	6.39	1	6.39	7.66	0.0183
Residual	9.18	11	0.8347		
Lack of Fit	8.85	5	1.77	31.76	0.0003
Pure Error	0.3343	6	0.0557		
Core total	1230.38	20			
Model statistics	R ²	Adjusted R ²	Predicted R ²	Adequate precision	
	0.9925	0.9864	0.9449	37.9356	

540

541

542

543

544