Yield stress of aerated cement paste

Blandine Feneuil^{a,b,*}, Nicolas Roussel^a, Olivier Pitois^a

^a *Laboratoire Navier, UMR 8205, École des Ponts ParisTech, IFSTTAR, CNRS, UPE,
Champs-sur-Marne, France*

^b *Current position : Department of Mathematics, University of Oslo, Oslo, Norway*

Abstract

Yield stress of aerated cement paste is studied. Samples are prepared by mixing aqueous foam with cement paste, which allows controlling bubble size, gas volume fraction and yield stress of the cement paste. Two distinct behaviors are observed depending on the surfactant used to prepare the precursor aqueous foam: (i) For a surfactant with low adsorption ability with respect to cement grains, bubbles tend to decrease the yield stress of the paste with magnitude governed by the Bingham capillary number, which accounts for bubble deformability. (ii) For a surfactant with high adsorption ability, bubbles increase significantly the yield stress. This behavior is shown to result from the surfactant-induced hydrophobization of the cement grains, which adsorb at the surface of the bubbles and tend to rigidify them. Within this regime, the effect of air incorporation is comparable to the effect of added solid particles.

Keywords:

rheology (A), cement paste (D), bubbles

*Corresponding author

Email address: bfeneui@math.uio.no (Blandine Feneuil)

21 1. Introduction

22 Yield stress of a cement paste, mortar or concrete is a crucial property.
23 For instance, sufficient yield stress can stop bleeding [1]. When material is
24 poured in a formwork, yield stress can have negative effects if it prevents proper
25 filling of the mold [1] but it helps to reduce the lateral formwork pressure [2].
26 In the case of mortar sprayed on a vertical support, yield stress dictates the
27 maximum thickness of the layer [3]. Among cementitious materials, aerated
28 materials raise growing interest. Entrainment of air bubbles into concrete, up
29 to 10% by volume, is known to improve its durability in environments exposed
30 to freeze-thaw cycles [4]. At higher air content, aerated construction materials
31 are promising for various industrial applications thanks to their low densities,
32 low raw material needs, and improved thermal and acoustic properties.

33 The goal of this paper is to understand the effect of air bubbles on the yield
34 stress of cement pastes containing air below 40% by volume. These materials
35 will be referred to as "aerated cement paste" or "bubbles suspensions in cement
36 paste" as the word "foams" usually refers to materials with higher air volume
37 content, above 64% [5], where bubbles are densely packed and deformed by their
38 neighbors. In foams, bubble interactions induce specific rheological properties
39 [5], that are not discussed in this paper.

40 Various observations have been reported in the literature concerning the rhe-
41 ological properties of aerated cement pastes or mortars. *Aïtcin* [4] notes that
42 entrained bubbles improve workability of concrete whereas *Rixom and Mailva-*
43 *ganam* [6] reports a large increase of viscosity with the amount of entrained
44 air. These opposite results may arise from the different experimental protocols
45 and the different paste formulations. Actually, quantifying the effect of air in-
46 clusions on cement paste rheology, independently from the paste formulation,
47 requires to determine normalized rheological quantities, e.g. yield stress τ_y of

the aerated paste divided by the yield stress τ_{ref} of the suspending paste. Micromechanical analysis shows that the normalized yield stress is a function of air volume content Φ and of the deformation of the bubbles when the fluid is yielding [7, 8]. Deformability of the bubbles is characterized by the Bingham capillary number Ca_y , which compares the suspending fluid yield stress τ_{ref} and the bubble capillary pressure $2\gamma/R$:

$$Ca_y = \frac{\tau_{ref}}{2\gamma/R} \quad (1)$$

where γ is the air-liquid surface tension and R is the bubble radius. Such a behavior has been confirmed experimentally when $Ca_y \rightarrow \infty$ and $Ca_y \rightarrow 0$ [9, 10] for model yield stress fluids, i.e. aerated concentrated emulsions.

The case of aerated cement paste is much more complex due to the potentially strong effect of added surfactants on the suspending fluid yield stress τ_{ref} [11]. In order to tackle this issue we prepare aerated cement paste by incorporating aqueous foam into cement paste within conditions where both water and surfactant amounts are controlled. In the first part of the study, the effects of both water and surfactants on the suspending fluid yield stress are quantified. The dimensionless yield stress τ_y/τ_{ref} of the prepared aerated cement pastes is then assessed as a function of bubble size and air volume content for two different surfactants.

2. Materials and methods

2.1. Materials

We use a CEM I cement from Lafarge, Saint Vigor factory. Specific surface area is $0.359 \text{ m}^2/\text{g}$ and chemical composition is given in Table 1.

Two surfactants will be used: TTAB (tetradecyltrimethylammonium bromide) is a cationic surfactant provided by Sigma-Aldrich, its molar mass is 336

C ₃ S	C ₂ S	C ₃ A	C ₄ AF	CaO/SiO ₂	MgO	Na ₂ O +0.658 K ₂ O	SO ₃	Gypsum
62%	16%	2.1%	15%	3	1.1%	0.34 %	2.6%	2.4%

Table 1: Chemical composition of CEM I cement from Lafarge, Saint Vigor

g/mol. Bio-Terge[®] is an anionic surfactant provided by Stepan, its molar mass is 315 g/mol.

Interaction of both surfactants with the same cement as used in this paper have been previously studied [11]. Adsorption isotherm of surfactants on cement grains have been measured and surfactant Critical Micelle Concentration (CMC) have been measured in DI water and in cement synthetic cement pore solution. For TTAB, CMC is 1.5 g/L in water and 0.5 g/L in cement pore solution. Regarding Bio-Terge, its CMC is 2 g/L in water and 0.5 g/L in cement pore solution. The main results of this paper will be recalled in the discussion.

2.2. Method

2.2.1. Preparation of aerated and reference cement pastes

As the yield stress of cementitious materials depends on their shear history, the same time schedule has been followed for all samples. First, distilled water and cement at water-to-cement mass ratio W/C_i are mechanically mixed for 3 min. Then, the paste is left at rest for 20 minutes to allow for the formation of sulfo-aluminates [12]. After 20 minutes, foam is added to the cement paste and carefully incorporated with a spoon. Hand mixing allows us to check visually that the bubbles size is kept constant during incorporation of the foam. Mixing duration is 4 minutes, and it is carried out always by the same operator in order to be similar in all experiments. 30 minutes after initial cement paste mixing, the rheometer cup is filled and rheometry starts.

Unfoamed samples, the so-called "reference cement pastes", were prepared for comparison purpose with foamed samples. In these cases, the above-described

95 procedure was followed except that pure surfactant solution was added (28 min
96 after initial cement paste mixing) instead of foam.

97 The weight of water contained into the foam added to the cement paste is
98 measured in order to calculate the new effective water-to-cement ratio, W/C_f ,
99 which characterizes the suspending cement paste in the aerated sample. Final
100 air content Φ is assessed by weighting the aerated paste in the rheometer cup.
101 Indeed, the density ρ of the sample is related to the air content by $\rho(\Phi) =$
102 $\rho_0(1 - \Phi)$, where $\rho_0 = (W/C_f + 1)/(W/C_f/\rho_w + 1/\rho_c)$ is the density of the
103 suspending cement paste, with ρ_w (resp. ρ_c) the density of water (resp. of
104 cement). The maximal relative error on the measured air fraction is 4%.

105 Note that in the chosen procedure, foam or surfactant solution is added
106 more than 20 minutes after first mixing of cement and water, so surfactant is
107 not expected to interfere in the formation of first hydration products [12].

108 2.2.2. Foam production

109 Aqueous foam is generated according to the method described in [13]. In
110 brief, bubbles are created with a small T junction with two inputs: surfactant
111 solution and nitrogen. Within such conditions, foams are made of bubbles
112 having the same diameter, which is set by the flow rates of both nitrogen and
113 surfactant solution. The foam is collected (bubble by bubble) in a column and
114 it is wetted from the top to prevent it from drying and breaking. Once foam is
115 ready to use, it is pushed from the column at constant flow rate.

116 2.2.3. Samples

117 We study seven sets of samples. For each set, both initial water-to-cement
118 ratio (i.e. before addition of foam) and foam characteristics (surfactant and
119 bubble size) are kept constant.

120 Sets of reference samples are prepared to match with each set of bubble

	Surfactant	Surfactant concentration	Bubble diameter	W/C_i	Reference set
Set T1	TTAB	4.5 g/L	475 +/- 10 μm	0.382	R_T1
Set T2	TTAB	4.5 g/L	270 μm	0.335	R_T2
Set T3	TTAB	4.5 g/L	475 +/- 10 μm	0.325	R_T3
Set T4	TTAB	4.5 g/L	475 +/- 10 μm	0.305	R_T4
Set T5	TTAB	4.5 g/L	780 +/- 20 μm	0.335	R_T2
Set B1	Bio-Terge	30 g/L	440 +/- 5 μm	0.329	R_B1
Set B2	Bio-Terge	8 g/L	590 +/- 10 μm	0.335	R_B2
-	-	-	-	0.305 to 0.405	R_0

Table 2: Characteristics of each set of aerated cement paste samples. The corresponding reference paste for each set contains the same surfactant at the same concentration, and the same initial water-to-cement ratio. Note that sets T2 and T5 share the same reference R_T2.

suspensions, i.e. they are prepared with the same surfactant solution and from the same initial cement paste, but they contain no bubble. In addition, reference set R_0 refers to yield stress measurement on surfactant-free paste.

2.2.4. Yield stress measurement

Yield stress measurements are carried out with a vane-in-cup geometry in Ultra+ Kinexus Rheometer from Malvern. The six-blade vane tool is 5 cm high and 25 mm wide. We use a striated cup to avoid wall slip: diameter is 37 mm and height 62.5 mm. The cup is filled with aerated or reference cement paste with a spoon, then the Vane tool is slowly inserted into the paste. Pre-shear is prevented before measurement in order to avoid material flow and buoyancy-induced bubble migration [2, 14, 15].

Yield stress is measured with a start of flow sequence at a constant shear rate $\dot{\epsilon} = 0.01 \text{ s}^{-1}$ for 10 minutes [16]. For all samples, stress increases up to the yield stress and then decreases. The yield stress is reached for shear strain values between 40 and 45%. This value is low enough to enable correct measurement of yield stress with a Vane tool [17].

Figure 1: Start of flow curves for yield stress measurement of an aerated cement paste (grey) and the corresponding reference paste (black). Examples correspond to set T3 with air content 31% and the corresponding reference sample from set R.T3.

3. Results

3.1. Reference yield stress

Yield stresses for reference samples are plotted in Fig. 2. As expected, when no surfactant is added, the yield stress decreases when the final water-to-cement ratio increases. For each reference data set containing TTAB surfactant, the yield stress decreases when the amount of added TTAB solution increases. The same trend is observed with Bio-Terge solution at the smallest concentration (R_B2), even if the decrease is lower than for TTAB. On the contrary, when 30 g/L Bio-Terge surfactant solution is used (R_B1), the yield stress increases with the amount of added solution.

Figure 2: Yield stress of reference cement pastes. Yield stresses for pastes with no surfactant (R_0) or TTAB surfactant (R_T1 to R_T4) are fitted with equation 3 with $\Phi_{perc} = 0.32$, $\Phi_{max} = 0.545$ and $m_1 = 65 \text{ Pa}$. In the case of Bio-Terge surfactant, linear regressions for each set of data are plotted with dotted lines.

3.2. Aerated cement paste

Yield stresses measured for each data set at different air contents are given in Figs. 3 and 4. Evolution of yield stress with increasing air content is not the same for all data sets: it is constant in set T1, it decreases in sets T2 to T5 and increases for B1 and B2.

4. Discussion

4.1. Reference yield stress with surfactant

Ionic surfactants, mainly anionic, can strongly modify yield stress when they are added to a cement paste [11]. At low concentration, adsorbed surfactant monolayer turns cement grains to hydrophobic grains which induces attractive interactions. At macroscopic scale, this results in the increase of the yield stress.

Figure 3: Yield stresses of aerated cement pastes made with TTAB surfactant. Bubble diameter is $475\ \mu\text{m}$ for T1, T3 and T4, $270\ \mu\text{m}$ for T2 and $780\ \mu\text{m}$ for T5. Initial water-to-cement ratio is 0.382 for T1, 0.335 for T2 and T5, 0.325 for T3 and 0.305 for T4.

At high surfactant concentration, surfactant agglomeration on the surface of the cement grains leads to steric repulsion between them and a drop of the paste yield stress.

As surfactant concentration has a significant effect on the yield stress, let us calculate the final concentrations $C_{TA,f}$ after mixing foam and cement paste. They depend on the concentration in the foaming solution $C_{TA,i}$, on the initial

Figure 4: Yield stresses of aerated cement pastes made with Bio-Terge surfactant. For B1, bubble diameter is $440 \mu\text{m}$, initial water-to-cement ratio is 0.329, and surfactant concentration in foam is 30 g/L. For B2, bubble diameter is $590 \mu\text{m}$, initial water-to-cement ratio, 0.335, and surfactant concentration in foam, 8 g/L.

Figure 5: Effect of surfactant concentration on the yield stress of cement pastes at $W/C_f = 0.5$ prepared following the protocol described in [11]. Repetition of a reference test in [11] showed that the error is about 5% of the yield stress value. Dotted line shows yield stress of the paste with no surfactant (12 Pa). Grey areas show the surfactant concentrations used in the present study.

164 water-to-cement ratio of the precursor cement paste W/C_i and the final water-
 165 to-cement ratio W/C_f :

$$C_{TA,f} = C_{TA,i} \frac{W/C_f - W/C_i}{W/C_f} \quad (2)$$

166 Calculated values range from 0.03 to 0.2 g/L for samples containing TTAB
 167 and between 0.08 and 0.8 g/L for Bio-Terge. In Fig. 5, yield stress is given as a
 168 function of surfactant concentration for cement pastes at $W/C_f = 0.5$ prepared

as in [11], with the same cement as this work, and containing TTAB or Bio-Terge. The figure shows that for both surfactants, the estimated concentrations are well below the concentrations at which maximum yield stresses are expected. Surfactants are therefore in the low concentration regime, where yield stress can be enhanced by hydrophobic interactions, but due to the very low concentrations used, we can expect this effect to be insignificant. Further analysis is made below for each surfactant.

4.1.1. Reference yield stress with TTAB

In Fig. 2, all yield stresses of cement pastes containing no surfactant or TTAB follow the same curve. First of all, this shows that TTAB, at the low concentrations we use here, has no effect on yield stress. In addition, yield stress depends only on the total water content in the cement paste, including both initial mixing water and foaming solution added later.

We choose to fit TTAB reference curve with equation 3 [18]:

$$\tau_{ref} = m_1 \frac{\Phi_p^2(\Phi_p - \Phi_{perc})}{\Phi_{max}(\Phi_{max} - \Phi_p)} \quad (3)$$

In this equation, m_1 accounts for the intensity of the interactions between cement grains, whose major components are Van der Waals, electrostatic and steric forces [18]. Φ_p is the solid volume fraction and is related to the water-to-cement ratio and to the densities of water ρ_w and cement ρ_c :

$$\Phi_p = 1/(1 + \rho_c/\rho_w W/C_f) \quad (4)$$

Φ_{perc} and Φ_{max} are respectively is the percolation threshold and the maximal solid fraction of the cement grains.

This curve is shown in Fig. 2 with parameters $\Phi_{perc} = 0.32$, $\Phi_{max} = 0.545$ and $m_1 = 65 \text{ Pa}$.

191 4.1.2. Reference yield stress with Bio-Terge

192 When Bio-Terge solution is added to cement paste, yield stress is higher than
 193 for samples containing TTAB or for surfactant-free pastes at the same water-
 194 to-cement ratio. In fact, addition of Bio-Terge solution into a cement paste
 195 has two consequences: solid fraction Φ_p decreases and the intensity of of the
 196 attractive forces between cement grains increases. As a result, reference yield
 197 stress τ_{ref} cannot be fitted by equation 3. Therefore, we choose to describe the
 198 corresponding data with linear regressions: $\tau_{ref} = 1062 W/C - 257$ for set R_B1
 199 and $\tau_{ref} = 369 - 859 W/C$ for set R_B2.

200 4.2. Dimensionless yield stress

201 Results for the normalized yield stress, i.e. $\tau_y/\tau_{y,ref}$, are shown in Fig. 6.

Figure 6: Dimensionless yield stress for all samples (see Table 2 for characteristics of the samples).

202 First of all, data corresponding to the different samples presented in Figs. 3
 203 and 4 collapse on two consistent sets characterized by the surfactant used. For
 204 Bio-Terge samples, the dimensionless yield stress increases with air content. On
 205 the other hand, with TTAB surfactant, all the measured value are below the
 206 reference yield stress; the lowest measured dimensionless yield stresses are 0.8
 207 (f.i. set 4 at 30% air content).

208 There is no major effect of Bio-Terge concentration nor bubble size on the
 209 dimensionless yield stress. During preparation however, we noted that incorpo-
 210 rating aqueous foam in cement paste was more difficult for B2, where Bio-Terge
 211 concentration is lower, because the bubbles tend to break during hand mixing.
 212 Observation of the bubbles after they have risen at the top surface of the
 213 sample has revealed a fundamental difference for the surfactant samples: bub-
 214 bles in Bio-Terge samples are covered with a layer of cement grains (Fig. 7-right)
 215 whereas bubbles in TTAB are bare (Fig. 7-left). Actually bare bubbles are dif-
 216 ficult to observe because they usually break as soon as they reach the sample
 217 surface. On the contrary, in Bio-Terge samples at rest, only few bubbles break.
 218 The difference observed for the rheological behavior of the two surfactant sam-
 219 ples seems to be related to the different nature of the bubbles surface. We
 220 consider each case in the following.

Figure 7: Left: sample from set T1 containing TTAB. Right: sample from set B1 containing Bio-Terge. Note that bubbles tend to break rapidly when exposed to air, especially for samples containing TTAB, so that the number of the bubbles on each picture is not representative of the air content.

221 4.2.1. Bare bubbles (TTAB)

222 The effect of such bubbles are expected to be described by micromechanical
 223 models for capillary inclusions [7, 8], which are based on the Bingham capillary

number $Ca_y = \tau_{y,ref}R/(2\gamma)$. Theoretical dimensionless yield stress for non-deformable bubbles $Ca_y \rightarrow 0$ is given by [7, 8]:

$$\tau_y/\tau_{ref} = \sqrt{(1-\Phi)\frac{5+3\Phi}{5-2\Phi}} \text{ when } Ca_y \rightarrow 0 \quad (5)$$

When the bubbles are fully deformable ($Ca_y \rightarrow \infty$), the relation becomes:

$$\tau_y/\tau_{ref} = \sqrt{(1-\Phi)\frac{3-3\Phi}{3+\Phi}} \text{ when } Ca_y \rightarrow \infty \quad (6)$$

Equations 5 and 6 are plotted in Fig. 8. Both curves have also been obtained experimentally for bubble suspensions in a model yield stress fluid (concentrated oil-in-water emulsion) [9, 10]. In [10], experimental results fitted with equation 5 for experimental Bingham capillary numbers within the range $0.0069 \leq Ca_y \leq 0.11$ and with equation 6 for $Ca_y = 0.57$.

Let us calculate Ca_y for each TTAB data set. As mentioned previously, reference yield stress τ_{ref} decreases with increasing liquid content as described by equation 3. Besides, at low surfactant concentration, surface tension γ decreases when concentration increases. Such a variation is reported in [11] as a function of TTAB concentration in the interstitial solution of the cement paste. By assuming that TTAB concentration in solution is close to the total TTAB concentration, i.e. that the amount of adsorbed molecules is negligible, surface tension can be described by $\gamma = 31 - 6.8 \cdot \ln(C_{res})$ within the range 0.02-0.2 g/L (this formula has been obtained by fitting experimental results from [11], with γ in mN/m and C_{res} in g/L). Using those γ values and equation 3, experimental values of Ca_y are calculated and given in Table 3. In Fig. 8, dimensionless yield stress results of aerated cement paste with TTAB are plotted for comparison with both theoretical curves.

At low air content, experimental dimensionless yield stresses are systemat-

Set	Ca_y
T1	0.08
T2	0.10
T3	0.21 - 0.23
T4	0.34 - 0.36
T5	0.28 - 0.30

Table 3: Bingham capillary numbers for experiments with TTAB

Figure 8: Dimensionless yield stress for samples made with TTAB. Theoretical curves, which have been observed experimentally on model yield stress fluid by Ducloué [19], are indicated for non-deformable bubbles (full line) and fully deformable bubbles (dotted line).

ically lower than theoretical values. This behavior is possibly an experimental artifact and shows that despite all our effort to keep the same preparation protocol for aerated and reference samples, shearing of the paste during hand mixing may be influenced by the presence of bubbles.

However, all the results fall within the range of expected values between the two theoretical curves. Moreover, the dimensionless yield stress values stretch as a function of Ca_y . This can be seen mainly at high air content: the higher the capillary number, the lower the dimensionless yield stress.

4.2.2. Particle covered bubbles (Bio-Terge)

Yield stress measured for aerated Bio-Terge cement pastes is well above the upper bound predicted by theory based on Ca_y (i.e. equation 5). The particle

257 layer attached to the bubble surface suggests that the behavior in the case of
258 Bio-Terge lies in the modified surface properties of the bubbles.

259 Particle covered interfaces have first been reported by *Ramsden* [20] and
260 *Pickering* [21]. Bubbles covered by a dense layer of irreversibly adsorbed parti-
261 cles, called armored bubbles, are known to be very stable compared to surfactant
262 stabilized bubbles: the particle armor can prevent bubble rupture (or coales-
263 cence) [22, 23, 24] and volume decrease due gas transfer (ripening) [25, 26, 27,
264 28, 29].

265 First requirement to allow solid particle adsorption at air-water or oil-water
266 interface is that the particles must be partially hydrophobic. Then, the elec-
267 trostatic barrier to particle adsorption must be low enough [30]. Increase of
268 contact angle of water on cement grains has been observed in the presence of
269 low amount of Bio-Terge, so we can assume that the first point is fulfilled. Ce-
270 ment grains have a size comprised between a few micrometers and 100 μm with
271 average value close to 10 μm [16]. Due to their irregular shape, radius of curva-
272 ture of the edges is several orders of magnitude below the grain size [31], which
273 decreases the adsorption barrier [30]. In addition, cement solution contains a
274 high concentration of dissolved ions [12], and this high electrolyte content re-
275 duces electrostatic repulsion between charged particles and interface, which also
276 decreases the adsorption barrier [30]. All these aspects show that cement par-
277 ticles covered by a monolayer of Bio-Terge molecules are good candidates to
278 adsorb at air-water interfaces.

279 In the micro-mechanical model for the bubbles, the stress of the air-fluid
280 interface is characterized by one value, i.e. the surface tension γ . However,
281 previous studies showed that this simple behavior cannot account for particle
282 stabilized interfaces, where complex behavior arises from the kinetics and irre-
283 versibility of the adsorption of the particles at the interface [30] and leads to

284 an additional extra stress. In the case of an isotropic interface between two
 285 Newtonian fluids, the extra stress can be expressed as a function of two scalars,
 286 namely the shear surface viscosity $\mu_{s,s}$ and the dilatational surface viscosity $\mu_{s,d}$
 287 [32]. The resistance of surface viscosity to the shear stress from the bulk around
 288 the inclusion can be quantified by the Boussinesq numbers $Bq_s = \mu_{s,s}/(\mu_{ext}R)$
 289 and $Bq_d = \mu_{s,d}/(\mu_{ext}R)$, where μ_{ext} is the viscosity of the external fluid. De-
 290 termination of the value of the surface rheological properties of cement covered
 291 bubbles is far out of the scope of this paper. Though, the wide literature re-
 292 lated to the rheology particle covered interfaces can highlight the behavior of
 293 adsorbed cement grains. We will recall here the main literature results. To get
 294 a more complete understanding of this complex issue, one can read the recent
 295 reviews from *Thijssen and Vermant* [33], *Maestro* [34] and *Pitois and Rouyer*
 296 [35].

297 Adsorption of particles to an interface can enhance both the dilatational
 298 [36] and the shear [37] surface viscosities. High surface viscosities indicate that
 299 under applied stress, deformation of the interface is slow. When particle volume
 300 fraction is high, surface viscosities diverge and the interface exhibits a yield stress
 301 behavior [38, 39, 40, 37], i.e. as long as the applied stress is below the yield
 302 stress, it behaves like a solid membrane. When interactions between particles
 303 are weak, yield stress behavior happens for particle surface fractions reaching
 304 the so-called *jamming surface fraction* [36]. On the contrary, when attractive
 305 interaction between the particles at the interface makes them agglomerate, the
 306 critical volume fraction leading to the yield stress behavior can be greatly re-
 307 duced [38, 39, 40, 37]. Note that for particles adsorbed at an interface, attractive
 308 interactions include capillary forces which are enhanced by the roughness of
 309 the particles [38, 39]. Cement-grains covered interfaces are therefore likely to
 310 exhibit a surface yield stress.

311 In addition, the complex rheological properties affect the deformability of the
 312 bubbles. Recent numerical work performed on droplets in shear flow has shown
 313 that the deformation $D = (L - B)/(L + B)$ (where L and B are the major and
 314 minor axes of the deformed droplet) of the inclusion is greatly influenced by the
 315 surface viscosities [41]. For flow conditions which leads to a high deformation
 316 $D \geq 0.35$ when $Bq_s = Bq_d = 0$, the deformation D is divided by a factor 2
 317 when $Bq_s = Bq_d = 10$ or when $Bq_d = 0$ and $Bq_s = 10$. For our system, the
 318 viscosities are expected to diverge, so we can assume that these values of the
 319 Boussinesq number are by far exceeded. Therefore, the bubbles must remain
 320 spherical during the start-of-flow experiment performed on the aerated cement
 321 pastes prepared with Bio-Terge.

322 Eventually, adsorption of hydrophobic cement grains at the surface of the
 323 bubbles leads to two effects: (1) the immobilization of the interface of the bub-
 324 bles due to a surface yield stress and (2) the reduction of the bubble defor-
 325 mation. Due to these two effects, armored bubbles are expected to behave as
 326 non-deformable solid inclusions.

327 In order to compare directly the armored bubbles with solid inclusions, addi-
 328 tional measurements were performed with solid beads instead of bubbles. Pro-
 329 cedure followed for the tests is the same as described in paragraph 2.2.1; at 27
 330 minutes after preparation of the cement paste, we added to the paste 500 μm
 331 diameter polystyrene beads or 2 mm diameter glass beads. These additional
 332 samples contain no surfactant, so reference yield stress is given by equation 3.

333 The micromechanical analysis for solid inclusions assumes no-slip conditions
 334 at their surface [7], and the corresponding theoretical dimensionless yield stress
 335 is:

$$\tau_y/\tau_{ref} = \sqrt{\frac{(1 - \Phi)}{(1 - \Phi/\Phi_m)^{2.5\Phi_m}}} \quad (7)$$

where Φ_m is the maximal packing fraction of the beads within shearing conditions. This curve has been experimentally validated in model yield stress materials [14] and in cement paste [16]. Φ_m value measured in cement paste is 0.56.

Figure 9: Dimensionless yield stress for samples made with Bio-Terge. Dotted line correspond to the theoretical curve for a suspension of solid spheres with maximal solid fraction 0.56. Crosses correspond to measurements carried out with 500 μm polystyrene beads or 2 mm glass beads.

In Fig. 9, we can see that our experimental results for Bio-Terge bubbles and for beads are consistent with equation 7, showing significant increase of the yield stress as a function of inclusion volume fraction, with no effect of inclusion size. Experimental data are slightly above the theoretical values, which could be related to our experimental method and the difficulty to follow accurately the same protocol for cement paste with and without inclusions. However, experimental dimensionless yield stresses for bead suspensions coincide with dimensionless yield stress of bubbles suspensions prepared with Bio-Terge surfactant. Therefore, armored bubbles behave mainly like solid spheres in the cement paste at the onset of yielding.

5. Conclusion

We have investigated the effect of added bubbles with well controlled size and volume fraction on the yield stress of aerated cement paste. Bubbles were

353 stabilized with two surfactants, which are known to have different adsorption
354 behavior with respect to cement grains.

355 The behavior of the bubbles is strongly affected by the surfactant. When sur-
356 factant has low affinity to cement grains, the dimensionless yield stress depends
357 only on the Bingham capillary number Ca_y , which accounts for the deformabil-
358 ity of the bubbles. For $Ca_y \sim 0.1$, i.e. for small bubbles and/or low cement paste
359 yield stress, the yield stress is almost unchanged with respect to the bubble-free
360 paste. On the contrary, when $Ca_y \gtrsim 0.2$, i.e. for large bubbles and/or high
361 cement paste yield stress, a small decrease of the dimensionless yield stress with
362 air volume content can be observed.

363 Totally different behavior is observed when surfactant adsorbs on cement
364 grains. Effect of bubbles is comparable to solid inclusions, and no effect of bubble
365 size can be seen. We attribute this effect to the in-situ hydrophobization of the
366 cement grains and their irreversible adsorption at the bubbles surface, which
367 changes completely the surface properties of the bubbles. In such a case, the
368 yield stress of the aerated cement paste increases significantly while its density
369 decreases in proportion of air introduced in the paste.

370 **Acknowledgements**

371 The authors want to thank Charles Joudon-Watteau for support to make
372 the experiments.

373 This work has benefited from two French government Grants managed by
374 the Agence Nationale de la Recherche [Grants number ANR-11-LABX-022-01
375 and ANR-13-RMNP-0003-01].

376 References

- 377 [1] N. Massoussi, E. Keita, N. Roussel, The heterogeneous nature of bleeding
378 in cement pastes, *Cement and Concrete Research* 95 (2017) 108–116.
- 379 [2] G. Ovarlez, F. Bertrand, S. Rodts, Local determination of the constitu-
380 tive law of a dense suspension of noncolloidal particles through magnetic
381 resonance imaging, *Journal of Rheology* 50 (2006) 259–292.
- 382 [3] F. Gorlier, Y. Khidas, O. Pitois, Yielding of complex liquid foams, *Journal*
383 *of Rheology* 61 (2017) 919–930.
- 384 [4] P.-C. Aïtcin, Entrained air in concrete: rheology and freezing resistance,
385 in: P.-C. Aïtcin, R. J. Flatt (Eds.), *Science and Technology of Concrete*
386 *Admixtures*, Woodhead publishing, 2016, pp. 87–95.
- 387 [5] I. Cantat, S. Cohen-Addad, F. Elias, F. Graner, R. Höhler, O. Pitois,
388 F. Rouyer, A. Saint-Jalmes, *Foams - Structure and dynamics*, Oxford Uni-
389 *versity Press*, 2013.
- 390 [6] R. Rixom, N. Mailvaganam, *Chemical Admixtures for Concrete*, 3rd Edi-
391 *tion*, E. & F.N. Spon Ltd, 1999, p106+.
- 392 [7] X. Chateau, G. Ovarlez, K. Trung, Homogenization approach to the be-
393 *havior of suspensions of noncolloidal particles in yield stress fluids*, *Journal*
394 *of rheology* 52 (2) (2008) 489–506.
- 395 [8] T. L. Nguyen Thi, L. Ducloué, G. Ovarlez, X. Chateau, Rhéologie des
396 *suspensions de bulles dans un fluide à seuil*, in: *21ème Congrès Français de*
397 *Mécanique*, Bordeaux, France, 2013.
- 398 [9] M. Kogan, L. Ducloué, J. Goyon, X. Chateau, O. Pitois, G. Ovarlez, Mix-
399 *tures of foam and paste: suspensions of bubbles in yield stress fluids*, *Rhe-*
400 *ologica Acta* 52 (2013) 237–253.

- 401 [10] L. Ducloué, O. Pitois, J. Goyon, X. Chateau, G. Ovarlez, Rheological be-
 402 haviour of suspensions of bubbles in yield stress fluids, *Journal of Non-*
 403 *Newtonian Fluid Mechanics* 215 (2015) 31–39.
- 404 [11] B. Feneuil, O. Pitois, N. Roussel, Effect of surfactants on the yield stress
 405 of cement paste, *Cement and Concrete Research* 100 (2017) 32–39.
- 406 [12] H. Bessaies-Bey, Polymères et propriétés rhéologiques d’une pâte de ciment
 407 : une approche physique générique, Ph.D. thesis, Université Paris-Est - SIE
 408 (2015).
- 409 [13] B. Feneuil, N. Roussel, O. Pitois, Optimal cement paste yield stress for
 410 the production of stable cement foam, *Cement and Concrete Research* 120
 411 (2019) 142–151.
- 412 [14] F. Mahaut, X. Chateau, P. Coussot, G. Ovarlez, Yield stress and elas-
 413 tic modulus of suspensions of non-colloidal particles in yield stress fluids,
 414 *Journal of Rheology* 52 (2008) 287–313.
- 415 [15] J. Goyon, F. Bertrand, O. Pitois, G. Ovarlez, Shear induced drainage in
 416 foamy yield-stress fluids, *Physical Review Letters* 104 (2010) 128301.
- 417 [16] F. Mahaut, S. Mokéddem, X. Chateau, N. Roussel, G. Ovarlez, Effect
 418 of coarse particle volume fraction on the yield stress and thixotropy of
 419 cementitious materials, *Cement and Concrete Research* 38 (2008) 1276–
 420 1285.
- 421 [17] G. Ovarlez, F. Mahaut, F. Bertrand, X. Chateau, Flows and heterogeneities
 422 with a vane tool: Magnetic resonance imaging measurements, *Journal of*
 423 *rheology* 55 (2011) 197–223.
- 424 [18] R. J. Flatt, P. Bowen, Yodel: a yield stress model for suspensions, *Journal*
 425 *of the American Ceramic Society* 89 (4) (2006) 1244–1256.

- 426 [19] L. Ducloué, Comportement rhéologique des fluides à seuil aérés, Ph.D.
427 thesis, Université Paris Est (2014).
- 428 [20] W. Ramsden, Separation of solids in the surface-layers of solutions and
429 ‘suspensions’ - preliminary account, Proceedings of the Royal Society of
430 London 72 (1904) 156–164.
- 431 [21] S. U. Pickering, Emulsions, Journal of Chemical Society 91 (1907) 2001–
432 2021.
- 433 [22] N. D. Denkov, I. B. Ivanov, P. A. Kralchevski, A possible mechanism of sta-
434 bilization of emulsions by solid particles, Journal of Colloids and Interface
435 Science 150 (2) (1992) 589–593.
- 436 [23] Y. Timounay, E. Lorenceau, F. Rouyer, Opening and retraction of partic-
437 ulate soap films, EPL - Europhysics Letters 111 (2).
- 438 [24] G. Kaptay, On the equation of the maximum capillary pressure induced
439 by solid particles to stabilize emulsions and foams and on the emulsion
440 stability diagrams, Colloids and Surfaces A 282-283 (2006) 387–401.
- 441 [25] M. Abkarian, A. B. Subramaniam, S.-H. Kim, R. Larsen, S.-M. Yang, ,
442 H. A. Stone, Dissolution arrest and stability of armored bubbles, Physical
443 Review Letters 99 (2006) 188301.
- 444 [26] A. Stocco, E. Rio, B. Binks, D. Langevin, Aqueous foams stabilized solely
445 by particles, Soft Matter 7 (4) (2011) 1260–1267.
- 446 [27] A. Maestro, E. Rio, W. Drenckhan, D. Langevin, A. Salonen, Foams sta-
447 bilised by mixtures of nanoparticles and oppositely charged surfactants:
448 relationship between bubble shrinkage and foam coarsening, Soft Matter
449 10 (2014) 6975–6983.

- [28] O. Pitois, M. Buisson, X. Chateau, On the collapse pressure of armored bubbles and drops, *European Physical Journal E* 38 (2015) 48.
- [29] N. Taccoen, F. Lequeux, D. Z. Gunes, C. N. Baroud, Probing the mechanical strength of an armored bubble and its implication to particle-stabilized foams, *Physical Review X* 6 (1) (2016) 011010.
- [30] S. Tcholakova, N. D. Denkov, A. Lips, Comparison of solid particles, globular proteins and surfactants as emulsifiers, *Physical Chemistry Chemical Physics* 10 (2008) 1608–1627.
- [31] N. Roussel, A. Lemaitre, R. J. Flatt., P. Coussot, Steady state flow of cement suspensions: A micromechanical state of the art., *Cement and Concrete Research* 40 (2010) 77–84.
- [32] L. E. Scriven, Dynamics of a fluid interface: equation of motion for newtonian surface fluids, *Chemical Engineering Science* 12 (1960) 98–108.
- [33] J. H. J. Thijssen, J. Vermant, Interfacial rheology of model particles at liquid interfaces and its relation to (bicontinuous) pickering emulsions, *Journal of Physics. Condensed Matter* 30 (2) (2018) 023002.
- [34] A. Maestro, Tailoring the interfacial assembly of colloidal particles by engineering the mechanical properties of the interface, *Current Opinion in Colloid & Interface Science* 39 (2019) 232 – 250.
- [35] O. Pitois, F. Rouyer, Rheology of particulate rafts, films, and foams, *Current Opinion in Colloid & Interface Science* 43 (2019) 125 – 137.
- [36] Y. Timounay, F. Rouyer, Viscosity of particulate soap films: approaching the jamming of 2d capillary suspensions, *Soft Matter* 13 (2017) 3449–3456.
- [37] S. Barman, G. F. Christopher, Simultaneous interfacial rheology and microstructure measurement of densely aggregated particle laden interfaces

475 using a modified double wall ring interfacial rheometer, *Langmuir* 30 (2014)
476 9752–9760.

477 [38] S. Barman, G. F. Christopher, Role of capillarity and microstructure on
478 interfacial viscoelasticity of particle laden interfaces, *Journal of Rheology*
479 60 (1) (2016) 35–45.

480 [39] R. Van Hooghten, L. Imperiali, V. Boeckx, R. Sharma, J. Vermant, Rough
481 nanoparticles at the oil-water interfaces: their structure, rheology and ap-
482 plications, *Soft Matter* 9 (2013) 10791.

483 [40] P. J. Beltramo, M. Gupta, A. Alicke, I. Liascukiene, D. Z. Gunes, C. N.
484 Baroud, J. Vermant, Arresting dissolution by interfacial rheology design,
485 *Proceedings of the National Academy of Sciences* 114 (39) (2017) 10373–
486 10378.

487 [41] J. Gounley, G. Boedec, M. Jaeger, M. Leonetti, Influence of surface vis-
488 cosity on droplets in shear flow, *Journal of Fluid Mechanics* 791 (2016)
489 464–494.