



HAL
open science

TEM study of boron phosphide: Discovery of rhombohedral BP

B.A. Kulnitskiy, V.D. Blank, T.A. Gordeeva, V.A. Mukhanov, Vladimir Solozhenko

► **To cite this version:**

B.A. Kulnitskiy, V.D. Blank, T.A. Gordeeva, V.A. Mukhanov, Vladimir Solozhenko. TEM study of boron phosphide: Discovery of rhombohedral BP. *Solid State Communications*, 2022, 354, pp.114886. 10.1016/j.ssc.2022.114886 . hal-03735898

HAL Id: hal-03735898

<https://hal.science/hal-03735898>

Submitted on 21 Jul 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

TEM study of boron phosphide: Discovery of rhombohedral BP

B.A. Kulnitskiy,^{a,b} V.D. Blank,^{a,b} T.A. Gordeeva,^{a,b} V.A. Mukhanov,^c and V.L. Solozhenko^{d,*}

^a *Technological Institute for Superhard and Novel Carbon Materials, 108840 Troitsk, Russia*

^b *Moscow Institute of Physics and Technology, 141700 Dolgoprudny, Russia*

^c *Department of Chemistry, Lomonosov Moscow State University, 119991 Moscow, Russia*

^d *LSPM–CNRS, Université Sorbonne Paris Nord, 93430 Villetaneuse, France*

Microstructure of sphalerite (3C) boron phosphide, BP, produced by self-propagated high-temperature synthesis has been studied by high-resolution transmission electron microscopy. Along with numerous twins on the $\{111\}_{3C}$ plane, layers of wurtzite (2H) polymorphic modification and previously unknown for BP rhombohedral (9R) structure were found which indicates trimorphism of BP.

Keywords: boron phosphide, transmission electron microscopy, polymorphism, twinning.

Introduction

Boron phosphide BP is a hard (Vickers hardness $H_V \sim 30$ GPa [1]) refractory (melting temperature at ambient pressure is 2840 K [2]) and low-compressible (300-K bulk modulus is 174 GPa [3]) wide bandgap ($E_g = 2.1$ eV [4]) semiconductor with outstanding chemical and high-temperature stability that makes it a promising material for a wide range of applications [5]. Under ambient conditions, BP crystallizes in cubic sphalerite ($F\bar{4}3m$) structure with boron and phosphorus tetrahedrally coordinated to each other. Another tetrahedral structure of boron phosphide, hexagonal wurtzite ($P6_3mc$) polymorph, has also been reported [6], however, in the literature there is no data on the structure and properties of this phase.

The main limitation for the use of boron phosphide is the lack of relatively simple and economical methods of its production, especially, of BP single crystals. The disadvantages of the existing methods are the use of toxic and aggressive reagents, complicated technical implementation and high time consumption. Recently, two new methods of boron phosphide synthesis have been

* Corresponding author (vladimir.solozhenko@univ-paris13.fr)

developed i.e. self-propagated high-temperature synthesis [7] and mechanochemical synthesis [8] that are characterized by simplicity, high efficiency, low cost and good perspectives for large-scale production. Here we report the results of transmission electron microscopy studies of BP produced by self-propagated high-temperature synthesis.

Experimental

Microcrystalline powder of boron phosphide has been synthesized by self-propagating high-temperature reaction of boron phosphate and metallic magnesium: $\text{BPO}_4 + 4\text{Mg} = \text{BP} + 4\text{MgO}$ using the method described earlier [7]. According to X-ray diffraction study (TEXT 3000 Inel, $\text{CuK}\alpha 1$ radiation) the sample is well-crystallized sphalerite BP with lattice parameter $a = 0.45356(9)$ nm, which was close to the literature value $0.4538(2)$ nm [9]. The amount of B_{12}P_2 boron subphosphide impurity caused by a partial decomposition of as-forming BP due to a high local temperatures in the reaction mixture did not exceed 1 vol.%.

Microstructure of boron phosphide has been studied by high-resolution transmission electron microscopy (HRTEM) using JEM-2010 microscope with energy dispersive x-ray spectroscopy (EDS) attachment.

Results and discussion

According to TEM data (Fig. 1), the boron phosphide powder consists of flat polyhedral particles having dimensions from 50 to several hundred nanometers (Fig.1a); significant part of them contains twins. Fig.1b shows two particles containing twins. Traces of twinning planes are shown by arrows. Such particles with a sphalerite structure predominate in the sample. At the same time, other phases were detected in small quantities.

Fig. 2 presents TEM and HRTEM images of sphalerite BP particle containing two systems of twins. White rectangles depict stacking faults which change the layer stacking sequence from $ABCABC$ for cubic (3C) sphalerite structure to ABA for hexagonal (2H) wurtzite structure. The corresponding fast Fourier transform (FFT) image is shown in the inset. Strong streakings parallel to (111) and (1-1-1) are caused by diffuse scattering from $\{111\}$ type stacking faults. Similar structural transformations were previously observed in carbon (diamond \rightarrow lonsdaleite) [10] and in silicon ($\text{SiII} \rightarrow \text{SiIV}$) [11]. According to [12], the lattice parameters of wurtzite BP are $a = 0.320$ nm and $c = 0.531$ nm, which are noticeably different from the lattice parameters of its closest structural analog, wurtzite BN ($a = 0.25505$ nm; $c = 0.4210$ nm [13]).

Fig. 3 shows a BP particle with a complex structure. In the upper part of HRTEM image twins in sphalerite 3C structure along the (111) plane are observed. The trace of the twinning plane is indicated by a vertical line at the top of the figure. In the lower part on the right, twins along the

(11-1) plane are visible. Both twinning planes are marked in Figure. The red circles (Fig. 3b) indicate the reflexes related to the 3C structure located in the upper right part, while the yellow circles indicate the reflexes of the 3C structure located in the upper left part of the figure. The yellow color line indicates the line separating the different phases in the particle. The rhombohedral (9R) phase was formed on both sides of the (111) plane in the lower part of the image. On the right side the tripling occurred along the $[11-1]_{3C}$ direction. On the left part – along the $[111]_{3C}$ direction. The crystal lattice in the upper part corresponds to the sphalerite (3C) structure with lattice parameter $a = 0.4538$ nm, whereas the structure in the lower part is a rhombohedral (9R) lattice with tripled value of interplanar distance for (111) sphalerite planes i.e. $0.262 \times 3 = 0.786$ nm. The tripling is visible both on HRTEM and FFT images. As follows from the comparison of FFT images of two neighboring fragments (Fig. 3b) the $(11-1)_{3C} \parallel (001)_{9R}$ and $[1-10]_{3C} \parallel [11-20]_{9R}$ orientation relation is observed. Red circles indicate reflexes from 3C crystalline lattice. According to our assessment, the lattice parameters of the rhombohedral phase are: $a = 0.321$ nm, $c = 2.358$ nm. Thus, Fig. 3 shows a twinned BP particle which also contains two fragments of rhombohedral phase. The rhombohedral phase in the right part is formed as a result of twinning.

Fig. 4 shows the schematic representation of different structures of the BP composition: a) *ABAB* packing (2H); b) *ABCABC* packing (3C) and c) *ABABCBCAC* packing (9R). Drawings containing models of crystal structures are made in a software package for visualization and analysis Ovito [14]. We could not find any information on the existence of rhombohedral BP in the literature, however, there is the experimental evidence for formation of rhombohedral polymorphic modification of zinc sulfide (ZnS) [15], the structural analogue of BP. This rhombohedral structure of ZnS was found to occur in the 600-1020°C temperature range as an intermediate phase between sphalerite (3C) and wurtzite (2H) structures. In our case, the appearance of rhombohedral BP can be associated with deformation of as-formed sphalerite lattice in the course of ultrafast self-propagated high-temperature reaction, which leads to a change of interplanar distances for $\{111\}_{3C}$ planes and, consequently, results in the change of the lattice symmetry.

Fig. 5a shows a two-phase particle. The left part of the particle corresponds to $B_{12}P_2$ composition and contains polytypes, as evidenced by the elongated streaks passing through the spots in the corresponding FFT-image (Fig. 4b). The right part contains a twice-twinned fragment of BP composition (the corresponding FFT-image is shown in Fig. 4c). The mutual orientation of these two phases corresponds to the $(003)_{B_{12}P_2} \parallel (111)_{BP}$ orientation relation. The arrows denote the $\{111\}_{BP}$ planes. One of the planes separates $B_{12}P_2$ and BP crystals, while the other two are twinning planes in BP crystal. Such a junction of twinning planes is generally denoted as $\Sigma = 9$ [16]. In other words, $\Sigma = 9$ (second order twin) boundary is created when two $\Sigma = 3$ (first order twin) boundaries intersect. EDS spectra of $B_{12}P_2$ is shown in Fig. 4d.

Previously, in boron subphosphide $B_{12}P_2$ synthesized by the same self-propagating high-temperature method we have discovered two systems of twins i.e. conventional twins on the $(0003)_h$ plane and nanotwins resulting from duplication of the rhombohedral unit cell of $B_{12}P_2$ along one of the basic vectors [17]. In the present study, neither these nor other twins were observed in the only

few $B_{12}P_2$ particles found. The latter can be explained by the fact that $B_{12}P_2$ is a secondary phase formed due to the thermal decomposition of as-synthesized BP at points of the local overheating in the reaction front.

Conclusions

In boron phosphide produced by self-propagated high-temperature synthesis, along with traditional sphalerite (3C) polymorphic modification, fragments of wurtzite (2H) polymorph and previously unknown for BP rhombohedral (9R) structure were found which shed new light on polymorphism of boron phosphide.

References

- [1] V.L. Solozhenko, V. Bushlya, Mechanical properties of boron phosphides. *J. Superhard Mater.*, **41** [2] 84-89 (2019).
- [2] V.L. Solozhenko, V.A. Mukhanov, On melting of boron phosphide under pressure. *J. Superhard Mater.*, **37** [6] 438-439 (2015).
- [3] V.L. Solozhenko, O.O. Kurakevych, Y. Le Godec, A.V. Kurnosov, A.R. Oganov, Boron phosphide under pressure: in situ study by Raman scattering and X-ray diffraction. *J. Appl. Phys.*, **116** [3] 033501 (2014).
- [4] A. Agui, S. Shin, Y. Kumashiro, Electronic structure of BP studied by resonant soft X-ray emission spectroscopy. *J. Phys. Soc. Japan*, **68** [1] 166-169 (1960).
- [5] K. Woo, K. Lee, K. Kovnir, BP: synthesis and properties of boron phosphide. *Mater. Res. Express*, **3** [7] 074003 (2016).
- [6] P. Villars, L.D. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases*, American Society for Metals, Metals Park, OH, 1985.
- [7] V.A. Mukhanov, P.S. Sokolov, Y. Le Godec, V.L. Solozhenko, Self-propagating high-temperature synthesis of boron phosphide. *J. Superhard Mater.* **35** [6] 415-417 (2013).
- [8] V.A. Mukhanov, D. Vrel, P.S. Sokolov, Y. Le Godec, V.L. Solozhenko, Ultra-fast mechanochemical synthesis of boron phosphides, BP and B₁₂P₂. *Dalton Trans.*, **45** [25] 10122-10126 (2016).
- [9] S. Rundqvist, Crystal structure of boron phosphide BP. *Congres International de Chimie pure et applique*, Mem. Sect. 1957, 539 (1958).
- [10] B. Kulnitskiy, I. Perezhugin, G. Dubitsky, V. Blank, Polytypes and twins in the diamond-lonsdaleite system formed by high-pressure and high-temperature treatment of graphite. *Acta Cryst. B*, **69**, 474-479 (2013).
- [11] B. Kulnitskiy, M. Annenkov, I. Perezhugin, M. Popov, D. Ovsyannikov, V. Blank, Mutual transformation between crystalline phases in silicon after treatment in a planetary mill: HRTEM studies. *Acta Cryst. B*, **72**, 733-737 (2016).
- [12] H. Momida, T. Oguchi, Effects of lattice parameters on piezoelectric constants in wurtzite materials: A theoretical study using first-principles and statistical-learning methods. *Appl. Phys. Express*, **11**, 041201 (2018).
- [13] A.V. Kurdyumov, V.L. Solozhenko, W.B. Zelyavski, Lattice parameters of boron nitride polymorphous modifications as a function of their crystal-structure perfection. *J. Appl. Crystallogr.*, **28**, 540-545 (1995).
- [14] A Stukowski, Visualization and analysis of atomistic simulation data with OVITO – the Open Visualization Tool. *Model. Simul. Mater. Sci. Eng.*, **18** [1] 015012 (2010).

- [15] D.C. Buck, L.W. Strock, Trimorphism in zinc sulfide. *Am. Mineral.*, **40** [3-4] 192-200 (1955).
- [16] J. Narayan, Dislocations, twins, and grain boundaries in CVD diamond thin films: Atomic structure and properties. *J. Mater. Res.*, **5** [11] 2414-2423 (1990).
- [17] B.A. Kulnitskiy, I.A. Perezhogin, V.D. Blank, V.A. Mukhanov, V.L. Solozhenko, Nanotwinning in boron subphosphide B₁₂P₂. *J. Superhard Mater.*, **41** [2] 139-141 (2019).




Fig. 1. A characteristic TEM image of boron phosphide particles(a); two particles contain twins (b).
Traces of twinning planes are shown by arrows.




Fig. 2. Two systems of twins in BP structure: (a) overview of the particle and (b) high resolution image of a portion of the particle where white rectangles depict the fragments of wurtzite (2H) structure with *BAB* and *ABA* layer stacking sequence; the corresponding FFT image is shown in the inset.




Fig. 3. (a) HRTEM image of BP particle which contains twinned sphalerite phase, as well as two fragments of rhombohedral (9R) polymorph: the upper part shows BP twins on the $(111)_{3C}$ plane; the trace of the twinning plane is indicated by a vertical line at the top of the figure; (b) the corresponding FFT-image. The red circles indicate the reflexes related to the 3C structure located in the upper right part, while the yellow circles indicate the reflexes of the 3C structure located in the upper left part of the figure. The yellow color indicates the line separating the different phases in the particle. At the lower part on both sides of the $(111)_{3C}$ plane (vertical white dash at the bottom of the figure), two fragments of rhombohedral phase were formed. On the right side the tripling occurred relative to the $(11-1)_{3C}$ plane; while on the left side the tripling occurred relative to the $(111)_{3C}$ plane. (c) FFT-image of the right fragment of a particle containing 9R and 3C structures. Red circles indicate reflexes from 3C crystalline lattice.




Fig. 4. Schematic representation of different structures of the BP composition: a) packing $ABAB$ (2H); b) packing $ABCABC$ (3C) and c) packing $ABABCBCAC$ (9R).




Fig. 5. (a) HRTEM image of two-phase particle: the left part is of $B_{12}P_2$ composition and contains polytypes; the right part is twice-twinned fragment of BP composition. The arrows indicate $\{111\}_{BP}$ planes. (b) FFT image of the left part of (a); (c) FFT image of the right part of (a); d) EDS-spectra from $B_{12}P_2$.