

MAGNETISM AND SUPERCONDUCTIVITY BY NMR STUDY

K. Asayama, Y. Kitaoka, Y. Kohori

► To cite this version:

K. Asayama, Y. Kitaoka, Y. Kohori. MAGNETISM AND SUPERCONDUCTIVITY BY NMR STUDY. Journal de Physique Colloques, 1988, 49 (C8), pp.C8-2125-C8-2129. 10.1051/jphyscol:19888952. jpa-00229233

HAL Id: jpa-00229233 https://hal.science/jpa-00229233

Submitted on 4 Feb 2008

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

MAGNETISM AND SUPERCONDUCTIVITY BY NMR STUDY

K. Asayama, Y. Kitaoka and Y. Kohori

Department of Material Physics, Faculty of Engineering Science, Osaka University, Toyonaka, Osaka 560, Japan

Abstract. – Results of NMR measurement on high T_c oxide superconductor are reviewed together with heavy electron superconductor. In high T_c compounds, superconductivity and antiferromagnetism compete with each other, while in heavy electron system both coexist or compete. The property of Cooper pair is discussed in high T_c superconductor together with the heavy electron superconductor.

In the several systems where superconductivity and magnetism interact with each other, heavy electron superconductor and high T_c oxide superconductor are of particular interest. There are several similar aspects in both systems. In these systems antiferromagnetic ordering and superconductivity appear in coexistence or in competition [1]. The property of superconductivity is unconventional in heavy electron system [1] which is also seen in high T_c superconductor in NMR measurement. There is a possibility of non-phonon mechanism, an attractive interaction through a magnetic fluctuations, being responsible for the occurrence of superconductivity, although any direct evidence for this is not proved.

In this paper a recent review on NMR measurements of high T_c superconductor will be presented together with a brief review on heavy electron systems [2].

1. Heavy electron system

1.1 MAGNETISM. – The neutron diffraction measurements have observed the antiferromagnetic correlation, sometimes static antiferromagnetic ordering, appearing in the ground state of heavy electron system, which seems to be a general property of this system [1]. The static antiferromagnetic ordering is reflected in the line broadening associated with the internal field and in the anomaly in the nuclear spin-lattice relaxation rate T_1^{-1} in NMR. In CeAl₂ NMR line broadening due to antiferromagnetic ordering has been reported [3]. A rapid decrease of T_1^{-1} due to a gap opening associated with SDW ordering is observed in URu₂Si₂ [4]. Recent NMR measurements have revealed that the systems CeCu₂Si₂ [5], CeAl₃ [6] and CeInCu₂ [7] are ordered at low temperature.

1.2 SUPERCONDUCTING PROPERTY. $-T_1$ in CeCu₂Si₂ [8], UBe₁₃ [9], URu₂Si₂ [4] and UPt₃ [10] in superconducting state all show an unconventional behavior. T_1^{-1} below T_c decreases monotonously and in proportion to T^3 at low temperature. These behaviors are explained in terms of an anisotropic superconductivity, the gap disappearing on lines at the Fermi surface.

2. High T_c oxide superconductor

2.1 MAGNETISM.

2.1.1 $(La_x Ba_{1-x})_2 CuO_4$. – La₂CuO₄ is an antiferromagnet with $T_N \simeq 240$ K. With replacing La by Ba, T_N decreases rapidly [11] and then superconductivity appears for $x \ge 2.5 \%$ [12]. Figure 1 shows a NQR spectrum of La at 4.2 K [13]. The complicated structure is well explained by a large electric quadrupole interaction together with a small Zeeman energy due



Fig. 1. - ¹³⁹La NQR spectra of La₂CuO₄. Calculated frequencies are shown by arrows [13].

to the magnetic order

$$\begin{split} \mathcal{H}_{\rm Q} &= \frac{e^2 q Q}{4 I \left(2 I - 1 \right)} \left\{ 3 I_z^2 - I \left(I + 1 \right) + \frac{\eta}{2} \left(I_+^2 + I_-^2 \right) \right\} \\ \mathcal{H}_{\rm Z} &= -\gamma \hbar H_\perp \left(I_+ \; \mathrm{e}^{-i\phi} + I_- \; \mathrm{e}^{i\phi} \right) - \hbar H_\parallel I_{\rm Z}. \end{split}$$

Here, H_{\parallel} and H_{\perp} are the parallel and perpendicular component of the internal field at La site with respect to the *c* axis respectively. Taking $e^2 qQ / \hbar$, H_{\parallel} , H_{\perp} and η as 89.3 MHz, 200 Oe, 1000 Oe and zero, the calculated energy levels up to second order of H_Z to H_Q reproduces the experiment quite well. The internal field is the dipole field from the magnetic moments on Cu whose direction is in the c plane with a small component to c axis. Figure 2 shows the change of the spectra with x for R(2)R(3) and R(4)R(5) in figure 1. The splitting due to H_{\perp} exists up to about



Fig. 2. – Spectra in $(La_{1-x}Ba_x)_2$ CuO₄ [13] corresponding to R(2), R(3), R(4) and R(5) in figure 1.

x = 0.025 where the superconductivity starts to appear. With increasing temperature H_{\perp} decreases becoming zero at $T_{\rm N}$, which is plotted in figure 3. The change of H_{\perp} is also plotted. $T_{\rm N}$ agrees with the temperature at which the transversal relaxation rate of signals R(6) and R(7) diverges [14]. $T_{\rm N}$ decreases first rapidly and then slowly. It should be noticed that no abrupt change in H_{\perp} is observed in spite of the discontinuous change of $T_{\rm N}$ around $x \sim 0.008$. This fact indicates that the magnetic arrangements surrounding La do not change over $x \sim 0.008$ drastically. On the other hand no anomaly in the specific heat is observed at $T_{\rm N}$ for x > 0.008 [15]. From these results it is considered that the three dimensional antiferromagnetic ordering appears exists up to x = 0.008 and then a



Fig. 3. – Phase diagram of $(La_{1-x}Ba_x)_2$ CuO₄ system. (•): T_N from NQR [13], (•): from susceptibility [11], (\blacktriangle): H_{\perp} [13].

spin glass type ordering appears where the two dimensional ordering still exists although the long range ordering along c axis is lost. Recently Aharony *et al.* [16] proposed a spin glass type ordering. In their scheme, a local ferromagnetic interaction is induced by the holes introduced at oxygen sites when Ba is substituted to La. This interaction destroys the three dimensional ordering, whereas the two dimensional antiferromagnetic correlation still remains. This model explains well the obtained magnetic phase diagram in figure 3.

2.1.2 YBa₂Cu₃O_{7-y}. – There are two inequivalent Cu sites in CuO₂ plane Cu(II) and in CuO chain Cu(I) for this compound. Since Cu has two isotopes both having I = 3/2, two pairs of NQR signals are expected. The NQR signals of Cu are observed as shown in figure 4a [17-21]. The signals around $30 \sim 32$ MHz and $20 \sim 22$ MHz are assigned to Cu at (II) and (I), respectively after several discussions [19, 20, 22-25]. When Y is replaced by Gd, Sm, and Nd, two pairs of Cu signals appear in almost the same frequency range as in Y case. In these replaced systems, T_1 of the signal around 32 MHz is much shorter than at 20 MHz which supports the above assignment [23]. Furthermore, analyses of Cu NMR spectra in the external field in the grain oriented sample also confirm the above assignment [24, 25].

Figure 4b, c and d show NQR spectra for y = 0.35, 0.7 [26] and 0.9 [25, 27, 28]. The line broadens below 20 K for y = 0.7 [25] and splits at 4.2 K for y = 0.8 [27]. For $y \simeq 1$ an antiferromagnetic ordering was already reported by μ SR [29] and neutron diffraction measurement [30] with $T_N \simeq 400 \sim 540$ K. Furthermore, the neutron diffraction in single crystal for $y \simeq 0.65$ shows



Fig. 4. - NQR spectra of ⁶³Cu and ⁶⁵Cu in YBa₂Cu₃O_{7-y}. (a) $y \sim 0$ [17-21] (b) y = 0.35 [26] (c) y = 0.7 [26] (d) y = 0.1 [25, 27, 28].

an antiferromagnetic order at Cu(II) site appearing below 405 K and then the second ordering at Cu(I) site with small moment below 40 K [31]. Recently, NMR signals due to Cu(II) site are observed around 100 MHz for $y = 0.9 \sim 0.7$ [32]. Thus the signals observed around 30 MHz in figures 4c and d are demonstrated to be due to Cu(I) site. The broadening and splitting observed for y = 0.7 and 0.8 correspond to modifications of the magnetic ordering. The phase diagram obtained by neutron diffraction [31, 33] μ SR [35] is shown in figure 5.



Fig. 5. – Phase diagram of $YBa_2Cu_3O_{7-y}$. Neutron diffraction [30, 31], (\circ) [31], (\circ) [33], μ SR (\blacktriangle) [34], NQR (\bullet) [35]. The solid line in antiferromagnetic phase indicates a change of the magnetic ordering.

2.2 SUPERCONDUCTING PROPERTY. $-T_1$ of Cu in YBa₂Cu₃O_{7-y} system was measured by several groups [17, 19, 20, 36-38]. The results agree qualitatively with each other. Figure 6 shows T_1 at Cu(II) site [37]. The characteristic aspects are as following: T_1^{-1} above T_c is not linear to T but changes more slowly. Below T_c , T_1^{-1} decreases rapidly and then shows a saturation behavior at low temperature. By comparing T_1 of ⁶³Cu and ⁶⁵Cu the relaxation above 20 K has been confirmed to be magnetic in origin whereas below 20 K the electric quadrupole relaxation begins to participate. By using a relation [37]

$$1/^{63}T_{1 M} = 1/^{63}T_{1 obs} \times \frac{Z - {}^{65}Q/^{63}Q}{\left({}^{65}\gamma/^{63}\gamma\right)^2 - \left({}^{65}Q/^{63}Q\right)^2}$$

with $Z = {}^{63}T_{1 \text{ obs}} / {}^{65}T_{1 \text{ obs}}$ the magnetic relaxation $T_{1 \text{ M}}$ has been separated from the observed T_{1} as shown in the figure by open dot circle. Thus T_{1}^{-1} associated with the magnetic relaxation decreases nearly in proportion to T^{3} at low temperature.

To see the behavior in normal state in wider temperature range, T_1 has been measured in YBa₂ (Cu_{0.98}Zn_{0.02})₃ O₇ with $T_c = 60$ K [39]. As seen in figure 6, the values above 100 K are almost the same as those for x = 0, whereas $T_1T = \text{const.}$ law begins to hold below 100 K. The deviation from T, T = const.law above 100 K may be attributed to antiferromagnetic fluctuations [38].

 T_1 of Y is proportional to T above T_c [36]. Below T_c , T_1^{-1} decreases monotonously rapidly.

The behavior of T_1 of Cu in superconducting state is in contrast with the usual BCS superconductor. T_1^{-1} in superconducting state is expressed as [40]



Fig. 6. $-T_1^{-1}$ of ⁶³Cu at Cu(II) site in YBa₂Cu₃O_{7-y} and YBa₂ (Cu_{0.98}Zn_{0.02})₃ O_{7-\delta}. (•): y = 0, (\odot): magnetic relaxation T_1 M separated from observed value, (\blacktriangle): $y \sim 0.35$ (above T_c [37, 41] and below T_c [42]), (o): Zn substituted system.

$$1/T_{1 s} = \frac{\pi}{\hbar} \int A^{2} \left(N_{s}^{2} (E) + M_{s}^{2} (E) \right) f(E) \left(1 - f(E) \right) dE$$

where A is the hyperfine coupling constant, $N_{\rm s}(E)$ and $M_{\rm s}(E)$ are $\frac{N_0 E}{\sqrt{E^2 - \Delta^2}}$ and $\frac{N_0 \Delta}{\sqrt{E^2 - \Delta^2}}$, respectively, with normal density of states N_0 . f(E) is the Fermi function, and 2 Δ is the energy gap. Owing to a uniform energy gap in BCS superconductor, which gives rise to a divergence of both $N_{\rm s}(E)$ and $M_{\rm s}(E)$ at the gap edge, T_1^{-1} shows an enhancement just below $T_{\rm c}$ and then decreases exponentially. The absence of the enhancement and non-exponential behavior, nearly T^3 dependence at low temperature, in the present system suggested the anisotropic nature of the superconductivity (p or d-wave).

On the other hand, the Knight shift of Cu is observed to decrease below T_c indicating the singlet pairing in this system [37]. Thus the superconducting pairing function was considered to be of d-wave due to a strong on-site Coulomb repulsion [37]. In the d wave pairing the gap disappears on lines and/or points which provides T^3 or T^5 dependence of T_1^{-1} at low temperature. Furthermore, $\Delta(\theta)$ takes positive and negative values becoming zero on the average which makes M_s zero. If we assume tentatively $2\Delta(\theta) = 12kT_c \cos \theta$ the experiment is well reproduced as shown by a solid line in the figure.

 T_1 of Cu in (I) site shows no rapid decrease below T_c as if the gap at this site is small [20]. However, T_1 at Cu(I) is sample dependent: an analysis of T_1^{-1} by Kitaoka *et al.* [37] shows that the quadrupole relaxation plays a dominant role which masks the intrinsic relaxation associated with the conduction electrons, whereas Warren *et al.* show that the relaxation is magnetic [20]. So we cannot say about the superconducting property on site (I).

 T_1^{-1} on site (II) for YBa₂Cu₃O_{6.65} becoming superconducting below 60 K is also shown in figure 6. T_1^{-1} in normal state is surprisingly suppressed compared with YBa₂Cu₃O₇ [37, 41]. A sharp peak appearing below T_c is attributed to an extra relaxation due to some impurity electron spins (probably free Cu spins) whose fluctuation rate decreases rapidly below T_c and passes through Cu NMR frequency at about 50 K [42]. It should be noted that the effect of Zn substitution and O defficiency on T_1 in normal state are quite different, even when the depressions of T_c are same.

Quite recently, Kitaoka et al. [43] have found that $1/T_1$ of ¹⁷O substituted at CuO₂ plane has a clear enhancement just below T_c which suggests strongly the s-wave pairing of the superconductivity. The d-wave like behaviour observed in Cu relaxation may be explained by a rapid reduction of antiferromagnetic fluctuation below T_c which is considered to be localized at Cu site and enhances the $1/T_1$ of Cu in normal state. This suggests that the superconductivity is carried by O p-holes. A remarkable reduction of $1/T_1$ of Cu at CuO₂ plane from YBa₂Cu₃O₇ to YBa₂Cu₃O_{0.65} in normal state may be attributed to a reduction of the antiferromagnetic fluctuations associated with the decrease of oxygen hole number.

In summary, superconductivity and antiferromagnetic ordering in high- T_c compounds appear with their region in contact with each other when the concentration of Ba or O are changed in $(La_{1-x}Ba_x)_2$ CuO₄ and YBa₂Cu₃O_{7-y}. This behavior is similar to the heavy electron system where the superconductivity and magnetic ordering coexist or compete.

In $YBa_2Cu_3O_7$, the nuclear relaxation behavior of Cu is d-wave like as in the case of heavy electron system. However recent study on O suggests s-wave pairing. The d-wave like behavior in Cu may be caused by a reduction of antiferromagnetic spin fluctuations localized on Cu site in superconducting state. This suggests that the superconductivity is carried by oxygen p-holes.

Acknowledgments

Our works in this review were partially supported by Research Project for high T_c superconducting Oxides of Ministry of Education, Science and Culture of Japan.

 Recent reviews for heavy electron system: Fisk, Z., Ott, H. R. and Aeppli, G., Jpn J. Appl. Phys. 26 (1987) 1882;

Ott, H. R., Physica B 148 (1987) 1;

Fisk, Z., Hess, D. W., Pethick, C. J., Pines, D., Smith, J. L., Thompson; J. D. and Willis, J. O., *Science* **239** (1988) **33**;

Fisk, Z., Borges, H., McElfresh, M., Smith, J. L., Thompson, J. D., Ott, H. R., Aeppli, G., Bucher, E., Lambert, S. E., Maple, M. B., Broholm, C. and Kjiem, J. K., Proc. Inter. Conf. on High Temperature Superconductors and Materials and Mechanism of Superconductivity, Interlaken, 1988 (Proc. I.C.H.T.S. 1988 Interlaken).

- [2] Review on NMR measurement in heavy electron system: MacLaughlin, D. E., J. Magn. Magn. Mater. 47 (1985) 121;
 Asayama, K., Kitaoka, Y. and Kohori, Y., Proc. ICCF 6 (Frankfurt) 1988.
- [3] MacLaughlin, D. E., Pena, O. and Lysak, M., Phys. Rev. B 23 (1981) 1039.
- [4] Kohara, T., Kohori, Y., Asayama, K., Kitaoka,
 Y., Maple, M. B. and Torikachvili, S., Solid State
 Commun. 59 (1986) 603; Jpn J. Appl. Phys.
 Suppl. 26 (1987) 1247.
- [5] Kitaoka, Y., Yamada, H. and Asayama, K., Proc. ICCF 6 (Frankfurt) 1988.
- [6] Nakamura, H., Kitaoka, Y., Asayama, K. and Flouquet, J., submitted to J. Phys. Soc. Jpn and ICCF 6 (Frankfurt) 1988.
- [7] Takagi, S., Kimura, T., Sato, N., Satoh, J. and Kasuya, T., to be published J. Phys. Soc. Jpn; Nakamura, H., Kitaoka, Y., Asayama, K., Onuki, Y. and Komatubara, T., submitted to J. Phys. Soc. Jpn.
- [8] Kitaoka, Y., Ueda, K., Kohori, K., Asayama, K., Onuki, K. and Komatsubara, T., J. Magn. Magn. Mater. 52 (1985) 341;
 Kitaoka, Y., Ueda, K., Kohara, T., Kohori, Y. and Asayama, K., Proc. 5th Int. Conf. Valence Fluctuations (Bangalore) 1987.
- [9] MacLaughlin, D. E., Cheng Tien, Clark, W. G., Law, M. D., Fisk, Z., Smith, J. L. and Ott, H. R., *Phys. Rev.* 53 (1984) 1833.

- [10] Kohori, Y., Kohara, T., Shibai, H., Oda, Y., Kaneko, T., Kitaoka, Y. and Asayama, K., J. Phys. Soc. Jpn 57 (1988) 395; Jpn J. Appl. Phys. Suppl. 26 (1987) 1239; Proc. ICCF 6 (Frankfurt) 1988.
- [11] Fujita, T., Aoki, Y., Maeno, Y., Sakurai, J., Fukuba, H. and Fujii, H., Jpn J. Appl. Phys. 26 (1987) L368.
- [12] Bednorz, J. G. and Muller, K. A., Z. Phys. B 6 (1986) 189.
- [13] Kitaoka, Y., Hiramatsu, S., Kohara, T., Asayama, K., Ohishi, K., Kikuchi, M. and Kobayashi, N., Jpn J. Appl. Phys. 26 (1987) L397;
 Kitaoka, Y., Hiramatsu, S., Ishida, K., Kohara, T., Asayama, K., J. Phys. Soc. Jpn 56 (1987) 3024;
 Kitaoka, Y., Ishida, K., Hiramatsu, S. and Asayama, K., J. Phys. Soc. Jpn 57 (1988) 734.
- [14] Kumagai, K., Watanabe, I., Aoki, H., Nakamura, Y., Kimura, T., Nakamichi, Y. and Nakajima, H., *Physica B* 148 (1987) 480.
- [15] Kobayashi, T. and Amaya, K., Proc. I.C.H.T.S. (Interlaken) 1988.
- [16] Aharony, A., Birgenean, R. J., Coniglio, A., Kastner, M. A. and Stanely, H. E., submitted to Phys. Rev. Lett.
- [17] Furo, I., Janossy, A., Mihaly, L., Banki, P., Procsic, I., Bakonyi, I., Heinmaa, I., Joon, E. and Lipmaa, E., *Phys. Rev. B* 36 (1987) 5690.
- [18] Lütgemeier, H. and Pieper, M. W., Solid State Commun. 64 (1987) 267.
- [19] Mali, M., Brinkmann, D., Pauli, L., Roos, J., Zimmerman, H. and Hullinger, J., Phys. Lett. A 124 (1987) 112.
- [20] Warren, W. W., Jr., Walstedt, R. E., Brennert, G. F., Espinosa, G. P. and Remeika, J. P., Phys. Rev. Lett. 59 (1987) 1860;
 Walstedt, R. E., Warren, W. W., Jr., Tycho, R., Bell, R. F., Brennert, G. F., Cava, R. J., Schneemeyer, L. and Waszczah, J., submitted to Phys. Rev. B.
- [21] Kitaoka, Y., Hiramatsu, S., Ishida, K., Kohara, T., Oda, Y., Amaya, K. and Asayama, K., *Physica* B 148 (1987) 298.
- [22] Kohara, T., Kohori, Y., Kitaoka, Y., Hiramatsu, S., Ueda, K., Kaburagi, M., Oda, Y. and Asayama, K., Physica B 148 (1987) 292.
- [23] Kohori, Y., Shibai, H., Oda, Y., Kohara, T., Kitaoka, Y. and Asayama, K., J. Phys. Soc. Jpn 57 (1988) 744.

- [24] Shimizu, T. et al. to be published J. Phys. Soc. Jpn.
- [25] Lütgemeier, H., Proc. I.C.H.T.S. (Interlaken) 1988.
- [26] Kitaoka, Y., Hiramatsu, S., Ishida, K., Asayama, K., Takagi, H., Iwabuchi, M., Uchida, S. and Tanaka, S., J. Phys. Soc. Jpn 57 (1988) 737.
- [27] Mihaly, L. et al., Proc. I.C.H.T.S. (Interlaken) 1988.
- [28] Ishida, K. et al., in preparation.
- [29] Nishida, N. et al., J. Phys. Soc. Jpn 57 (1988) 597.
- [30] Tranquada, J. M., et al., Phys. Rev. Lett. 60 (1988) 156.
- [31] Kadowaki, H., Nishi, M., Yamada, Y., Takeya, H., Takei, H., Shapiro, S. M. and Shirane, G., preprint.
- [32] Yamada, Y. et al., submitted to J. Phys. Soc. Jpn.
- [33] Rossat-Mignod, J. et al., Proc. I.C.H.T.S. (Interlaken) 1988.
- [34] Nishida, N. et al., Proc. I.C.H.T.S. (Interlaken) 1988.
- [35] Kitaoka, Y. et al., Proc. ICM (Paris) 1988.
- [36] Markert, J. T., Noh, T. W., Russek, S. E. and Cotts, R. M., Solid State Commun. 63 (1987) 847.
- [37] Kitaoka, Y., Hiramatsu, S., Kondo, T. and Asayama, K., J. Phys. Soc. Jpn 57 (1988) 30; Kitaoka, Y., Hiramatsu, S., Kohori, Y., Ishida, K., Kondo, T., Shibai, H., Asayama, K., Takagi, H., Uchida, S., Iwabuchi, H. and Tanaka, S., Proc. I.C.H.T.S. (Interlaken) 1988.
- [38] Imai, T., Shimizu, T., Tsuda, T., Yasuoka, H., Takabatake, T., Nakazawa, Y. and Ishikawa, M., to be published in J. Phys. Soc. Jpn.
- [39] Kohori, Y. et al., to be submitted to J. Phys. Soc. Jpn and Proc. ICM (Paris) 1988.
- [40] MacLaughlin, D. E., Solid State Phys. (Academic Press) 31 (1976).
- [41] Warren, W. W. Jr., Walstedt, R. E., Brennert, G. F., Cava, R. J., Battlogg, B., Rupp, L. W., preprint.
- [42] Ishida, K. et al., submitted to J. Phys. Soc. Jpn.
- [43] Kitaoka, Y., Ishida, K., Asayama, K., Katayama-Yoshida, H., Okabe, Y. and Takahashi, T., submitted to *Nature*.