Temperature dependence of the resistivity and structure of liquid alkali metals

H. Minoo, C. Deutsch, J.P. Hansen

► To cite this version:

H. Minoo, C. Deutsch, J.P. Hansen. Temperature dependence of the resistivity and structure of liquid alkali metals. Journal de Physique Lettres, 1977, 38 (9), pp.191-194. 10.1051/jphyslet:01977003809019100 . jpa-00231357

HAL Id: jpa-00231357

<https://hal.science/jpa-00231357>

Submitted on 1 Jan 1977

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Classification
 Physics Abstracts
 7.126 — 8.214

TEMPERATURE DEPENDENCE OF THE RESISTIVITY AND STRUCTURE OF LIQUID ALKALI METALS

H. MINOO, C. DEUTSCH

Laboratoire de Physique des Plasmas (*), Université Paris XI, Bâtiment 212,
 91405 Orsay, France

and

J. P. HANSEN

Laboratoire de Physique Théorique des Liquides (*), Université Paris VI,
 4, place Jussieu, 75005 Paris, France

(Reçu le 17 février 1977, révisé le 1^{er} avril 1977, accepté le 5 avril 1977)

Résumé. — Un facteur de structure phénoménologique et simple $a(k)$ pour les métaux alcalins liquides est proposé, et utilisé pour calculer le coefficient de température de la résistivité à volume constant. Un excellent accord avec les résultats expérimentaux est obtenu.

Abstract. — A simple phenomenological structure factor $a(k)$ for liquid alkali metals is proposed, and used to calculate the temperature coefficient of the resistivity at constant volume. Excellent agreement with experimental results is obtained.

In a previous paper [1] we considered electronic transport in dense fully-ionized hydrogen; here we extend our calculations to liquid alkali metals. This extension requires an appropriate choice of $a(k)$ and $U(k)$, where $a(k)$ is the static structure factor of the system and $U(k)$ is the Fourier transform of the screened pseudo-potential of a single ion (form factor).

The basic formula for the electrical resistivity, ρ , of liquid metals, in the framework of the nearly-free-electron (NFE) model is [2]

$$\rho = \frac{3\pi}{\hbar e^2} \frac{\Omega}{v_F^2} \int_0^1 |U(k)|^2 a(k) 4 \left(\frac{k}{2k_F} \right)^3 d \left(\frac{k}{2k_F} \right) \quad (1)$$

where k_F and v_F are, respectively, the Fermi wave-number and the Fermi velocity, and Ω is the atomic volume.

The temperature coefficient of ρ at constant volume, α_Ω , is defined by :

$$\alpha_\Omega \equiv \frac{T_M}{\rho_M} \left(\frac{\partial \rho}{\partial T} \right)_\Omega \quad (2)$$

where T_M is the melting temperature and ρ_M is the

electrical resistivity at T_M . The evaluation of α_Ω requires a knowledge of $[\partial a(k)/\partial T]_\Omega$. This quantity has not yet been measured experimentally, and has to be evaluated theoretically. The widely used Percus-Yevick hard-sphere model is unsatisfactory for the reasons given in reference [1]. Moreover, as was shown by Greenfield *et al.* [3], no combination of hard-sphere diameter and packing fraction can lead to quantitative agreement with the experimental data of the structure factor of liquid Na and K.

Because of these difficulties the question of the temperature dependence of the resistivity [4] is left open [5, 6].

In the present work, we obtain a structure factor for liquid alkali metals by a normalized linear combination of $a(k)_{\text{OCP}}$, and the correct thermodynamic limit of $a(k)$ at long-wavelength, $a(0)$; $a(k)_{\text{OCP}}$ is the structure factor, obtained from Monte-Carlo simulations, of the classical One-Component Plasma (OCP) [7]. Combining this structure factor with the empty-core model for the ionic pseudopotential, we obtain α_Ω for liquid alkali metals in excellent agreement with experimental results.

(*) Laboratoire associé au C.N.R.S.

(*) Equipe associée au C.N.R.S.

The structure factor $a(k)$ is related to the pair distribution function $g(r)$ by

$$a(k) = a(0) + 4\pi n_i \int_0^\infty [g(r) - 1] \left(\frac{\sin kr}{kr} - 1 \right) r^2 dr \quad (3)$$

where $a(0)$ is the long-wavelength limit of $a(k)$ and is defined by

$$a(0) = 1 + 4\pi n_i \int_0^\infty [g(r) - 1] r^2 dr. \quad (4)$$

In a first approximation we consider a liquid alkali metal as a set of ion cores and free degenerate valence electrons with equal number densities ($n_i = n_e$). Moreover, at the initial stage of this development, ion cores are regarded as point charges interacting through the repulsive coulomb potential and degenerate valence electrons are viewed as merely forming a uniform neutralizing background. This is essentially the basis of the OCP model. Brush, Sahlin, and Teller [8] have noted that the OCP is a reasonable model of liquid alkali metals, and later Ng [9] showed that certain equilibrium quantities, such as the melting temperature, the liquid structure factor, the specific heat at constant volume, and the entropy of liquid alkali metals near the triple point are correctly accounted for by the OCP model. As regards the structure factor of liquid alkali metals, the overall agreement between the experimental results and those obtained from the OCP is good except that $a(k)_{\text{OCP}}$ tends to zero as $k \rightarrow 0$ whereas the experimental curve does not (cf. Fig. 1).

In fact the charge neutrality and perfect screening conditions imply that [10] :

$$a(x)_{\text{OCP}} \simeq \alpha^2 x^2 / 3 \Gamma \quad \text{as } x \rightarrow 0 \quad (5)$$

where $x = k/2 k_F$, $\alpha = (18 \pi Z)^{1/3}$ and Γ is the single dimensionless parameter on which depend the equilibrium properties of the OCP :

$$\Gamma = \beta(Ze)^2/r_i \quad (6)$$

where $\beta = (k_B T)^{-1}$.

However for real liquid metals the OCP model is too crude and one has to take into account the finite-size effect of ion cores and the polarization of the valence electrons by the ionic-charge distribution. These effects lead to a finite value of $a(0)$, which is related to the isothermal compressibility, χ_T , through the standard relation :

$$a(0) = n_i \chi_T / \beta. \quad (7)$$

This result can also be obtained in the framework of the two-component charged-particle model of a liquid metal [11].

Now, our basic assumption is that the structure factor of liquid alkali metals can be written as

$$a(k) = f(k) a(0) + [1 - h(k)] a(k)_{\text{OCP}} \quad (8)$$

where $a(0)$ is taken from experiment, $a(k)_{\text{OCP}}$ is obtained from the Monte-Carlo simulation of the OCP [7], [12], and the functions $f(k)$ and $h(k)$ are chosen such that $a(k)$ tends to unity when $k \rightarrow \infty$ and fulfils the following sum rule [expressing that $g(0) = 0$] :

$$\int_0^\infty [1 - a(k)] k^2 dk = 2 \pi^2 n_i. \quad (9)$$

In our calculation we chose

$$f(k) = \exp - (kr_i/5)^4$$

and

$$h(k) = C \exp - [(kr_i - 10)/5]^4,$$

and we adjusted C in such a way that the sum-rule, eq. (9), is obeyed by $a(k)$ as defined in eq. (8). The adjusted value of C , and also the maximum height of $h(k)$ are very small compared to unity and range between 10^{-4} and 10^{-3} . Consequently in the interval $0 \leq k \leq 2 k_F$ we have $f(k) \approx 1$, $h(k) \approx 0$ and also

$$a(k) \approx a(0) + a(k)_{\text{OCP}}. \quad (10)$$

If we call ρ_1 and ρ_2 the resistivities obtained from eq. (8) and (10) respectively, then $(\rho_1 - \rho_2)/\rho_1 < 10^{-4}$. This allows us to use eq. (10) safely for the purpose of resistivity calculations.

The structure factor $a(k)$ as obtained from eq. (8) is compared with the experimental results, $a(k)_{\text{exp}}$, of Greenfield *et al.* [13] for liquid K at 135 °C and

FIG. 1. — (A) Structure factor, $a(k)$, of liquid K at 135 °C. $a(k)_{\text{exp}}$: experimental results of Greenfield-Wellendorf-Wiser ; $a(k)_{\text{OCP}}$: structure factor of the classical one-component plasma (OCP) ; $a(k)$: obtained from eq. (8) with $a(0)_{\text{exp}}$ and $a(k)_{\text{OCP}}$. (B) Long-wavelength region of $a(k)$.

liquid Na at 200 °C on figures 1 and 2 respectively. Γ for K at 135 °C is 153 and for Na at 200 °C is 163. $a(k)_{\text{OCP}}$ at these Γ are not available, and the closest values of Γ for which $a(k)_{\text{OCP}}$ is computed are 155 and 160.

FIG. 2. — Structure factor of Na at 200 °C.

It is seen that the agreement between the theoretical and the experimental curves is good except that the first and, to a lesser extent, the second peaks are somewhat overestimated. It is interesting to note that the theoretical and experimental curves are in phase, in contrast to the hard-sphere model [3].

In order to obtain α_Ω as defined in eq. (2), the electrical resistivity, ρ , at constant volume, Ω_M , was computed from eq. (1). Ω_M is the volume of liquid near melting. The structure factor $a(k)$ was derived from eq. (8) or (10) using $a(k)_{\text{OCP}}$ from references [7] and [11], and $a(0)_{\text{exp}}$. The function $U(k)$ was obtained in the framework of the empty-core model [14]

$$U(k) = -\frac{2}{3} \varepsilon_F \lambda^2 \cos(sx) / [x^2 + \lambda^2 f(x)] \quad (11)$$

where $s = 2 k_F r_c$, $\lambda^2 = (\pi a_0 k_F)^{-1}$, a_0 is the first Bohr radius, ε_F is the Fermi energy, $f(x)$ is the Lindhard function

$$f(x) = \frac{1}{2} + \frac{1-x^2}{4x} \ln \left| \frac{1+x}{1-x} \right| \quad (12)$$

and r_c is the empty-core radius. r_c was adjusted to reproduce the experimental resistivity at melting, ρ_M . Figure 3 shows the comparison between experimental results and theoretical predictions of the resistivity of liquid alkali metals at constant volume Ω_M and at different temperatures. Values of α_Ω thus obtained theoretically are compared in table I (column 5) with experimental results (column 3). The experimental results are those measured by Endo [15] for Na, K, Rb and Cs and by Lien and Sivertsen [16] for Na, K and Rb. The maximum relative error of our results given in the table is 4×10^{-3} . If another potential

FIG. 3. — Electrical resistivity, ρ , of liquid alkali metals at constant volume, Ω_M , and at different temperatures, T . Ω_M : liquid volume near the melting point; (...) : experimental results; (+ + +) our results.

$U(k)$ is used, e.g. that proposed by Harrison [17], the calculated α_Ω differs by less than 0.1 %.

The importance of the contribution of $a(0)$ in these calculations can be seen by putting $a(0) = 0$ and $a(k) = a(k)_{\text{OCP}}$ in eq. (8). The results thus obtained for α_Ω are reproduced in column 7 of the table. It is seen that in this case the agreement deteriorates appreciably.

Finally the apparently linear behaviour of $\rho(T)$ at low temperatures exhibited in figure 3 is qualitatively accounted for by the very weak T -dependence of $a(k)$, as can be seen through the inversion of the virial relationship

$$\int \frac{4\pi e^2}{k^2} [a(k) - 1] d^3k = \frac{U}{N} \simeq -\frac{0.9 e^2}{r_i}, \quad \Gamma \gg 1 \quad (13)$$

where the right-hand-side is T -independent.

These results show that :

a) $a(k)$ as obtained from eq. (8) with $a(0)_{\text{exp}}$ reproduces the structure factor of liquid alkali metals reasonably well ;

b) it is possible to obtain α_Ω from Ziman's formula in quantitative agreement with the experimental data in the case of liquid alkali metals.

On the basis of these results we are now in a position to extend our previous calculations [1] to dense alkali metal vapors in the super-critical regime.

TABLE I

Temperature coefficient of the resistivity at constant volume, α_Ω , and the electrical resistivity, ρ_M , of liquid alkali metals near their melting. r_c is the empty-core radius in atomic units. ^(a) Measured by Endo. ^(b) Measured by Lien and Sivertsen.

	Experimental results		$[a(0)_{\text{exp}}, a(k)_{\text{OCP}}]$		$[0, a(k)_{\text{OCP}}]$	
	ρ_M ($\mu\Omega \text{ cm}$)	α_Ω	r_c (au)	α_Ω	r_c (au)	α_Ω
Li	25	—	0.91	0.59	0.79	0.46
Na	9.6	0.84 ^(a) , 0.82 ^(b)	1.53	0.79	1.39	0.57
K	13	0.77 ^(a, b)	1.94	0.76	1.78	0.61
Rb	22	0.7 ^(a) , 0.65 ^(b)	1.96	0.7	1.80	0.57
Cs	36	0.69 ^(a)	2.00	0.66	1.84	0.54

References

- [1] MINOO, H., DEUTSCH, C. and HANSEN, J. P., *Phys. Rev. A* **14** (1976) 840.
- [2] ZIMAN, J. M., *Phil. Mag.* **6** (1961) 1013.
- [3] GREENFIELD, A. J., WISER, N., LEENSTRA, M. R. and VAN DER LUGT, W., *Physica* **59** (1972) 571.
- [4] GREENFIELD, A. J., *Phys. Rev. Lett.* **16** (1966) 6.
- [5] FABER, T. E., *An Introduction to the Theory of Liquid Metals* (Cambridge U.P., Cambridge) 1972.
- [6] ZIMAN, J. M., *The Properties of Liquid Metals*, Proc. 2nd. Int. Conf. Tokyo, 1972 (Taylor and Francis LTD, London) 1973, p. 13.
- [7] HANSEN, J. P., *Phys. Rev. A* **8** (1973) 3096.
- [8] BRUSH, S. G., SAHLIN, H. L. and TELLER, E., *J. Chem. Phys.* **45** (1966) 2102.
- [9] NG, K., preprint, University of Florida (1974).
- [10] STILLINGER, F. H. and LOVETT, R., *J. Chem. Phys.* **49** (1968) 1991.
- [11] WATABE, M. and HASEGAWA, M., *The Properties of Liquid Metals*, Proc. 2nd Int. Conf. Tokyo, 1972 (Taylor and Francis LTD, London) 1973, p. 133, see also DEUTSCH, C., *J. Non-Cryst. Solids* **8-10** (1972) 713.
- [12] GALAM, S. and HANSEN, J. P., *Phys. Rev.* **14** (1976) 816.
- [13] GREENFIELD, A. J., WELLENDOFF, J. and WISER, N., *Phys. Rev. A* **4** (1971) 1607.
- [14] ASHCROFT, N. W., *J. Phys. C* (Proc. Phys. Soc.) **1** (1968) 232.
- [15] ENDO, H., *Phil. Mag.* **8** (1963) 1403.
- [16] LIEN, S. Y. and SIVERTSEN, J. M., *Phil. Mag.*, **20** (1969) 759.
- [17] HARRISON, W. A., *Pseudopotentials in the theory of metals* (Benjamin, New York) 1966.