Electric field induced tricritical point in chiral polarized liquid crystals

A. Michelson, D. Cabib

► To cite this version:

A. Michelson, D. Cabib. Electric field induced tricritical point in chiral polarized liquid crystals. Journal de Physique Lettres, 1977, 38 (15), pp.321-323. 10.1051/jphyslet:019770038015032100 . jpa-00231386

HAL Id: jpa-00231386

<https://hal.science/jpa-00231386>

Submitted on 1 Jan 1977

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Classification
 Physics Abstracts
 64.70E — 61.30

ELECTRIC FIELD INDUCED TRICRITICAL POINT IN CHIRAL POLARIZED LIQUID CRYSTALS

A. MICHELSON

and

D. CABIB

Physics Department, Technion, Haifa, Israel

(Reçu le 1^{er} juin 1977, accepté le 23 juin 1977)

Résumé. — On présente une théorie de la transition entre un smectique C polarisé uniformément et un smectique C* hélicoïdal en présence d'un champ électrique parallèle aux couches, en utilisant la théorie de Landau. Le diagramme de phase (champ électrique-température) a un point tricritique (E_t , T_t). Les valeurs de E_t et T_t sont exprimées en fonction des propriétés macroscopiques du matériau.

Abstract. — We present a Landau theory of the transition between a uniformly polarized smectic C phase and a distorted smectic C* phase in the presence of an electric field parallel to the layers. The field-temperature (E - T) phase diagram is shown to exhibit a tricritical point (E_t , T_t). The values of E_t , T_t are expressed in terms of observable macroscopic properties of the material.

We have been attempting recently [1] to explain some macroscopic properties of recently discovered [2-5] polarized liquid crystals composed of chiral molecules (DOBAMBC and related materials). These materials present a helicoidal smectic C phase (named the C* phase) with spontaneously polarized layers. On the basis of the suggested [2] linear coupling between the layer polarization and the quadrupolar order parameter characterizing the tilt in the C* phase, we found qualitative agreement with experiments on the structure of the C* phase and on the linear response to an external electric field E parallel to the layers. For $E = 0$, experiments [2] and theory [1, 6] agree in showing a second-order phase transition from the smectic A to the C* phase. For an infinitesimal $E \neq 0$, the theory [1] predicts a monotonically decreasing line of critical temperatures $T_c(E)$ separating a uniformly polarized smectic C phase (at $T > T_c$) and a distorted smectic C* phase (at $T < T_c$). The distortion induced by the field in the C* phase is essentially a tilt of the axis of the helix with respect to the layer normal, which makes the C* phase biaxial.

In this paper, we go a step further in studying the line $T_c(E)$ and show that it terminates at a tricritical point (E_t , T_t), so that at $E > E_t$ the phase transition becomes first order. As in the previous works [1, 7], we use a formalism based on the Landau theory of second-order phase transitions.

Because of the linear coupling between the layer polarization and the tilt angle, these two are proportional below the transition [1, 2]. It can be shown [1] that only one complex parameter is independent, and one can choose $P = P_x + iP_y$ as such a parameter (P_x , P_y are the cartesian components of the layer polarization; the z -axis is chosen to be normal to the layers). In the smectic C* phase, P varies helicoidally in the z -direction, with a pitch much larger than the interlayer distance. Therefore we will consider P as a slowly varying function of z and expand the free energy F in both P and $\partial P/\partial z$. The expansion of F (per unit volume) has the form [7]

$$F = V^{-1} \int \frac{1}{2} [K_1 |P|^2 + iK_2 (P \partial P^*/\partial z - P^* \partial P/\partial z) + K_3 |\partial P/\partial z|^2 + K_4 |P|^4 - E(P + P^*)] d^3r. \quad (1)$$

The integration is performed over the sample volume V , and the main assumption is that only K_1 is temperature dependent among the coefficients $K_1, \dots, K_4$. The ordinary dielectric coupling, $-\frac{1}{2} \chi E^2$, is omitted from (1), since it is small [2] compared with the ferroelectric coupling, $-PE$. Expanding P in a Fourier series $P(z) = \sum_k P_k e^{ikz}$ and substituting

into (1), we obtain

$$F = \frac{1}{2} [K_1 |P_0|^2 + K_4 |P_0|^4 - E(P_0 + P_0^*)] + \frac{1}{2} \sum_k' [(A_k + 4 K_4 |P_0|^2) |P_k|^2 + K_4 (P_0^{*2} P_k P_{-k} + \text{c.c.})] + \frac{1}{2} K_4 \sum_{kk'k''}' P_k P_{k'} P_{k''}^* P_{k+k'-k''}^*, \quad (2)$$

where

$$A_k = K_1 + 2 K_2 k + K_3 k^2, \quad (3)$$

and the primes exclude $k = 0$ from the summation on k . The quantity P_0 , corresponding to a uniform polarization, obviously vanishes for $E = 0$. In this case the helicoidal phase is characterized by a pitch $l = 2\pi/|k_0|$, where k_0 , the wave number of the soft mode of the smectic A to C* phase transition, is determined from the minimization of $A_k : \partial A_k / \partial k = 0$. This yields

$$k_0 = -K_2/K_3. \quad (4)$$

The critical temperature T_{c0} at $E = 0$ is determined from the equation $A_{k_0}(T_c) = 0$, where

$$A_{k_0}(T) = K_1(T) - K_2^2/K_3. \quad (5)$$

Assuming linear dependence of A_{k_0} on T near $T_{c0} : A_{k_0}(T) = C^{-1}(T - T_{c0})$, we obtain from (5) :

$$K_1(T) = C^{-1}(T - T_{c0}) + K_2^2/K_3. \quad (6)$$

The zero-field dielectric susceptibility at $T > T_{c0}$ is $\chi = K_1^{-1}$; it tends to the finite value

$$\chi_c = K_3/K_2^2 \quad (7)$$

at $T \rightarrow T_{c0} + 0$, and behaves according to the Curie-Weiss law

$$\chi \cong C(T - T_{c0})^{-1} \quad (8)$$

at

$$T - T_{c0} \gg C\chi_c^{-1}.$$

For $E \neq 0$, the higher-temperature phase is a uniformly polarized smectic C, characterized by a real $P_0 \neq 0$ and $P_k = 0$ for all $k \neq 0$; P_0 is determined, as a function of T and E , from the equation

$$K_1(T) P_0 + 2 K_4 P_0^3 = E \quad (9)$$

following from the minimization of F with respect to P_0 . As T goes below $T_c = T_c(E)$, the free energy (2) becomes unstable with respect to the appearance of a non-zero P_k , in addition to P_0 , so that a second-order transition occurs to a distorted (distorted because of $P_0 \neq 0$) smectic C* phase. To determine the soft mode of this transition, one has to diagonalize the harmonic part of F , quadratic in P_k ($k \neq 0$), and find the lowest eigenvalue A_{k_0}' of the quadratic expression. One thereby determines the wave number k_0 of the soft mode ψ which is a certain linear combination of P_{k_0}

and $P_{-k_0}^* : \psi = \alpha P_{k_0} + \beta P_{-k_0}^*$. $T_c = T_c(E)$ is found from the equation $A_{k_0}' = 0$ together with eq. (9). It is then possible to present F in the effective form

$$F = F_0 + \frac{1}{2} (A_{k_0}' |\psi|^2 + B |\psi|^4 + \dots). \quad (10)$$

Then it can be shown that, on increasing E , the coefficient B decreases along the line $T_c(E)$, until it vanishes at the tricritical point (E_t, T_t) . The procedure described, which is simple but rather tedious, makes it possible to find the exact (within the Landau theory) parametric equations of the critical line $T_c(E)$ and the values of E_t, T_t (expressed in terms of χ_c, C , and K_4). It turns out, however, that a much simpler, although approximate, calculation based on neglecting the off-diagonal terms $P_k P_{-k}$ in (2) leads to the same results with small differences (e.g., a difference of 4% in the value of E_t). For the sake of brevity and simplicity, we will use the approximate method here.

By neglecting the coupling terms $P_k P_{-k}$ in (2), the soft mode is again $\psi = P_{k_0}$ with k_0 from (4). However, T_c is now determined from the equation

$$A_{k_0}' = A_{k_0} + 4 K_4 P_{00}^2 = 0, \quad (11)$$

where P_{00} is the equilibrium value of P_0 at the transition point. Since at this point $P_k = 0$ ($k \neq 0$), P_{00} must satisfy eq. (9) with $K_1 = K_1(T_c)$. It then follows from (5)-(7), (9), (11) that

$$E = \chi_c^{-1} P_{00} (1 - 2 \chi_c K_4 P_{00}^2), \quad (12)$$

$$T_c = T_{c0} - 4 C K_4 P_{00}^2. \quad (13)$$

Eq. (12), (13) are parametric equations of the line $T_c(E)$. For

$$E \ll (\chi_c^3 K_4)^{-1/2}, \quad P_{00} \cong \chi_c E,$$

and we return to the quadratic dependence

$$T_{c0} - T_c(E) \propto E^2$$

found in our previous work [1].

Slightly below T_c , the system is characterized by two parameters, ψ (complex) and P_0 (real). Putting in (2) $P_k = 0$ for $k \neq 0, k_0$ and $P_{k_0} = \psi$, we obtain

$$F = \frac{1}{2} (K_1 P_0^2 + K_4 P_0^4 - 2 E P_0 + A_{k_0} |\psi|^2 + 4 K_4 P_0^2 |\psi|^2 + K_4 |\psi|^4). \quad (14)$$

Here ψ is the order parameter of the phase transition, and P_0 is a non-critical parameter coupled to ψ through the term $P_0^2 |\psi|^2$. To express F as a function of ψ only, we proceed as in a recent work of Benguigui [9]. Solving the equation $\partial F / \partial P_0 = 0$ with respect to P_0 infinitesimally below T_c and expanding the solution in powers of $|\psi|^2$, we get

$$P_0 = P_{00} - \frac{4 K_4 P_{00} |\psi|^2}{K_1 + 6 K_4 P_{00}^2} + O(|\psi|^4). \quad (15)$$

Substituting (15) into (14), we arrive at (10), with

$$B = K_4 \frac{K_1 - 10 K_4 P_{00}^2}{K_1 + 6 K_4 P_{00}^2}. \quad (16)$$

To find the tricritical point, we put $B = 0$ and, using eqs. (5) and (11), we obtain

$$P_{00}^2 = K_2^2/14 K_3 K_4 = 0.071/\chi_c K_4. \quad (17)$$

Substituting (17) into (12), (13), we get

$$E_t = 0.228 \chi_c^{-3/2} K_4^{-1/2}, \quad (18)$$

$$T_t = T_{c0} - 0.284 C \chi_c^{-1} \quad (19)$$

(the values obtained by the exact method are $E_t = 0.220 \chi_c^{-3/2} K_4^{-1/2}$ and $T_{c0} - T_t = 0.238 C \chi_c^{-1}$). According to the Landau theory [8], K_4 is related to the jump in specific heat Δc occurring at the smectic A to C* phase transition (at $E = 0$) by the formula $\Delta c = C^2 T_{c0}/4 K_4$; hence (we use the exact value for E_t)

$$E_t = 0.44(\Delta c/C^2 \chi_c^3 T_{c0})^{1/2}. \quad (20)$$

Formula (20) expresses E_t in terms of measurable quantities.

The simplified calculation presented in this paper results in k_0 independent of E (eq. (4)). According to the more accurate calculation mentioned before, k_0 is a decreasing function of P_{00} , and thereby of E . However, for $E \leq E_t$, the decrease in k_0 is negligible, and therefore the above approximation is completely justified. For $E \gg E_t$, the growth of E should lead to an appreciable decrease of k_0 until the helix is completely unwound [2, 3] ($k_0 = 0$). A theoretical description of this unwinding poses great difficulties, because the Landau theory is inapplicable for first-order transitions far from the tricritical point.

In conclusion, we have demonstrated on the basis of the Landau theory [8], that the line $T_c(E)$ of second-order phase transitions between the electrically induced uniform smectic C phase and the electrically distorted smectic C* phase terminates at a tricritical point. Having related the critical quantities E_t , T_t to other measurable properties of the material, we hope to stimulate further experimental work on these interesting liquid crystal phases.

References

- [1] MICHELSON, A., BENGUIGUI, L. and CABIB, D., To be published in *Phys. Rev. A*, May 1977.
- [2] MEYER, R. B., LIEBERT, L., STRZELECKI, L., KELLER, P., *J. Physique Lett.* **36** (1975) L-69.
- [3] MARTINOT-LAGARDE, Ph., *J. Physique Colloq.* **37** (1976) C3-129.
- [4] PIERANSKI, P., GUYON, E. and KELLER, P., *J. Physique* **36** (1975) 1005.
- [5] KELLER, P., LIEBERT, L. and STRZELECKI, L., *J. Physique Colloq.* **37** (1976) C3-27.
- [6] PRIEST, R. G., *J. Chem. Phys.* **65** (1976) 408.
- [7] MICHELSON, A., *Phys. Lett.* **60A** (1977) 29.
- [8] LANDAU, L. D. and LIFSHITZ, E. M., *Statistical Physics* (Addison-Wesley Pub. Co.) 1974.
- [9] BENGUIGUI, L., *Phys. Status Solidi (b)* **60** (1973) 835.