Cr⁴⁺-doped silicates: spectroscopy and laser applications

V.P. MIKHAILOV, N.V. KULESHOV, V.G. SHCHERBITSKY, B.I. MINKOV,
N.I. ZHAVORONKOV, A.S. AVTUKH, T.G. GLYNN* and R. SHERLOCK*

Institute for Applied Physics Problems, Belarusian State University, Minsk 220064, Belarus

** University College Galway, Ireland*

Chromium doped forsterite and YAG have been shown to be efficient laser materials for the near infrared [1,2]. The lasing centers were described as Cr⁴⁺ ions occupying tetrahedrally coordinated positions. Recently, laser action in Cr⁴⁺:Y₂SiO₅ was demonstrated at low temperatures [3]. In this paper we discuss the spectroscopic properties of tetravalent chromium in two silicates Y₂SiO₅ (YSO) and Gd₂SiO₅ (GSO). The results of polarized optical absorption, emission and lifetime measurements are presented.

At least two types of the near infrared emitting centers were observed in YSO. The dominant strong absorption bands with peaks at about 16700 and 14000 cm⁻¹, weak absorption at about 10000 cm⁻¹ and broad emission band with peak at 1250 nm are assigned to transitions on Cr⁴⁺ ions, substituting for the Si in distorted tetrahedral sites. The temperature dependence of two zero-phonon lines observed at 1148.7 nm and 1144.3 nm indicated the 33.5 cm⁻¹ splitting in excited state of this centers. Fluorescence decay time excited by 578 nm pumping varied from 11.5 μs at 77K to 0.8 μs at 300 K. A decreasing of emission intensity was observed with temperature increasing giving an evidence for strong nonradiative processes.

Another type of emitting centers in YSO had a weak absorption bands at about 20500 and 13000 cm⁻¹ and fluorescence band with peak at about 1.2 μm. The emission lifetime at 77 K was found to be 5.2 μs and extremely strong temperature fluorescence quenching was observed for this center.

A broad near infrared emission band peaking at 1.32 μm was observed in GSO with a lifetime of 1.7 μs at 77 K. At room temperature the fluorescence intensity and lifetime was two orders of magnitude smaller than that at 77 K. This emission associated with dominant absorption bands at 18000 and 14000 cm⁻¹ was assigned to ³T₂ - ³A₂ transition of tetrahedrally coordinated Cr⁴⁺.

Q-switched operation of ruby laser was observed using both these crystals as saturable absorbers. The giant pulses were 80 - 100 ns in duration and upto 0.5 J in energy at flash-lamp pump energy of about 1.5 kJ.

References

1. V.Petricevic, S.K.Gayen, R.R.Alfano, Appl. Opt. **27** (1988) 4162.
2. B.Angert, N.I.Borodin, V.M.Garmash, V.A.Zhitnyuk, A.G.Okhrimchuk, O.G.Siyuchenko, A.V.Shestakov, Kvantov. Electron.(Moscow). **15** (1988) 113.
3. C. Deka, B.H.T. Chai et al, Appl. Phys. Lett. **61** (1992) 2141.