Monitoring of SiC Deposition in an Industrial CVI/CVD Reactor by In-Situ FTIR Spectroscopy

H. Mosebach, V. Hopfe, M. Erhard, M. Meyer

► To cite this version:

H. Mosebach, V. Hopfe, M. Erhard, M. Meyer. Monitoring of SiC Deposition in an Industrial CVI/CVD Reactor by In-Situ FTIR Spectroscopy. Journal de Physique IV Proceedings, 1995, 05 (C5), pp.C5-97-C5-104. 10.1051/jphyscol:1995509 . jpa-00253765

HAL Id: jpa-00253765

<https://hal.science/jpa-00253765>

Submitted on 1 Jan 1995

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Monitoring of SiC Deposition in an Industrial CVI/CVD Reactor by *In-Situ* FTIR Spectroscopy

H. Mosebach, V. Hopfe*, M. Erhard and M. Meyer**

Kayser-Threde GmbH, Wolfratshauser Str. 48, 81379 München, Germany

* Fraunhofer-Institut für Werkstoffphysik und Schichttechnologie, PF 16, 01171 Dresden, Germany

** Daimler-Benz AG, Zentrales Werkstofflabor, 81663 München, Germany

Abstract. A FTIR based method was developed for *in-situ* monitoring the gas phase chemistry in the reaction chamber of technological scale CVI/CVD reactors. Using methyltrichlorosilane (MTS) as SiC precursor, several gaseous species could be detected including MTS, SiCl_2 , $(\text{SiCl}_3)_{n=1,2}$, SiCl_4 , HSiCl_3 , CH_4 , CH_3Cl and HCl which, consequently, can be monitored simultaneously. First attempts have been established for deriving arbitrary and absolute concentrations of species from emission spectra. The determined composition of the reaction mixture supports recent theoretical results of kinetic modelling. Using the established technique, several runs have been monitored within the SiC-CVI/CVD reactor at different stages of deposition. Unexpectedly strong variations of concentrations of most of the gaseous species have been detected whose reason is not fully clear yet. These technique will be a key element in establishing a closed loop process control.

1. INTRODUCTION

Chemical vapour deposition (CVD) as well as infiltration (CVI) are premier techniques for the production of fibre reinforced ceramic composite materials. Fibre woven structures (preforms) are coated/impregnated in a hot wall reactor by pyrolysing a mixture of precursor gases, which precipitates the ceramic material within the pores of the preform. The techniques are attractive for forming composites with superior mechanical properties and high thermal stability, but the long processing time (CVI) of typically some days up to weeks and the poor run-to-run reproducibility still limit the applicability of that technology.

In order to maximize the potential of CVD technology, flexible, high yield processes are required. Critical in achieving this potential is an effective degree of process control. To date this has largely been ignored due to the technical challenges posed. These often include corrosive atmospheres, particulates, hot environments, vibrations, difficulties in establishing steady states, measurement (e.g. sensitivity) and response time issues. Reactor operation in an open loop with optimization of process parameters based on characterization of post processed materials is the conventional way of operation. In CVI e.g., the change in precursor concentration leads to uncontrolled variations of the pore filling rate, and consequently, to unwanted closing of unfilled pores. Thus, the use of a sensor system for *in-situ* monitoring is a key element for improving control of CVD/CVI processes.

Although the deposition and infiltration techniques are used on a technological scale, the underlying chemistry is not completely understood [1,2]. Using extractive techniques, gas phase reactions governing CVD related processes have been studied extensively during the past fifteen years by means of mass spectrometry and FTIR. These methods suffer from having no capability of detecting intermediates and thus, give no complete look into the chemistry. This drawback can be overcome by *in-situ* techniques, in which optical methods are most suitable. Many different spectroscopic methods have been used, particularly for gas-phase reaction studies to understand the mechanisms and kinetics of

CVI/CVD and chemically based physical vapour deposition [3-8]. First attempts were carried out to investigate surface processes in CVD systems by *in-situ* FTIR reflection and emission spectroscopy [9]. Amongst all the different spectroscopic techniques the FTIR method seems to be one of the most favourable for *in-situ* monitoring because of important advantages like multicomponent capability, the common application of emission, transmission and even reflection spectroscopy, and finally the low operating costs.

Most of the above mentioned research was focussed on basic problems and measurements in specially designed lab reactors. So far, only two projects are known, in which FTIR *in-situ* monitoring was applied to prototype production plants. In one group the ability of film (ferroelectric films) reflectance and radiance measurements during MOCVD was demonstrated [8]. In previous papers the authors of this paper presented the application of FTIR *in-situ* monitoring to a full scale SiC CVI/CVD production plant, where the feasibility of FTIR *in-situ* monitoring could be verified and important results on the SiC chemistry could be achieved when using methyltrichlorosilane (MTS) as precursor [2,11].

It is the goal of this work to establish *in-situ* FTIR monitoring methods as leading components for a future process control line on CVD/CVI production scale reactors. This paper presents, after a short outline of the hardware adaption, the chemistry involved, and the spectrometric aspects of the analysis, some very recent not fully exploited results of *in-situ* monitoring of CVD/CVI runs at the DB plant and a first attempt at quantification of the precursor gas concentration.

2. EXPERIMENTAL AND ANALYTICAL SYSTEM

The FTIR system K300 was used as the spectrometric device for analysis. This instrument was originally designed for open path environmental monitoring consisting of a collecting telescope, which feeds the IR radiation coming in from a remote radiation source (either an artificial source for transmission measurements or a hot plume) into the spectrometer. The K300 system has a maximum, apodized, spectral resolution of 0.1 cm^{-1} and is equipped with a MCT detector ranging from $450 - 3500\text{ cm}^{-1}$ wavenumber. With this detector the particularly interesting region of the stretching and bending vibrations of the chlorinated silanes was covered.

For installation at the DB CVD/CVI reactor the telescope of the K300 was removed and replaced by a new optical interface connected to the reactor, see Fig.1.

Fig. 1: Schematic diagram of FTIR and CVI/CVD reactor system.

Two tubes made of graphite were implemented on either side of the hot zone of the reactor, which were aligned on-axis to the K300 line of sight. The tube opposite the spectrometer was designed for collimating the IR radiation from an external infrared source into the reaction zone in case of transmission measurements. In case of emission measurements this port will be left open to have a low background radiation. The process dependent IR radiation to be analyzed by the spectrometer was fed into the K300 via the second tube. The outer ends of the tubes were closed by IR transparent KBr windows being purged with argon in order to avoid coverage by reaction by-products.

By means of comprehensive test measurements the feasibility of the analytical method could be demonstrated, algorithms for the interpretation of IR spectra were developed and better understanding of the SiC chemistry was achieved [2]. After a longer period of optimization of the measuring configuration the best results have been achieved by emission spectroscopy [11]. Test runs were made in a temperature range from 670 K to 1320 K. Beside MTS also other compounds like methane and tetrachlorosilane were used as input gases. Several gaseous species have been detected, including MTS, SiCl_2 , $(\text{SiCl}_3)_{n=1,2}$, SiCl_4 , HSiCl_3 , H_2SiCl_2 , CH_4 , CH_3Cl and HCl (Fig.2) also possible indications for CH_3 radicals and SiC clusters.

Fig. 2: FTIR monitoring of a typical CVI run: Emission spectrum of MTS / H_2 .

The CVI/CVD runs at the DB plant were normally performed at process temperatures between 1170 K and 1470 K under reduced pressure (typically 10 - 50 hPa) with a reaction mixture of MTS and H_2 . Fig. 2 illustrates observed emittance bands detected during a typical CVI run.

A specific problem of the spectroscopy of reactive gas mixtures at high temperatures is the quantification of the results, i.e. to estimate concentrations of the species from band intensities, since it was found that most of the mentioned compounds are not stable at process temperatures, not even SiCl_4 . Therefore, it is very difficult at operation temperature to prepare a sample for analysis with known concentration of the species of interest, but this is essential for quantitative analysis.

In order to extract concentration proportional quantities from spectra, reference measurements must be performed. This can be done by turning off, at intervals, the incoming precursor gas flow while keeping

ping all other parameters of the whole system unchanged. The background radiation, originating from the hot walls, has a blackbody characteristic which makes them useful for estimating apparent emittance quantities by forming the ratio of the sample and reference spectra. Furtheron, spurious effects in the IR single beam spectra are removed by this procedure so all signatures resulting from gaseous species in the CVI reaction zone. The observed apparent emittance values are proportional to the concentrations, a value of 100 means that concentration was at or below the detection limit. This simple but very convenient calibration method is useful for estimating concentration changes of individual species.

3. ONLINE MONITORING WITH *IN-SITU* FTIR SPECTROMETRY

3.1 Monitoring an SiC - FCVI Run

The SiC forced flow infiltration (FCVI) of a demonstrator nozzle at the DB reactor was on-line monitored by spectrometric analysis with the K300. The process parameters are listed in Tab. 1:

Table 1: Parameters of the SiC- CVI/CVD processes on the demonstrator nozzle.

Process type	Forced flow CVI (FCVI)	CVD
MTS flow rate (liquid)	3.7 ml/ min	17 ml/min
H ₂ flow rate	7.5 l/ min	10 l/min
Carrier gas	Ar	Ar
Reaction temperature	1220 K	1470 K
Total pressure behind nozzle	50 hPa	
Pressure	varying between 10 - 20 hPa	50 hPa

The following compounds were clearly detected: MTS, SiCl₂, SiCl₄, (SiCl₃)_{n=1,2}, SiHCl₃, a chlorosiloxanes band, CH₃Cl, HCl and CH₄. Next, realtime measurements with different time scale have been performed: (i) with 25 s sampling time over a period of 12min., and (ii) with 9 s sampling time over 250 s. Caused by software restrictions in case (ii) the concentration changes of only one species have been followed.

Fig. 3: Time dependence of emittance values of MTS, SiCl₂, SiCl₄ and CH₄.

Fig. 3 shows the time dependence of the observed emittance values of the four species MTS, SiCl_2 , SiCl_4 and CH_4 . These compounds along with HCl and $(\text{SiCl}_3)_{n=1,2}$ were the dominating features in obtained spectra. The concentrations of these four species significantly changed with time and were, as a striking result, strongly correlated. Also with higher time resolution these concentration changes are clearly detectable, see Fig. 4. The pressure difference behind and in front of the nozzle also varied significantly (between 10 and 20 hPa) which have been correlated with the change in concentration of the detected species. After the CVI run a leakage in the high pressure region was found, which possibly gave rise to the pressure fluctuations.

During start-up of the CVI run, the K300 monitoring was carried out with the shortest possible sampling time, which at the desired resolution of 1 cm^{-1} is around 2 seconds. This was done for inspecting the initial phase of the CVI process. It was found that typical emittance values were observed after about 20 seconds. The presently available software does not allow this time dependence to be registered.

Fig. 4: Time dependence of emittances for MTS (curve has been fitted by spline function interpolation).

3.2 Monitoring a SiC CVD Run

In a second step the same demonstrator nozzle was encapsulated with SiC. This CVD run was also monitored *in-situ* by realtime spectrometric analysis with the K300. For process parameters see Tab.1.

Fig. 5: Time dependence of emittances for MTS and SiCl_4 .

In contrast to the CVI runs only six species have been detected: MTS, SiCl_2 , SiCl_4 , HCl , CH_4 and chlorosilanes. In addition, the observed emittance values were considerably lower than those measured during the infiltration run, which might be caused by higher reaction rates at higher temperatures.

Fig. 5 and 6 show the time dependence of the SiCl_2 , SiCl_4 and MTS emittance values. Despite the flows of MTS and H_2 were kept constant, periodical emittance peaks of MTS were observed. There is a strong correlation between these maxima and the SiCl_4 peaks. On the contrary, there seems to be less significant correlation between MTS and SiCl_2 emittances. The minimum emittance values in these plots indicate the actual detection limits.

Fig. 6: Time dependence of emittances for MTS and SiCl_2 .

4. ESTIMATION OF CONCENTRATION

Caused by a lack of reference spectra for intensity calibration at working temperature, the quantitative spectroscopy is very difficult. The *variation of concentration* can be estimated by taking into account the following assumptions: (i) the absolute emittance E of the gaseous species is $E \ll 1$, and (ii) the background radiation, as well as (iii) the reabsorption are negligible. With the additional assumption of (iv) negligible changes in temperature dependence of the integrated band intensity (constant oscillator strength), also the *absolute concentration* of MTS can be derived.

The above stated assumptions (i) and (ii) have been verified by measuring the radiation fluxes within the spectrometer-reactor configuration using a calibrated blackbody source. Reabsorption phenomena (iii) have been checked by comparing the band contour of the HCl rotational/vibrational band with simulated spectra.

For estimating *concentration changes* two data processing procedures have been developed:

- Estimation of maximum intensity (baseline method) of selected bands having low overlap with bands of other species.
- Estimation of weighting factors by balancing the ratio of two spectra within the region of a selected band of the component to be measured. This is a better attempt for partially overlapping bands of different species.

For estimating the *absolute concentration* of MTS a multi-step concept was established. It is based on a set of reference spectra being measured as a function of temperature in an inert atmosphere:

- (1) Selecting a MTS emission with a low temperature dependence of the integrated band intensity and band position: band at 803 cm^{-1} .
- (2) Using the spectrum of pure MTS at 870 K as a reference where no decay products have been detected, the corresponding absolute concentration (partial pressure) is derived from control of the precursor feed system.
- (3) Calculating the MTS concentration (or partial pressure) at higher temperatures by the spectra balancing method (see above)

The results are summarized in Tab.3 for some reaction conditions.

Table. 3: Concentration estimates of individual gaseous species.

Temp	p	MTS	H_2	-----Concentration-----						
				MTS	SiCl_2	SiCl_3	SiCl_4	CH_3Cl	CH_4	HCl
/K/	/hPa/	/slm/	/slm/	/Pa/	/1)/	/1)/	/1)/	/1)/	/1)/	/1)/
870	10	10.5	7.5	500	0	0	0	0	0	0
1070	10	10.5	7.5	407	0	0	0	0	0	7.6
1320	10	10.5	7.5	78.2	46	5	0	0	9.0	18.7
1320	10	21	7.5	150	90	23	3	1	17	19
1320	10	10.5	0	145	90	110	10	10	12	42
1320	10	10.5	15	64.8	39	0	0	0	7.5	39.0
1320	20	10.5	7.5	71.5	86	10	3	0	13	40

1) arbitrary units

5. KINETICS OF THE MTS DECAY

The estimated concentrations of MTS and some other species (CH_4 , CH_3Cl , Tab.3) are much higher than the equilibrium concentration (cf. Tab.1 in [2]) which gives evidence for a kinetically controlled reaction. Without being able within the framework of this paper to discuss the kinetics of the MTS pyrolysis reactions in more detail, it might be very useful to compare the results given above with some recent theoretical attempts [1]. Supported by RRKM calculations the most abundant reaction channels of the primary decay of MTS are given by equation (1) - (3). Reaction (4) is less probable because of its higher activation entropy [10].

The reaction rate of the primary reaction increases rapidly with total pressure, e.g. from 1 kPa to 100 kPa by a factor of 20. This is accompanied by reaction branching where the C-H bond cleavage (eq.2) becomes more probable. The products of the primary decay can undergo several consecutive reaction. In a hydrogen rich mixture, being typical for the SiC-CVI/CVD process, equation (5)-(6), for instance, are dominating but in an "inert" atmosphere the reaction paths (7)-(8) are more probable.

The most important gaseous species for the deposition reaction are expected to be: SiCl_2 , CH_4 and HSiCl_3 [10].

In comparing the kinetic model with both the spectroscopic results and the thermodynamic estimates [2], the following conclusions can be drawn:

- (i) Most of the species proposed by kinetic theory have been identified in the experiments. Because of the variety of reaction channels it cannot be distinguished whether some key species, as SiCl_2 and CH_3Cl , are arising from primary bond cleavage or from secondary reactions.
- (ii) The CVI process is kinetically controlled. This is suggested by the observation that the concentrations of CH_3SiCl_3 , CH_4 and CH_3Cl are some orders higher and those of SiCl_4 and HSiCl_3 are lower than derived from thermodynamic equilibrium.
- (iii) The MTS decay rate increases with total pressure, and the distribution of species changes.

6. CONCLUSION AND OUTLOOK

The FTIR method presented in this paper is well suited for *in-situ* monitoring the gas atmosphere in the reaction chamber of technological scale CVI/CVD reactors. More than ten gaseous species and intermediates have been identified and can be monitored simultaneously. Using the established technique, several CVI/CVD runs have been followed online. The performance has been demonstrated by multicomponent measurements with a time resolution down to 2 s. Unexpectedly strong variations of concentrations of most of the gaseous species have been detected whose reason is not fully clear yet.

The determined composition of the reaction mixture supports recent theoretical results of kinetic modeling. Together with the advanced in-situ FTIR monitoring capabilities established here, this approach will serve as a starting point for developing a closed loop control of CVD based coating techniques. Related work is underway.

Acknowledgements

This work was funded by the Commission of the European Community (CEC) within the BRITE-EU-RAM research programme under contract number BREU-CT91-0447.

The CVI/CVD plant at Daimler-Benz AG was built by Archer Technicoat Ltd, UK. Archer also realized the mechanical modifications of the reactor for FTIR adaption with the K300.

References

- [1] Osterheld T.H., Allendorf M.D. and Melius C.F., Sandia Report SAN93-8576.UC-401, (1993).
- [2] Hopfe V., Mosebach H., Erhard M., Meyer M., J. Molec. Structure 347(1995) 331.
- [3] Ho P. and Breiland W.G., Appl. Phys. Lett., 43 (1983) 125.
- [4] Hanabusa M. and Kikushi H., Jpn. J. Appl. Phys., 22 (1983) 11; M. Hanabusa et.al., Springer Series in Chem. Phys., 39 (1984) 197.
- [5] Butler J.E., J.Cryst. Growth, 77 (1986) 163.
- [6] Cleland T.A. and Hess D.W., J. Vac. Sci. Technol. B, 7 (1989) 35.
- [7] Salim S., Lim C.K. and Jensen K.F., SPIE, 2069 (1993) 132.
- [8] Farquharson S., Carangelo R.M., Haigis J.R., Morrison P.W., Solomon P.R., Kirklin P.S. and Van Buskirk P.C., SPIE Proc. on: Optical Methods for Chemical Process Control, Boston, September 1993, p. 2.
- [9] Hopfe V., Wagner D., Klobes P., Herzig S. and Marx G., J. Molecular Structure, 217 (1990) 115-130.
- [10] Allendorf M.D. and Melius C.F., J. Phys. Chem., 97 (1993) 720.
- [11] Mosebach H., Erhard M., Resch M. and Bittner H., SPIE Proc. on "Optical Methods for Chemical Process Control" Boston, USA, Sept. 1993.