Theoretical and Experimental Study of the Substrate Effect on the Fully Depleted SOI MOSFET at Low Temperatures

M. Pavanello, J. Martino, J.-P. Colinge

► To cite this version:

M. Pavanello, J. Martino, J.-P. Colinge. Theoretical and Experimental Study of the Substrate Effect on the Fully Depleted SOI MOSFET at Low Temperatures. *Journal de Physique IV Proceedings*, 1996, 06 (C3), pp.C3-67-C3-72. 10.1051/jp4:1996310 . jpa-00254228

HAL Id: jpa-00254228

<https://hal.science/jpa-00254228>

Submitted on 1 Jan 1996

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Theoretical and Experimental Study of the Substrate Effect on the Fully Depleted SOI MOSFET at Low Temperatures

M.A. Pavanello, J.A. Martino and J.-P. Colinge*

Laboratório de Sistemas Integráveis, Universidade de São Paulo, Brazil

**Laboratoire de Microélectronique, Université Catholique de Louvain, Belgium*

Abstract. In this work is presented a theoretical and experimental analysis of the substrate potential drop and your influence on the fully depleted SOI MOSFET threshold voltage. This study is done at room temperature and at liquid nitrogen temperature. Good agreement was found between the simple model and experimental results.

1. INTRODUCTION

The influence of the underlying substrate on SOI MOSFET operation, i. e. Substrate Effect, has been considered negligible in the classical models that describe the coupling in SOI structure as a function of the voltage applied in the front and back gate.

The first approach in order to develop a simple analytical model for substrate potential drop at room temperature was done by Martino et al.[1], where it was demonstrated that the influence of the substrate in the threshold voltage of the SOI MOSFET cannot be neglected under some circumstances depending on the processing parameters and bias conditions. This simple model was generalized later by Pavanello&Martino[2] for all enhancement mode SOI MOSFET at room temperature. An analytical back-gate bias effect model for ultrathin SOI devices was studied later by Sim&Kuo[3].

2. ANALYTICAL MODEL

For thin film fully depleted SOI MOSFETs the coupling between the front and back surface potential (ϕ_{SF} and ϕ_{SB} , respectively) as a function of the front gate voltage (V_{GF}) and back gate voltage (V_{GB}) is described classically by the Lim&Fossum[4] equations (1) and (2):

$$V_{GF} = \phi_{MS1} - \frac{Q_{ox1}}{C_{oxf}} + \frac{q N_{af} t_{Si}}{2 C_{oxf}} + \left(\frac{\epsilon_{Si}}{t_{Si} C_{oxf}} + 1 \right) \phi_{SF} - \frac{\epsilon_{Si}}{t_{Si} C_{oxf}} \phi_{SB} \quad (1)$$

$$V_{GB} = \phi_{MS2} - \frac{Q_{ox2}}{C_{oxb}} + \frac{q N_{af} t_{Si}}{2 C_{oxb}} + \left(\frac{\epsilon_{Si}}{t_{Si} C_{oxb}} + 1 \right) \phi_{SB} - \frac{\epsilon_{Si}}{t_{Si} C_{oxb}} \phi_{SF} \quad (2)$$

where C_{oxf} and C_{oxb} are the front and back oxide capacitance per unit of area respectively; C_{Si} is the Silicon film capacitance per unit of area; N_{af} is the Silicon film dopant concentration; Q_{ox1} and Q_{ox2} are the fixed charge density in the 1st and 2nd interfaces; ϕ_{MS1} and ϕ_{MS2} are the front and back work function differences; V_{FB1} and V_{FB2} are the front and back flatband voltages respectively.

In this model the substrate potential drop (ϕ_{SUB}) is neglected.

The determination of the new equation for ϕ_{SUB} is done using the pseudo-MOS structure (Silicon film - Buried Oxide - Silicon Substrate), resulting the Band Diagram presented in figure 1.

As proposed by [2], solving the Band Diagram presented in figure 1 we obtain:

$$\phi_{SB} - V_{GB} = -\phi_{Siib} + \phi_{Siif} + V_{oxb} + \phi_{SUB} \quad (3)$$

Solving the equation (3) and assuming the depletion approximation the equation for ϕ_{SUB} is given by(4):

$$\phi_{SUB} = \left[\frac{-\sqrt{2q N_{ab} \epsilon_{Si}}}{2C_{oxb}} + \sqrt{\left(\frac{2q N_{ab} \epsilon_{Si}}{4C_{oxb}^2} - V_{FB3} \right) + (\phi_{SB} - V_{GB})} \right]^2 \quad (4); \quad V_{FB3} = \frac{kT}{q} \ln \frac{N_{af}}{N_{ab}} - \frac{Q_{ox3}}{C_{oxb}} \quad (5)$$

where N_{ab} is the Silicon Substrate concentration, Q_{ox3} is the fixed charge density at 3rd interface and V_{FB3} is the flatband voltage for pseudo-MOS structure.

The equation (4) is valid in the interval $0 \leq \phi_{SUB} \leq 2\phi_{Fb}$, where ϕ_{Fb} is the Fermi potential of the underlying substrate. With this interval it is possible to determine the extremes for V_{GB} .

Thus, if $V_{GB} \leq V_{GBmin}$ the 3rd interface will be in inversion ($\phi_{SUB} = 2\phi_{Fb}$) and the maximum influence of the substrate is observed. Otherwise, if $V_{GB} \geq V_{GBmax}$ the 3rd interface will be in accumulation ($\phi_{SUB} = 0$) and there are no influences of the substrate on SOI MOSFET.

To link the equation (4) with the equations (1) and (2) is necessary to add the term $(-\phi_{SUB})$ in equation (2), resulting:

$$V_{GB} = V_{FB2} + \frac{q N_{af} t_{Si}}{2 C_{oxb}} + \left(\frac{\epsilon_{Si}}{t_{Si} C_{oxb}} + 1 \right) \phi_{SB} - \frac{\epsilon_{Si}}{t_{Si} C_{oxb}} \phi_{SF} - \phi_{SUB} \quad (6)$$

In order to estimate ϕ_{SUB} at 77K, the change in the bandgap (E_g), the new values for Fermi potential and the reduction of the effective doping level due to the impurity freeze-out must be accounted in the equations (1), (4) and (6) using the Selberherr's[5] equations.

3. NUMERICAL SIMULATION

The validation of this new model at room temperature and at 77K was performed by numerical bidimensional simulation with MEDICI[6] for a SOI nMOSFET with p-type substrate.

The parameters used in the simulations are:

$$N_{af} = 8 \times 10^{16} \text{ cm}^{-3}; N_{ab} = 1 \times 10^{15} \text{ cm}^{-3}; t_{oxf} = 20 \text{ nm}; t_{oxb} = 400 \text{ nm}; t_{Si} = 50 \text{ nm}; Q_{ox1}/q = 5 \times 10^{10} \text{ cm}^{-2}; Q_{ox2}/q = Q_{ox3}/q = 1 \times 10^{11} \text{ cm}^{-2}.$$

The results of the comparison with the simulation and the solution of the equations system (1), (4) and (6) at room temperature and at 77K are shown in figure 2, where it is possible to observe a good agreement between the numerical simulation and the analytical model.

The analysis of the substrate effect on the threshold voltage[7] at room temperature and at 77K are presented in figures 3A and 3B respectively, where the results obtained solving the simple analytical model equations are compared with MEDICI numerical simulation using structures with and without substrate. The resultant ΔV_{thF} , i. e. the difference between the threshold voltage considering or not the substrate effect is shown.

As observed in figures 3A and 3B, the maximum threshold shift occurs when the 3rd interface is in inversion and increases when the temperature decreases because ϕ_{SUB} becomes higher due to the increase of the Fermi potential.

Using the simple model is possible to study the substrate effect as a function of process parameters variation. As demonstrated by [7] the most important parameter affecting the threshold voltage is the buried oxide thickness which is shown in figure 4. This parameter also influences the subthreshold slope[8].

In figure 4 can be seen that the maximum ΔV_{thF} increases drastically when the buried oxide thickness increases and temperature decreases. In the example, for $t_{oxb} = 80 \text{ nm}$ the maximum ΔV_{thF} changes from 90mV to 230 mV when the temperature changes from 300K to 77K.

4. EXPERIMENTAL RESULTS

Devices were fabricated using 0.5 μm SOI CMOS technology in SIMOX wafers with the characteristics below:

$$N_{af} = 1 \times 10^{17} \text{ cm}^{-3}; N_{ab} = 1 \times 10^{15} \text{ cm}^{-3}; t_{oxf} = 15 \text{ nm}; t_{oxb} = 390 \text{ nm}; t_{Si} = 85 \text{ nm}.$$

The experimental characterization of the substrate effect was done using a SOI nMOSFET with $L=2\mu\text{m}$ and $W=20\mu\text{m}$. Only long channel devices were measured in order to avoid short channel effects which would cause problems in the observation of the shift in the threshold voltage. The threshold voltage was obtained experimentally and by simulation using the current level criteria $I_D=10^{-7}\text{ W/L}$ in curve I_{DS} vs V_{GS} . The experimental I_{DS} vs V_{GS} curves were obtained using the parameter analyzer HP4145B. The bias applied in the devices are $V_{DS}=0.1\text{ V}$, V_{GF} from -0.5 V to 1.5 V step 5 mV and V_{GB} from -1.5 V to 3.5 V step 100 mV at room temperature and V_{GF} from -0.5 V to 1.5 V step 5 mV and V_{GB} from -2.5 V to 3.5 V step 100 mV at 77 K .

The results of the electrical characterization are shown in the figure 5, where it is plotted the curve V_{thF} as a function of V_{GB} obtained at room temperature and at 77 K respectively. In these figures are also plotted the results obtained analytically solving the model equations considering or not the substrate.

As can be seen in figure 5, an excellent agreement was found between the results obtained experimentally and by the solution of analytical model equations at room temperature and at 77 K . In both cases the substrate effect on threshold voltage can be identified and the maximum substrate influence occur when the 3rd interface is in inversion, confirming the theoretical and simulation study.

In the showed curves, when the temperature decreases from 300 K to 77 K the maximum ΔV_{thF} increases from 28 mV to 48 mV becoming significant.

5. CONCLUSION

In this work was presented a simple analytical model for account the potencial drop in the substrate and determine your influence on threshold voltage.

As experimentally demonstrated, the substrate effect on the threshold voltage occurs at room and at liquid nitrogen temperature and cannot be neglected at some process parameters conditions. Mainly at low temperatures the substrate effect becomes higher due to the increase of the Fermi potential. The comparison between the experimental results and modeled results was showed and an excellent agreement was found.

Indeed, the simple analytical model developed is sufficiently powerful for describe the substrate effect on the threshold voltage and should be included in the analytical device simulators, as SPICE for example, to improve the agreement between the experimental and simulated results .

Acknowledgment

The authors would like to thank IMEC for supplying the devices and Marcelo Antonio Pavanello would like to thank FAPESP for financial support to do this work.

References:

- [1] J. A. Martino, L. Lauwers and J. P. Colinge , *Electronics Letters*, Vol. 26, p. 1462, 1990.
- [2] M. A. Pavanello and J. A. Martino, *Proceedings of the IX Congress of Brazilian Microelectronics Society*, p. 546, 1994.
- [3] J. Sim and J. B. Kuo, *IEEE Trans. on Electron Devices*, Vol. 40, p. 755, 1993.
- [4] H. K. Lim and J. G. Fossum, *IEEE Trans. on Electron Devices*, Vol. 30, p. 1244, 1983.
- [5] S. Selberherr, *IEEE Trans. on Electron Devices*, Vol. 36, n. 8, p. 1464, 1989.
- [6] TMA MEDICI, version 5_2_2, Palo Alto, CA, 1992.
- [7] M. A. Pavanello and J. A. Martino, *Proceedings of the X Congress of the Brazilian Microelectronics Society*, p. 537, 1995.
- [8] M. A. Pavanello and J. A. Martino, *Proceedings of the X Congress of the Brazilian Microelectronics Society*, p. 527, 1995.

figure 1 - Band Diagram for pseudo-MOS structure

figure 2 - Comparison between analytical model and MEDICI simulation at room temperature and at 77 K.

SOI nMOSFET - T = 300 K

figure 3A - Influence of the substrate on the threshold voltage at room temperature

SOI nMOSFET - T = 77 K

figure 3B - Influence of the substrate on the threshold voltage at 77K

figure 4 - Maximum ΔV_{th_F} as a function of buried oxide thickness decrement

figure 5 - Comparison between modeled and experimental results for a SOI nMOSFET