Magnetic Structure of Hexagonal Ferrites Studied by Mössbauer Spectroscopy

M. Nejezhleba, Z. Simsa, K. Zaveta

► To cite this version:

M. Nejezhleba, Z. Simsa, K. Zaveta. Magnetic Structure of Hexagonal Ferrites Studied by Mössbauer Spectroscopy. Journal de Physique IV Proceedings, 1997, 07 (C1), pp.C1-345-C1-346. 10.1051/jp4:19971139 . jpa-00254782

HAL Id: jpa-00254782

<https://hal.science/jpa-00254782>

Submitted on 1 Jan 1997

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Magnetic Structure of Hexagonal Ferrites Studied by Mössbauer Spectroscopy

M. Nejezchleba, Z. Šimša* and K. Závěta*

Joint Laboratory of Mössbauer Spectroscopy, KFNT-MFF UK, V Holešovičkách 2, 180 00 Praha 8, Czech Republic

* Institute of Physics, Academy of Sciences of the Czech Republic, Cukrovarnická 10, 162 00 Praha 6, Czech Republic

Abstract: Hexagonal Ba-ferrites of M-type ($\text{BaFe}_{12}\text{O}_{19}$) and W-type ($\text{BaMe}^{2+}_2\text{Fe}^{3+}_{16}\text{O}_{27}$, Me -divalent cation) are promising materials for perpendicular magnetic recording. For this purpose it is desirable that their high uniaxial anisotropy be adjustable according to the specific requirements. Substitution of Co^{2+} for Fe^{2+3+} cations usually decreases the magnitude of the uniaxial anisotropy and may be used to this end.

In this work the influence of Co^{2+} content on the details of magnetic structure of Ba-hexaferrites is studied.

Mössbauer spectra of ^{57}Fe in single crystals of $\text{BaFe}_{12-2x}\text{Co}^{2+}_x\text{Ti}^{4+}_x\text{O}_{19}$ and $\text{Ba}(\text{Fe}_{2-x}\text{Co}_x)^{2+}\text{Fe}_{16}\text{O}_{27}$ were measured at 293K. The dependence of the canting of magnetic moments on the concentration of Co was determined from the relative intensities of Mössbauer lines in the Zeeman nuclear multiplet and compared with the results deduced from the magnetic measurements.

1. INTRODUCTION

Hexagonal Ba-ferrites of M- and W-types are two from several magnetic iron oxides based on a *hcp* structure of oxygen divalent ions. The magnetic structure of both of these types is then given by strong superexchange interactions between magnetic cations via oxygens. Here lies the origin of the uniaxial anisotropy found with these types of Ba-hexaferrite. These hexaferrites may prove suitable for perpendicular recording. One of the requirements is, however, a special range of the anisotropy field values. Replacing of iron ions by some other ones with different single-ion anisotropy contribution might lead to lower anisotropy. The present experience, however, shows that some more complex changes in moment arrangement in the magnetic structure. When Co^{2+} is used as a substitution, the magnetic moments in various magnetic sublattices tend to cant from the hexagonal *c*-axis direction. The main aim of this work is to study in details of the magnetic structure of the mentioned structures by two different methods: magnetization measurements and Mössbauer spectroscopy.

2. EXPERIMENTAL

2.1 Characterisation of samples

Two series of single crystals barium hexaferrites of M- and W-types with various content of Co have been used for magnetic measurements. (For denotation see Tab. 1). Both series included platelet-shaped samples of ~50µm thickness prepared by grinding and polishing along hexagonal basal plane. A surface treatment has been performed in order to suppress the influence of deforming the surface.

Sample	Co content
M0	0
M1	0.11
M4	0.35
M8	0.78
W0	0
W1	1
W2	2

Tab. 1: Denotation of samples

2.2 Magnetic measurements

A SQUID magnetometer has been used for measuring the W-series of samples and a vibrated sample magnetometer for the M-series samples at room temperature. Both series have been measured along the hard magnetization direction. Values of anisotropy field have been estimated from the measured magnetization curves without consideration of higher anisotropy constant contributions. The canting

Fig. 1: Mössbauer spectra of selected samples of M- and W-series; the tags (I) entitle parts of spectra reflect the changes of the magnetic structure

angle of magnetization θ_M , with respect to the c-axis, was estimated from the magnitude of the component of M into the hard direction at moderately low fields that should be equal to $M_s \sin \theta_M$.

2.3 Mössbauer spectroscopy

^{57}Fe transmission Mössbauer spectroscopy in constant acceleration mode has been used. All the spectra have been measured at room temperature. The samples have been oriented with the hexagonal axes parallel to the γ -ray propagation direction.

For decomposing the spectra, sextets with the Voight line shapes have been used according to particular ferrite sublattices. The angles θ between magnetic moments on given ions of iron and propagation of a γ -ray have been calculated from ratios of intensities in sextets by well-known expression (see e.g. [1]):

$$\vartheta = \arcsin \sqrt{\frac{2R_{23}}{4 + R_{23}}}, \quad (1)$$

where $R_{23} = I_{2,5}/I_{3,4}$ are ratios of intensities of the 2nd and 5th line to the 3rd and 4th ones in given sextets. The R_{23} value has been fitted by considering the same value for all sextets, except the cases mentioned below.

3. RESULTS AND CONCLUSIONS

The selected spectra together with their fits and the magnetization curves are shown in figs. 1 and 2, respectively. The final results are summarized in Tab. 2. Since the samples were of very similar shape, we did not correct values of anisotropy field for the demagnetization field. It is seen that in both structures the Co substitution results in a decrease of the anisotropy field. From the experimental data, in particular from the Mössbauer spectra, it follows that with gradual substitution of Co for Fe in both M- and W-type hexagonal ferrites the magnetization in the sublattices makes an angle with the c-axis. The values of the canting angle θ given in the Tab. 2 correspond to an effective angle common to all sublattices. The detailed analysis of the Mössbauer spectra of the samples M5-8 indicates that the canting is not homogeneous and that its value is higher for the sublattice where Co is substituted [2]. The agreement between the conclusions about the changes of magnetization arrangement with Co substitutions derived from the magnetization measurements and Mössbauer spectra is found satisfactory.

Acknowledgement

The help of Dr. M. Maryško with magnetic measurements is gratefully acknowledged.

References

- [1] Gonser U.: Mössbauer Spectroscopy I., Springer-Verlag, Berlin-Heidelberg-New York, 1975, p. 29
- [2] Lego S.: Ph.D. Thesis, Faculty of Mathematics and Physics, Charles University, Prague, 1995

Fig. 2: Magnetization curves for M- (top) and W-series (bottom)

Denot. of sam.	Cont. of Co	H_A [kOe]	θ_M [°]	θ [°]
M0	0	16.9	0	0
M1	0.11	-	-	11
M5	0.35	13.7	~ 0	13
M8	0.78	5.6	18	20
W0	0	18	0	0
W1	1	6.0	35	23
W2	2	0.9(5)	60	64

Tab. 2: Table of final results; H_A .. anisotropy field, θ_M and θ .. deviation of magnetization from c-axes derived from magnetization curves and Mössbauer spectra, resp.