Crystal Oriented Manganese Zinc Ferrites Made from Acicular Fine Particles

N. Hiratsuka, K. Kakizaki, M. Sugimoto

► To cite this version:

N. Hiratsuka, K. Kakizaki, M. Sugimoto. Crystal Oriented Manganese Zinc Ferrites Made from Acicular Fine Particles. Journal de Physique IV Proceedings, 1997, 07 (C1), pp.C1-69-C1-70. 10.1051/jp4:1997115 . jpa-00254794

HAL Id: jpa-00254794

<https://hal.science/jpa-00254794>

Submitted on 1 Jan 1997

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Crystal Oriented Manganese Zinc Ferrites Made from Acicular Fine Particles

N. Hiratsuka, K. Kakizaki and M. Sugimoto*

*Department of Functional Materials Science, Faculty of Engineering, Saitama University,
255 Shimo-Ohkubo, Urawa 338, Japan*

** Department of Culture Information, Teikyo Heisei University, Uruido, Ichihara 290-01, Japan*

Abstract

The acicular Mn-Zn ferrite fine particles composed of 65.6 mol% Fe, 21.9 mol% Mn and 12.5 mol% Zn were made. These Mn-Zn ferrite particles were etched in 1N-HCl solution for 3hrs.. The fine particle was made up of several crystallites whose long axis were 0.2-1.0 μ m, and arranged to $\langle 311 \rangle$ direction. These fine particles were pressed with applying magnetic field. The oriented Mn-Zn ferrites were prepared by sintering at 1250°C for 4hrs. in air and then cooling in nitrogen atmosphere. The oriented Mn-Zn ferrite exhibited strong crystal orientation similar to the single crystal of it. The magnetic anisotropy constants were $K_1=2.5 \times 10^3$ erg/cc and $K_2=-0.2 \times 10^3$ erg/cc and the easy magnetization axis was $\langle 100 \rangle$ direction.

1. Introduction

Single-crystal Mn-Zn ferrites, which have high saturation magnetization and initial permeability, are widely put into practice as high density magnetic head. However, they can't been used at high frequency of 1 MHz or above because of low resistivity. On the other hand, polycrystalline Mn-Zn ferrites, whose saturation magnetization and initial permeability are not good as those of single-crystal Mn-Zn ferrites, can improve magnetic characteristics at high frequency by forming high resistive boundary layers. We therefore prepare crystal oriented Mn-Zn ferrites whose crystallites are oriented like those of single-crystal as well as form high resistivity layers at grain boundary. The reports of the crystal oriented soft ferrites were few : the Mn-Zn ferrite was formed by using hexagonal platelet α -Fe₂O₃ and α -MnOOH. [1,2] In this paper, preparation procedure, crystal orientation and magnetic properties of the crystal oriented Mn-Zn ferrites are presented.

2. Experimental

The starting materials were acicular goethite (α -FeOOH), of the order of around 3.5 μ m long axis and aspect ratio of around 35, as well as Mn(C₅H₇O₂)₃ and Zn(C₅H₇O₂)₂. These were weighed to compose of 65.6mol% of Fe, 21.9mol% of Mn and 12.5mol% of Zn, and then well-mixed in the solvent of water and ethanol. The acicular Mn-Zn ferrite fine particles were prepared when heated at 900°C for 4hrs. in nitrogen gas atmosphere. After these fine particles were dispersed in 70% of slurry concentration by using wet ball-milling method, they were pressed at 200kg/cm² by the wet press method being applied 12kOe(960kA/m) of magnetic field. The samples which were also pressed applying no magnetic field for comparing with above-mentioned samples. The oriented Mn-Zn ferrites were prepared when they were heated at 1250°C for 4hrs. in air and then cooled in nitrogen gas atmosphere.

3. Results and discussion

Photo 1 shows SEM photograph of the acicular Mn-Zn fine particles ($M_s=68.8$ emu/g) having about 2 μ m of long axis and about 15 of aspect ratio. Photo 2 shows SEM photograph of the fine particle which was etched in 1N-HCl for 3hrs. Several crystallites having 0.2-1.0 μ m of long axis arranged to $\langle 311 \rangle$ in the parallel direction to its long axis.

Figure 1 shows a scheme of press and applied magnetic field direction for the cubic shaped Mn-Zn ferrite. Oriented Mn-Zn ferrite were made as follows. The pressed bodies were sintered at 1250°C for 4 hrs. in air and then cooled in nitrogen gas.

Figure 2 shows x-ray diffraction patterns of the sample as shown in fig.1. The sample indicates intense crystal orientation :

(311) plane in (a), (100) plane in (b) and (110) plane in (c). Figure 3 shows a torque curve of the oriented Mn-Zn ferrite measured for (c) plane as shown in fig 1. The curve was distorted comparing with sine wave in the vicinity of 150° to 210°. When the curve was analyzed and calculated anisotropy constants, K_1 and K_2 were 2.5×10^3 erg/cc and -0.2×10^3 erg/cc, respectively.

The easy magnetization axis of the oriented Mn-Zn ferrite corresponds to $\langle 111 \rangle$ direction as a result of $K_1 > 0$. Toroidal cores of the oriented Mn-Zn ferrite bulk were prepared to investigate dependence of initial permeability on frequency. Three kinds of toroidal cores were prepared to press by wet method with applied magnetic field: sample (A) was pressed between same magnetic poles, sample (B) between different poles and sample (C) without magnetic field. These were sintered by the above-mentioned process. Figure 4 shows dependence of initial permeability on frequency for the samples. The sample (A) shows the highest value of initial permeability. This is because the $\langle 100 \rangle$ direction of the easy magnetization axis arranged parallel to flux. As a result of x-ray diffraction analysis, the crystal orientation of the sample (A), (B) and (C) arranged parallel to the $\langle 100 \rangle$, $\langle 111 \rangle$ and $\langle 110 \rangle$ direction, respectively.

4. Conclusion

- 1) The acicular Mn-Zn ferrite fine particles composed of 65.6 mol% Fe, 21.9 mol% Mn and 12.5 mol% Zn were fabricated by sintering at 900°C for 4hrs. in nitrogen gas atmosphere. The fine particles, of the order of 2μm long axis and 15 of aspect ratio, have 68.8 emu/g of saturation magnetization.
- 2) These Mn-Zn ferrite particles were etched in 1N-HCl solution for 3hrs.. The fine particle was made up of several crystallites whose long axis were 0.2-1.0μm, and arranged to $\langle 311 \rangle$ direction.
- 3) These fine particles were pressed with applying magnetic field. The oriented Mn-Zn ferrites were prepared by sintering at 1250°C for 4hrs. in air and then cooling in nitrogen atmosphere.
- 4) The oriented Mn-Zn ferrite exhibited strong crystal orientation similar to the single crystal of it. The magnetic anisotropy constants were $K_1 = 2.5 \times 10^3$ erg/cc and $K_2 = -0.2 \times 10^3$ erg/cc and the easy magnetization axis was $\langle 100 \rangle$ direction.

References

[1] K.Kugimiya : IEEE Trans. Mag., 10 (1974) 907.
[2] E.Hirota : IEEE Trans. Mag., 7 (1971) 337.

Fig.2 X-ray diffraction patterns measured in the three dimensional directions of crystal-oriented manganese zinc ferrite sintered at 1250 °C.

Photo.1 SEM micrograph of acicular manganese zinc ferrite particles sintered at 900°C.

Photo.2 SEM micrograph of chemically etched acicular manganese zinc ferrite particles.

Fig.1 Schematics of the process of making crystal-oriented Mn-Zn ferrites.

Fig.3 Magnetic torque curve of the oriented Mn-Zn ferrite measured for (c) plane as shown in fig.1.

Fig.4 Dependence of initial permeability on frequency for the samples.