Magnetic and Magneto-Optical Properties of Nano-Size Bi-YIG Particles Dispersed in a Plastic Binder

Y. Yamazaki, T. Namimawa, T. Hirano, K. Yoshida

► To cite this version:

Y. Yamazaki, T. Namimawa, T. Hirano, K. Yoshida. Magnetic and Magneto-Optical Properties of Nano-Size Bi-YIG Particles Dispersed in a Plastic Binder. *Journal de Physique IV Proceedings*, 1997, 07 (C1), pp.C1-543-C1-544. 10.1051/jp4:19971223 . jpa-00254896

HAL Id: jpa-00254896

<https://hal.science/jpa-00254896>

Submitted on 1 Jan 1997

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Magnetic and Magneto-Optical Properties of Nano-Size Bi-YIG Particles Dispersed in a Plastic Binder

Y. Yamazaki, T. Namimawa, T. Hirano* and K. Yoshida*

Tokyo Inst. Tech., Nagatsuta, Midori-ku, Yokohama, 226 Japan

* Toppan Printing, TRI, Takanodai-minami, Sugito, Saitama, 345 Japan

Abstract. Magneto-optical films were prepared by coating nano-size Bi-YIG particles, the Faraday rotation of the films were measured. The particle size was changed by milling with a planetary milling machine from 1 h to 100 h. The magnetic and magneto-optical properties were measured. The M_s of the films dropped with milling time, however, the peak values of Faraday rotation increased. The Faraday rotation spectra of the films changed with particle size. These results indicate that the magneto-optical properties of the coated films differ from those of sputtered films. The figure of merit of the coated films was 3.0 and comparable to that of sputtered films.

1. INTRODUCTION

Thin films of bismuth substituted yttrium iron garnet (Bi-YIG) are expected to be applied to magneto-optical devices. We have reported that the Faraday rotation spectra of particle-coated films differ from sputtered films [1]. The origin of the spectrum change was presumed to be the change in the interactions between Bi-YIG particles and binder. In this paper, we study the magnetic and magneto-optical properties of the coated films which were made with various size particles.

2. EXPERIMENTAL

The $\text{Bi}_{1.8}\text{Y}_{1.2}\text{Fe}_5\text{O}_{12}$ particles were prepared by coprecipitation and annealing processes [2]. The crystal phases in the particles were examined by X-ray diffraction analysis. The particles were mixed with an epoxy binder and cyclohexanone. Then the mixtures were milled with a planetary milling machine from 1 to 100 h. The particles were coated by a spin coater. The particles in the films were observed by an atomic-force microscope (AFM). The magnetic properties were measured with a VSM. Absorption coefficient α were measured by a spectrophotometer. Faraday rotation θ_F were measured by the polarization modulation method.

3. RESULTS

Figure 1 shows an AFM image of the coated particles which were milled for 30 h. The size of the particles is about 15 nm. It is noted that the size of the particles is uniform. The mean size of the particles is smaller than the wavelength of visible light. The size of the particles did not change when the milling time extended to 100 h. This result suggests that the size of the primary particles is about 15 nm.

Figure 2 shows the saturation magnetization M_s and in-plane coercive force H_c of the films as a function of the milling time. The M_s and H_c are divided by milling time. The M_s and H_c are dropped during the 1 ~ 30 h milling. This result shows that the non-magnetic surface parts of the particles are increased by pulverization [3]. After 30 h milling, the magnetic properties of the films did not change with the milling time.

Fig. 1 An AFM image of the Bi-YIG particles coated with a binder.

Figure 3 shows the Faraday rotation spectra of the coating films. The films containing particles milled over 20 h show the Faraday rotation spectra which are similar to those of Bi-YIG sputtered films. However, the 1 to 20 h milled films do not show similar spectrum. The lights were scattered by the Bi-YIG particles in the films which were milled 1 to 20 h, because the size of the particles is nearly equal to the wavelength of the measuring light.

Figure 4 shows θ_F and α of the films as a function of the milling time. The α decreased with milling time. The peak values of Faraday rotation increased with milling time, although the M_s of the films dropped.

The figure of merit of the coating films as a function of the milling time is shown in Fig. 5. The maximum figure of merit was obtained with the coating film containing 30h-milled particles. The figure of merit of the coated films was 3.0 and comparable to that of sputtered films [4].

4. CONCLUSIONS

Nano-size Bi-YIG fine particles were synthesized. Thin films were prepared by coating the fine particles milled from 1 to 100 h. Magnetic and magneto-optical properties of the films were measured.

The peak values of Faraday rotation increased with milling time, however, the M_s of the films dropped. The Faraday rotation spectrum of the films was changed with particle size. These results indicate that the magneto-optical properties of Bi-YIG nano-size particle coating films differ from those of sputtered films.

The figure of merit of the coated films was 3.0 and comparable to that of sputtered films. The Bi-YIG coating film is a new material for magneto-optical devices.

References

[1] T. Hirano, T. Namikawa and Y. Yamazaki, *DENKI KAGAKU*, **64**(4), 307 (1996).
[2] T. Hirano, T. Namikawa and Y. Yamazaki, *IEEE Trans. Magn.*, **31**(6), 3280 (1995).
[3] A. H. Morrish and K. Haneda, *J. Magn. Magn. Mater.*, **35**, 105 (1983).
[4] M. Gomi, T. Taneda and M. Abe, *J. Appl. Phys.*, **57**(1), 3888 (1985).

Fig.2 Saturation magnetization and coercive force as a function of the milling time.

Fig.3 Faraday rotation spectra of Bi-YIG coating films.

Fig.4 Faraday rotation θ_F and absorption coefficient α as a function of the milling time.

Fig.5 Figure of merit as a function of the milling time.