XAS Study on the Intermediate Species Formed During the Surface Oxidation of CrN Films

F. Esaka, K. Furuya, H. Shimada, M. Imamura, N. Matsubayashi, T. Sato, A. Nishijima, T. Kikuchi, A. Kawana, H. Ichimura

► To cite this version:

F. Esaka, K. Furuya, H. Shimada, M. Imamura, N. Matsubayashi, et al.. XAS Study on the Intermediate Species Formed During the Surface Oxidation of CrN Films. *Journal de Physique IV Proceedings*, 1997, 7 (C2), pp.C2-1149-C2-1150. 10.1051/jp4:19972167 . jpa-00255231

HAL Id: jpa-00255231

<https://hal.science/jpa-00255231>

Submitted on 1 Jan 1997

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

XAS Study on the Intermediate Species Formed During the Surface Oxidation of CrN Films

F. Esaka, K. Furuya, H. Shimada*, M. Imamura*, N. Matsubayashi*, T. Sato, A. Nishijima*, T. Kikuchi**, A. Kawana*** and H. Ichimura***

Department of Applied Chemistry, Faculty of Science, Science University of Tokyo, 1-3, Kagurazaka, Shinjuku-ku, Tokyo 162, Japan

** National Institute of Materials and Chemical Research, 1-1, Higashi, Tsukuba, Ibaraki 305, Japan*

*** Science University of Tokyo in Yamaguchi, 1-1-1, Daigakudori, Onoda, Yamaguchi 756, Japan*

**** Sumitomo Metal Mining Co. Ltd., 3-18-5, Nakakokubun, Ichikawa, Chiba 272, Japan*

Abstract. XAS was applied to the identification of the intermediate species formed during the surface oxidation of CrN films. The N K-edge XAS spectra indicated formation of an intermediate species which gave a feature at 401.4 eV. A high resolution XAS spectrum exhibited that the feature at 401.4 eV has the same vibration splitting as that of gaseous N₂. It was also found that the species assigned to molecular N₂ occurred in the interstitial position of the surface oxide layer in the oxidized films. The result implied the importance of high energy resolution XAS in the field of material science.

1. INTRODUCTION

CrN is used for surface coatings to improve the hardness and corrosion resistance of various mechanical tools. During the use under an oxidizing atmosphere at a high temperature, these film properties fail due to the formation of surface oxide layer. There have been several studies on the surface oxidation mechanisms of CrN films [1], however, no detailed discussion was carried out on the intermediate species during surface oxidation. In previous reports [2,3], we investigated the surface oxidation of CrN films by x-ray absorption spectroscopy (XAS) and suggested that molecular N₂ is formed in the interstitial position of the surface oxide layer. The purpose of the present study is to obtain the evidence which shows that the intermediate species is molecular N₂. In addition, in-depth distribution of the nitrogen species is investigated by changing the analysis depth of XAS.

2. EXPERIMENTAL PROCEDURE

CrN films with a thickness of 3 μm were deposited on austenite stainless steel by a cathodic arc ion-plating method. The deposition procedures were described in detail in a previous report [4]. Surface oxidation of the CrN film was performed at 400 °C for 1 h in a flow of dry air (50 cm³ / min.). All XAS measurements were performed at the BL-13C of the Photon Factory [5]. The angle between the incident x-ray and the sample surface was set at 90°. XAS spectra were recorded with total electron yield (TEY), partial electron yield (PEY) with a retarding voltage of 270 V and x-ray fluorescence yield (FY) modes. All the spectra were normalized by dividing the signals by the signals recorded by a gold mesh located at the upstream side of the sample.

3. RESULTS AND DISCUSSION

Fig. 1 shows the N K-edge XAS spectra of the CrN films before and after surface oxidation. The TEY spectrum of the film before surface oxidation exhibits only the features assigned to CrN. In the PEY and TEY spectra of the oxidized film, a sharp feature attributed to an intermediate species is observed at 401.4 eV with a full width at half maximum (FWHM) value of 0.7 eV besides the CrN features. This feature is scarcely observed in the FY spectrum. Probing depths for each detection mode is <20 Å in PEY, 20-100 Å in TEY and > 1000 Å in FY. This indicates that the intermediate species is present predominantly in the surface oxide layer of the oxidized film.

In previous reports [2,3], we assigned the feature at 401.4 eV to molecular N₂ by comparing the photon energies of the features. To confirm the assignment, N K-edge XAS spectra of gaseous N₂ have been measured and compared with that of the oxidized film as shown in Fig. 2. The obtained spectra are fitted by a least-square method using mixed Gaussian-Lorentzian envelopes with a fixed Lorentzian width of 128 meV. The obtained Gaussian width corresponds to the line-width of the incident x-ray, indicated as

ΔE in Fig. 2. When the entrance and exit slit widths are quite narrow, well split vibration structures are observed as shown in Fig. 2(c). However, the signal intensity from the oxidized film is not high enough to measure the spectrum under the same instrumental conditions. Thus, the spectrum is compared with the spectrum of molecular N_2 measured at a moderate energy resolution of $\Delta E = 210$ meV. The comparison evidently indicates that the intermediate species in the oxidized film is molecular N_2 . The vibration splitting precludes the formation of atomic nitrogen which was suggested by Soriano et al. [6].

In conclusion, the present high resolution XAS result has confirmed the assignment that the intermediate species in the oxidized CrN film is molecular N_2 . This indicates the importance of the high resolution XAS for material science. In addition, it is found that XAS can be used for acquiring in-depth information by using various detection modes.

Figure 1 : N K-edge XAS spectra of CrN films before and after surface oxidation

Figure 2 : High resolution N K-edge XAS spectra of oxidized CrN film and N_2 gas

Acknowledgements

This work has been performed with the approval of the Photon Factory Programme Advisory Committee (PF-PAC No. 96-G144). F. E. was grateful for the Research Fellowships of the Japan Society for the Promotion of Science for Young Scientists.

References

- [1] S. Hofmann and H. A. Jehn, *Surf. Interface Anal.* 12 (1988) 329-333.
- [2] F. Esaka, H. Shimada, M. Imamura, N. Matsubayashi, T. Sato, A. Nishijima, A. Kawana, H. Ichimura, T. Kikuchi and K. Furuya, *Thin Solid Films*, in printing.
- [3] F. Esaka, H. Shimada, M. Imamura, N. Matsubayashi, T. Sato, A. Nishijima, A. Kawana, H. Ichimura, T. Kikuchi and K. Furuya, *J. Vac. Sci. Technol. A*, submitted.
- [4] H. Ichimura and A. Kawana, *J. Mater. Res.* 9 (1994) 151-155.
- [5] N. Matsubayashi, H. Shimada, K. Tanaka, T. Sato, Y. Yoshimura and A. Nishijima, *Rev. Sci. Instrum.* 63 (1992) 1363-1366.
- [6] L. Soriano, M. Abbate, J. C. Fuggle, C. Jimenez, J. M. Sanz, L. Galan, C. Mythen and H. A. Padmore, *Surf. Sci.* 281 (1993) 120-126.